

**DEVELOPMENT OF HYBRID CEMENTITIOUS  
COMPOSITE (HCC) FOR SUSTAINABLE  
CONSTRUCTION IN SEA WATER  
ENVIRONMENT**

**ALONGE OLAYIWOLA RICHARD**

**UNIVERSITI SAINS MALAYSIA**

**2016**

**DEVELOPMENT OF HYBRID CEMENTITIOUS  
COMPOSITE (HCC) FOR SUSTAINABLE  
CONSTRUCTION IN SEA WATER  
ENVIRONMENT**

**by**

**ALONGE OLAYIWOLA RICHARD**

**Thesis submitted in fulfilment of the requirements  
for the degree of Doctor of Philosophy**

**MARCH 2016**

## **DEDICATION**

I dedicate this research study to the Almighty God, my wife and children, Oluwaseye Caroline Alonge, Esther Temiloluwa Alonge and Michael Oluwatimilehin Alonge, my late father, Mr. Isaac Oluwole Alonge and my mother, Mrs Victoria Alonge.

## ACKNOWLEDGEMENT

First and foremost, my heartfelt gratitude is towards the Almighty God for endowing me with the grace, opportunity, support and spiritual backing to complete my PhD study.

I wish to express my sincere gratitude to my supervisor and adopted father, Professor, Dato' Dr.Mahyuddin B. Ramli for his unrelented efforts, conscious advice, guidance, encouragement, enthusiasm and constant financial support.

My appreciation goes to all the technical staffs of the School of Housing, Building and Plannings' structure and concrete laboratory, wood and metal laboratory. Likewise, all the support and help of all other administrative staffs of the School of HBP are noted and appreciated.

In the same vein, I wish to appreciate the Universiti Sains Malaysia (USM) management for the Postgraduate research grant (1000/PPBGN/846112) fund granted to me as well as the USM graduate assistance scheme award.

I will love to appreciate the entire pastorate, the management committee members, as well as all the members of Tabernacle of Grace Church, Penang, Malaysia.

My regards goes to all my co-PhD candidates in the research room of School HBP.

Finally, I appreciate my lovely wife and children, my mother and my siblings. Mrs. Oluwaseye Caroline, Esther Temiloluwa, Michael Oluwatimilehin, Madam Victoria Olutayo for their unflinching love, support and prayers coupled with their endurance during the journey of almost five years of my Master degree and PhD.

I say thanks to you all.

## TABLES OF CONTENTS

	Page
<b>DEDICATION</b>	
<b>ACKNOWLEDGEMENT</b>	<b>ii</b>
<b>TABLE OF CONTENTS</b>	<b>iii</b>
<b>LIST OF TABLES</b>	<b>xi</b>
<b>LIST OF FIGURES</b>	<b>xv</b>
<b>LIST OF ABBREVIATION</b>	<b>xxii</b>
<b>ABSTRAK</b>	<b>xxiii</b>
<b>ABSTRACT</b>	<b>xxv</b>
<b>CHAPTER ONE: INTRODUCTION</b>	
1.1 Introduction	1
1.2 Background of the Research Study	1
1.3 Statement of Problem	10
1.4 Aim and Objectives	14
1.5 Research Significance	15
1.6 Scope of Work	16
1.7 The thesis Layout	19
<b>CHAPTER TWO: LITERATURE REVIEW</b>	
2.1 General Appraisal	22
2.2 Historic Issues About Kaolin	22
2.3 Metakaolin	25
2.3.1 Production of Metakaolin	28
2.3.2 Features of Metakaolin	32
2.3.3 Benefits and Uses of Metakaolin	33

2.3.4 Calcination Process	33
2.3.5 MK Reaction Techniques	34
2.3.6 Temperature Effects on Pozzolanic Reaction of MK	37
2.3.7 Porosity Properties of Metakaolin	38
2.3.8 Early Age Properties of Concrete and Mortar Containing Metakaolin (MK)	41
2.3.8 (a) Slump	41
2.3.8 (b) Setting Time	44
2.3.8 (c) Shrinkage	47
2.3.8 (d) Hardened Mortar/Concrete Properties	49
2.4 Evolution Of Engineered Cementitious Composites	72
2.4.1 Major Physical Properties of ECC	74
2.4.2 ECC Material Design Factors	75
2.4.3 ECC Mixture Proportioning, Material Processing and Quality Control	77
2.4.4 Application of ECC	81
2.5 Influence of Fibre in Concrete	82
2.5.1 Mechanism of Crack Control Using Short Discrete Fibres	84
2.5.2 Hybrid Fibres in Cementitious Composites	87
2.5.3 Micro Mechanic Model for Cementitious Composites Mybrid Fibre Design	91
2.5.4 Fibre Influence on Shrinkage of Concrete	95
2.5.5 Fibres Features in Reinforced Concrete	97
2.5.6 Fibres Strength and Toughness Features in Reinforced Concrete	98
2.5.7 Fibres Influence on Concrete permeability	103

2.5.8 Natural Fibres	106
2.5.9 Coconut Fibre Reinforced Concrete Properties	109
2.5.10 Oil Palm Fruit Bunch Fibres	118
2.5.11 Properties and Morphology of Oil Palm Empty Fruit Bunch	119
2.5.12 Polyolefin Fibres	121
2.6 Nanomaterials in the Sustainable Building Materials	123
2.6.1 Nanoparticles in Concrete	125
2.6.2 Mechanical Properties of Nanoparticle Concrete	126
2.6.3 Durability Properties of Nanoparticle Concrete	127
2.6.4 Effect of Nanoparticles on Calcium Leaching	130
2.7 Epoxy in Concrete	131
2.8 Concrete in Sea Water	133
2.8.1 Sulphate Attacks	134
2.9 Sustainable Construction	136
2.10 Critical Summary	137

### **CHAPTER THREE: EXPERIMENTAL PROGRAMME AND MATERIAL CHARACTERIZATION**

3.1 Introduction	142
3.2 Objective of the Experiment	142
3.3 Materials	143
3.3.1 Physical Properties of Binder and Fibre Materials	144
3.3.2 Metakaolin (MK)	144
3.3.3 Nanosilica	146
3.3.4 Epoxy Resin	146
3.3.5 Fine Aggregates (Natural Sand)	147

3.3.6 Water	148
3.3.7 Superplasticiser	148
3.3.8 Coconut Fibre	149
3.3.9 Oil Palm Empty Fruit Bunch Fibre	150
3.3.10 Synthetic Fibre (Barchip)	152
3.4 Experimental Programme	153
3.5 Exposure Conditions	157
3.6 Calcination of Kaolin for Metakaolin Production	157
3.7 Characterization of binder materials	158
3.7.1 Particle Size Analysis	159
3.7.2 Determination of Binders Specific Gravity	160
3.7.3 X-ray Fluorescence Analysis (XRF)	161
3.7.4 X-ray Diffraction Analysis	162
3.7.5 Loss on Ignition	163
3.8 The Determination of Blended Cement Pastes Rheology and Setting Times	164
3.9 Laboratory Investigation on Engineering Properties of Hybrid Cementitious Composite	165
3.9.1 Rheological Properties	165
3.9.2 Mechanical Properties	166
3.10 Durability Properties and Shrinkage Behaviour of HCC Materials	177
3.11 X – RAY Diffraction Test	194
3.12 Scanning Electron Microscopy	195
3.13 Structural Behaviour of HCC Panel	199
3.13.1 Fabrication of Test Specimen	200

3.13.2 Flexural Test Set Up for HCC Panels	202
3.14 Structural Behaviour of HCC Reinforced Beam	203
3.14.1 Fabrication of Test Specimen	204
3.14.2 Test Setup for the Four Point Bending Test of HCC Beam	205
3.15 Mix Design	207
3.16 Research Specimens Preparation	213
3.16.1 Fabrication of HCC Prisms	214
3.16.2 Fabrication of HCC Cubes	215
3.17 Exposure Regime	216
3.18 Summary	216

## **CHAPTER FOUR: PROPERTIES OF METAKAOLIN AND ENGINEERING**

### **PROPERTIES OF HYBRID CEMENTITIOUS COMPOSITE**

4.1 Introduction	219
4.2 Morphology, Chemical and Physical Properties of MK	220
4.3 Early Age Engineering Properties of MK-CNS-EPOXY Blended Cement Mortar	229
4.3.1 Standard Consistency of Blended Cement	229
4.3.2 Initial and Final Setting Times of the Blended Cement Paste	230
4.3.3 Workability of HCC Mixes	232
4.3.4 HCC Mixes's Bulk Density	235
4.4 Mechanical Properties of HCC	238
4.4.1 Compressive Strength	238
4.4.2 Splitting Tensile Strength	247
4.4.3 Flexural Strength	249

4.4.4 Relationship Between Compressive Strength and Flexural Strength of HCC	253
4.4.5 Dynamic Modulus of Elasticity	255
4.4.6 Static Modulus of Elasticity	260
4.4.7 Relationship Between Dynamic and Static Modulus	265
4.4.8 Relationship Between Static Modulus and Compressive Strength	267
4.4.9 Relationship Between Dynamic Modulus and Compressive Strength	268
4.5 Ultra Pulse Velocity (UPV) Test	270
4.5.1 Relationship Between UPV and Compressive Strength of HCC	274
4.6 Drying Shrinkage of HCC Specimens	276
4.7 Impact Load Resistance	279
4.7 Summary	281

## **CHAPTER FIVE: DURABILITY PROPERTIES OF HCC MIXES**

5.1 Introduction	285
5.2 Water Absorption	285
5.3 Porosity	288
5.3.1 Relationship Between Total Porosity and Water Absorption	291
5.4 Capillary Absorption	292
5.5 Intrinsic Air Permeability	296
5.5.1 Relationship Between Intrinsic Air Permeability and Water Absorption	299
5.5.2 Relationship Between Intrinsic Air Permeability and Compressive Strength	301

5.5.3 Relationship Between Intrinsic Air Permeability and Total Porosity	302
5.6 Chloride Permeability	303
5.7 Microstructure of MK, CNS-Epoxy Cement Mortar	312
5.8 X-Ray Diffraction and Energy – Dispersive X-ray Spectroscopy (EDX)	328
5.9 Summary	331

## **CHAPTER SIX: STRUCTURAL BEHAVIOUR OF HCC PANELS AND BEAMS**

6.1 Introduction	334
6.2 Flexural Property of HCC Panels	335
6.2.1 First Crack and Ultimate Crack Strengths of HCC Panels	336
6.2.2 HCC Panels Load Deflection Characteristics	334
6.2.3 Stress-Strain Relationship of HCC Panel	339
6.2.4 HCC Toughness Indices	341
6.2.5 HCC Crack Width Development Behaviour	342
6.3 Structural Behaviour of HCC Beams	344
6.3.1 Objectives	344
6.3.2 Specimens Preparation	345
6.3.3 Flexural Property of HCC Beams	347
6.3.4 First Crack and Ultimate Crack Strength of HCC Beams	347
6.3.5 HCC Beams Deflection Characteristics	348
6.3.6 Stress-Strain Relationship of HCC	350
6.3.7 HCC Beams Toughness Indices	352
6.3.8 Flexural Cracking Development of HCC Beam	354

6.4 Summary	358
-------------	-----

## **CHAPTER SEVEN: CONCLUSIONS AND RECOMMENDATIONS**

7.1 Production, Physical and Chemical Properties of MK as Observed in the Laboratory	360
7.2 Setting Features of MK, Quaternary Blended Cement and the Engineering Properties of the Quaternary Blended Cement.	361
7.3 Durability Properties of HCC Mixes	364
7.4 Structural Performance of HCC Panels and Reinforced HCC Beams	366
7.5 Recommendation	368
REFERENCES	370
STANDARDS	402
APPENDIX A	407
LIST OF PUBLICATIONS	409

## LIST OF TABLES

		<b>Page</b>
Table 2.1	Properties of Kaolin	24
Table 2.2	Physical Properties of Selected Pozzolans	28
Table 2.3	Calcinations of Kaolin at 800°C and Heating Hours	31
Table 2.4	Physical Features of Metakaolin	32
Table 2.5	Typical Chemical Composition of MK	32
Table 2.6	Requirement According to the ASTM C618 Specifications	33
Table 2.7	Workability and Setting Time of Concrete With MK	42
Table 2.8	Metakaolin Cement Properties	44
Table 2.9	Water Absorption for Mortars Consists of CEM I 42.5, Metakaolin and Kaolin	50
Table 2.10	Results of Compressive Strengths of Metakaolin-Concrete	52
Table 2.11	Samples and the Compressive Strength	54
Table 2.12	Paste Composition	63
Table 2.13	Chloride Diffusion Rates for Mortar with CEM I 42.5, Metakaolin and Kaolin	64
Table 2.14	Chloride Permeability of Blended and Control Concretes	65
Table 2.15	Creep Results After 200 Days	70
Table 2.16	Total and Autogenous Shrinkage of Concrete	71
Table 2.17	Fundamental Major Physical Properties of ECC	74
Table 2.18	ECC Mix Design Proportion by Weight for ECC- M45	77
Table 2.19	Properties of Fibre, Matrix and Fibre/Matrix Interface	94
Table 2.20	Natural Fibres Lignin and Cellulose Contents	110
Table 2.21	Chemical Composition of OPEFB	120
Table 2.22	Physical-Mechanical Properties of OPEFB	120
Table 3.1	Chemical Composition of Ordinary Portland Cement	144

Table 3.2	Physical Properties of Metakaolin Produced in the Laboratory in % Weight	146
Table 3.3	Physical and Chemical Properties of Nanosilica as Supplied by the Producer	146
Table 3.4	Physical and Chemical Properties as Given by the Manufacturer	147
Table 3.5	Sieve Analysis of the Fine Aggregates	148
Table 3.6	Physical Properties of the Fine Aggregate	148
Table 3.7	Specification of Coconut Fibre	150
Table 3.8	Specification of Oil Palm Empty Fruit Bunch	151
Table 3.9	Chemical Composition of Coconut and Oil Palm Empty Fruit Bunch Fibre as Provided by the Producer	151
Table 3.10	Specification of Barchip Fibre	153
Table 3.11	Outline of the Study's Experimental Programme	155
Table 3.12	Research Methodology Flow Chat for Programmes	156
Table 3.13	Constituents Ions in Fresh Sea Water	157
Table 3.14	Mix Design Proportion by Weight for M45 SCC	207
Table 3.15	Mix Proportions of All the Trial Mix	211
Table 3.16	Compressive and Flexural Strength of the Trial Mixes	211
Table 3.17	Cement and Binder Efficiency of the Mix Proportion	213
Table 3.18	Mix Proportion for All Mixes	214
Table 4.1	Chemical Compounds in Raw Kaolin and Calcined Kaolin (MK)	222
Table 4.2	Particle Size Distribution of MK	226
Table 4.3	Standard Consistency, Initial and Final Setting Time of Blended Cement Pastes	230
Table 4.4	Slump Flow of the HCC Mixes With Superplastizer Dosage	234

Table 4.5	Bulk Density of All Specimens Over the Ages	237
Table 4.6a	Compressive Strength of All HCC Specimens at All the Ages	242
Table 4.6b	Normalized Strength of HCC of All Specimens Over the Ages Against Control Specimens	243
Table 4.7	Splitting Tensile Strength (N/Mm <sup>2</sup> ) of All HCC Specimens at Age 28 Days	247
Table 4.8	Flexural Strengths of all Specimens of All Ages of Exposure	250
Table 4.9	Dynamic Modulus of HCC Specimen	258
Table 4.10	Static Modulus of HCC Specimen	261
Table 4.11	Velocities of Ultrasonic Pulse Through HCC Specimens Over the Ages	271
Table 4.12	Drying Shrinkage of HCC Specimens Over the Ages	277
Table 4.13	Impact Load of HCC Specimens at 28days	279
Table 5.1	Water Absorption of All HCC Specimens Over the Exposure Ages(%)	286
Table 5.2	Total Porosity of All Specimens Over the Ages	289
Table 5.3a	Capillary Test Results for Sea Water Specimens	295
Table 5.3b	Capillary Test Results for Water Specimens	295
Table 5.4	Intrinsic Air Permeability of All HCC Specimens Over the Ages	296
Table 5.5a	Chloride Content in SCC Specimens (% By Weight of Binder)	305
Table 5.5b	Average Chloride Percentage Content, and Percentage Reduction	306
Table 5.6a	EDX for Control Specimen Exposed in Sea Water at EDX Spot 1	331

Table 5.6b	EDX for Base Mix BM Specimen Exposed in Sea Water At EDX Spot 2	331
Table 6.1	Experimental First Crack and Ultimate Failure Load of HCC Panels Under Flexure	337
Table 6.2	Toughness Indices of HCC Specimens	341
Table 6.3	Crack Width and the Number of Cracks of HCC	343
Table 6.4	Experimental First Crack and Ultimate Failure Load of HCC Beam Under Flexure	348
Table 6.5	Toughness Indices of HCC Specimens	353
Table 6.6	Crack Width and the Number of Cracks of HCC	358

## LIST OF FIGURES

		Page
Figure 2.1	Typical View and Colour of Kaolin	25
Figure 2.2	March Flow Cone Test	80
Figure 2.3	Composites Bridging Law	91
Figure 2.4	First Crack Strength ( $\Sigma_{fc}$ ) and Ultimate Bridging Strength ( $\Sigma_{cu}$ )V	94
Figure 2.5	ACI Committee 544 (1996) Definition of Toughness Index	99
Figure 2.6	ASTM C 1018 Definition of Toughness Index	100
Figure 2.7	Barr and Hasso Proposed Definition of Toughness Index	100
Figure 2.8	Natural Fibres Cellular Structure	111
Figure 2.9	Lignin Concentration Between Different Cell Walls of Fibres	111
Figure 2.10	Particle Size and Specific Surface Area Scale Relative to Concrete Materials	125
Figure 3.1	Sample of Metakaolin	145
Figure 3.2	Sample of Coconut Fibre	150
Figure 3.3	Sample of Oil Palm Waste Fruit Bunch Fibre	151
Figure 3.4	Sample of Barchip Fibre	152
Figure 3.5	Laboratory ELLE International Laboratory Muffler Furnace and the Temperature	158
Figure 3.6	Malvern Mastersizer Model of Laser Particle Size Analyzer	160
Figure 3.7	X-Ray Spectrometer Used for the XRF Analysis	162
Figure 3.8	X-Ray Diffraction Machine Used for XRD Analysis	163
Figure 3.9	Laboratory Muffler Furnace	164
Figure 3.10	Flexural Test of Sample Using Gotech Universal Testing Machine	168

Figure 3.11	Splitting Tensile Strength Test Setup	169
Figure 3.12	Test Setup of Static Modulus of Elasticity	171
Figure 3.13	Dynamic Modulus of Elasticity Test	172
Figure 3.14	Electric Pulse Generator with Transducer	173
Figure 3.15	Impact Load Resistance Test Set Up	177
Figure 3.16	Standard Setup of the Intrinsic Air Permeability Test	180
Figure 3.17	Chloride Test Setup	184
Figure 3.18	Water Absorption Test Setup and the Coring Process	188
Figure 3.19	Vacuum Intrusion Porosimetry Test Setup	190
Figure 3.20	Drying Shrinkage Test Setup	191
Figure 3.21	Capillary Test Setup	194
Figure 3.22	Sem. Quanta Feg 650	196
Figure 3.23	Platinum Micro Particle Coating System	198
Figure 3.24	Test Setup for the Flexural Test of Panel	203
Figure 3.25	Test Setup of the Flexural Test of HCC Beam	206
Figure 4.1a	XRD of the Kaolin	223
Figure 4.1b	XRD for the MK Produced in the Laboratory	224
Figure 4.2	DTA/TGA Curve of the Raw Kaolin	225
Figure 4.3a	Particle Morphology of MK at Magnification of 1200 X	226
Figure 4.3b	Particle Morphology of MK at Magnification of 3000 X	227
Figure 4.3c	Plate-Like Structure of MK at Magnificent of 5000 X	227
Figure 4.3d	Plate-Like Structures of MK at Magnificent of 5000 X	228
Figure 4.4a	Average Bulk Density of All HCC Mixtures and Control Cure in Water Over the Ages	237
Figure 4.4b	Average Bulk Density of All HCC Mixtures and the Control Cure in Sea Water Over the Ages	238
Figure 4.4c	Average Bulk Density of All HCC Mixtures and the Control Over	238

	Ages	
Figure 4.5a	Compressive Strength of All HCC Mixes of All Ages (Days)	243
Figure 4.5b	Compressive Strength of HCC Mixes of All Ages (Days) Exposed in Water	244
Figure 4.5c	Compressive Strength of HCC Mixes of All Ages (Days) Exposed in Sea Water	244
Figure 4.6.	Splitting Tensile Strength of All HCC Mixes at Age 28 Days	248
Figure 4.7a	Flexural Strength of Sandwich HCC at Various Exposure Ages	250
Figure 4.7b	Flexural Strength of Sandwich HCC at Various Water Exposure Ages	251
Figure 4.7c	Flexural Strength of Sandwich HCC at Various Sea Water Exposure Ages	251
Figure 4.8a	Correlation Between Compression and Flexural Strength Of Samples Exposed in Water At 28 Days	254
Figure 4.8b	Correlation Between Compression and Flexural Strength of Samples Exposed in Sea Water at 28 Days	254
Figure 4.9a	Dynamic Modulus of Elasticity of HCC at Various Exposure Ages	259
Figure 4.9b	Dynamic Modulus of Elasticity of HCC in Water at Various Exposure Ages	259
Figure 4.9c	Dynamic Modulus of Elasticity of HCC in Sea Water at Various Exposure Ages	260
Figure 4.10a	Static Modulus of Elasticity of HCC at Various Exposure Ages	261
Figure 4.10b	Static Modulus of Elasticity of HCC in Water at Various Exposure Ages	262
Figure 4.10c	Static Modulus of Elasticity of HCC in Sea Water at Various Exposure Ages	262

Figure 4.11a	Correlation Between the Static and Dynamic Modulus of All Samples Exposed in Water at Age 365 Days	265
Figure 4.11b	Correlation Between the Static and Dynamic Modulus of All Samples Exposed in Sea Water at Age 365 Days	266
Figure 4.12a	Correlation Between the Static and Compressive Strength of All Samples Exposed in Water at Age 365 Days	267
Figure 4.12b	Correlation Between the Static and Compressive Strength of All Samples Exposed in Sea Water at Age 365 Days	268
Figure 4.13a	Correlation Between the Dynamic and Compressive Strength of All Samples Exposed in Water at Age 365 Days	269
Figure 4.13b	Correlation Between the Dynamic and Compressive Strength of All Samples Exposed in Sea Water at Age 365 Days	270
Figure 4.14a	Ultrasonic Pulse Velocity of HCC at Various Exposure Ages	271
Figure 4.14b	Ultrasonic Pulse Velocity of HCC Exposed in Water at Various Exposure Ages	272
Figure 4.14c	Ultrasonic Pulse Velocity of HCC Exposed in Sea Water at Various Exposure Ages	272
Figure 4.15a	Correlation Between the UPV and Compressive Strength of All Samples Exposed in Water at Age 365 Days	275
Figure 4.15b	Correlation Between the UPV and Compressive Strength of All Samples Exposed in Sea Water at Age 365 Days	275
Figure 4.16	Drying Shrinkage of All HCC at Different Age	277
Figure 4.17	Impact Load of All the HCC Specimens at 28 Days	280
Figure 5.1	Water Absorption of All HCC at Different Exposure Ages	286
Figure 5.2	Total Porosity of All HCC at Different Exposure Ages	289
Figure 5.3a	Correlation Between the Water Absorption and Porosity of All Samples Exposed in Water at Age 365 Days	292

Figure 5.3b	Correlation Between the Water Absorption and Porosity of All Samples Exposed in Sea Water at Age 365 Days	292
Figure 5.4a	Cumulative Weight Gain of HCC Specimens Exposed in Sea Water	294
Figure 5.4b	Cumulative Weight Gain of HCC Specimens Exposed in Sea Water	294
Figures 5.5	Intrinsic Air Permeability of All HCC at All Exposure Ages	297
Figure 5.6a	Correlation Between the Intrinsic Air Permeability and the Water Absorption of All Samples Exposed in Water at Age 365 Days	300
Figure 5.6b	Correlation Between the Intrinsic Air Permeability and the Water Absorption of All Samples Exposed in Sea Water at Age 365 Days	300
Figure 5.7a	Correlation Between the Intrinsic Air Permeability and the Compressive Strength of All Samples Exposed in Water at Age 365 Days	301
Figure 5.7b	Correlation Between the Intrinsic Air Permeability and the Compressive Strength of All Samples Exposed in Sea Water at Age 365 Days	301
Figure 5.8a	Correlation Between Total Porosity and Intrinsic Air Permeability of All Samples Exposed in Water for 365 Days	302
Figure 5.8b	Correlation Between Total Porosity and Intrinsic Air Permeability of All Samples Exposed in Sea Water for 365 Days	303
Figure 5.9a	Chloride Content of Control and BM Samples of HCC Exposed in Both Water and Sea Water for All Ages of Test	306
Figure 5.9b	Chloride Content of Control and CF Samples of HCC Exposed in Both Water and Sea Water for All Ages of Test	307
Figure 5.9c	Chloride Content of Control and OPFBF Samples of HCC	307

	Exposed in Both Water and Sea Water for All Ages of Test	
Figure 5.9d	Chloride Content of Control and BF Samples of HCC Exposed in Both Water and Sea Water for All Ages of Test	308
Figure 5.9e	Chloride Content of Control and CF+BF Samples of HCC Exposed in Both Water and Sea Water for All Ages of Test	308
Figure 5.9f	Chloride Content of Control and CF+BF Samples of HCC Exposed in Both Water and Sea Water for All Ages of Test	309
Figure 5.10a	Control Mix Exposed in Sea Water at the Age of 28 Days	313
Figure 5.10b	Control Mix Exposed in Water at the age of 28 Days	314
Figure 5.10c	BM Mix Exposed in Sea Water at the age of 28 Days	314
Figure 5.10d	BM Mix Exposed in Water at the age of 28 Days	315
Figure 5.10e	CF Mix Exposed in Sea Water at the age of 28 Days	315
Figure 5.10f	CF Mix Exposed in Water at the age of 28 Days	316
Figure 5.10g	OPFBF Mix Exposed in Sea Water at the age of 28 Days	316
Figure 5.10h	OPFBF Mix Exposed in Water at the age of 28 Days	317
Figure 5.10i	BF Mix Exposed in Sea Water at the age of 28 Days	317
Figure 5.10j	BF Mix Exposed in Water at the age of 28 Days	318
Figure 5.10k	CF+ BF Mix Exposed in Sea Water at the age of 28 Days	318
Figure 5.10l	CF+ BF Mix Exposed in Water at the age of 28 Days	319
Figure 5.10m	OPFBF+ BF Mix Exposed in Sea Water at the age of 28 Days	319
Figure 5.10n	OPFBF+ BF Mix Exposed in Water at the age of 28 Days	320
Figure 5.11a	Control Mix Exposed in Sea Water at the age of 365 Days	321
Figure 5.11b	Control Mix Exposed in Water at the age of 365 Days	322
Figure 5.11c	BM Mix Exposed in Sea Water at the age of 365 Days	322
Figure 5.11d	BM Mix Exposed in Water at the age of 365 Days	323
Figure 5.11e	CF Mix Exposed in Sea Water at the age of 365 Days	323
Figure 5.11f	CF Mix Exposed in Water at the age of 365 Days	324

Figure 5.11g	OPFBF Mix Exposed in Sea Water at the age of 365 Days	324
Figure 5.11h	OPFBF Mix Exposed in Water at the age of 365 Days	325
Figure 5.11i	BF Mix Exposed in Sea Water at the age of 365 Days	325
Figure 5.11j	BF Mix Exposed in Sea Water at the age of 365 Days	326
Figure 5.11k	CF+BF Mix Exposed in Sea Water at the age of 365 Days	326
Figure 5.11l	CF+BF Mix Exposed in Water at the age of 365 Days	327
Figure 5.11m	OPFBF+BF Mix Exposed in Sea Water at the age of 365 Days	327
Figure 5.11n	OPFBF+BF Mix Exposed in Water at the age of 365 Days	328
Figure 5.12a	Typical XRD Pattern of the Control Specimen Exposed in Sea Water After 28 Days	329
Figure 5.12b	Typical XRD Pattern of the BM Specimen Exposed in Sea Water After 28 Days	329
Figure 6.1	Bending Moment Test Set Up for HCC Panels	336
Figure 6.2	Flexural Strength Versus Mid Span Deflection of HCC Panels	338
Figure 6.3	Flexural Stress Versus HCC Panels Strain	340
Figure 6.4	Toughness Indices of The HCC Mixes	342
Figure 6.5	Design Beam Sketch	346
Figure 6.6	HCC Beam Bending Moment Test Setup	347
Figure 6.7	Flexural Stress Versus Mid Span Deflection of All HCC Beam Samples	349
Figure 6.8	Flexural Stress Versus Strain of The HCC Beams	352
Figure 6.9	Toughness Indices of HCC Beams	353
Figure 6.10a	Crack Pattern and Failure Mode of All the HCC Beams	357
Figure 6.10b	Crack Pattern and Failure Mode of All the HCC BF Beam	357

## LIST OF ABBREVIATIONS

ACI	America Concrete Institute.
ASTM	America Society Testing Methods.
BF	Barchip Fibre
BSI	British Standards Institution
CF	Coconut Fibre
CNS	Colloids Nanosilica
ECC	Engineered Cementitious Composites
EDX	Energy Dispersion X-Ray
FRC	Fibre Reinforced Concrete
ITZ	Interfacial Transition Zone
MK	Metakaolin
OPC	Ordinary Portland Cement
OPFBF	Oil Palm Fruit Bunch Fibre
HCC	Hybrid Cementitious Composites
SEM	Scanning Electron Microscopy
SP	Superplasticizer

**PEMBENTUKAN KOMPOSIT SIMEN HIBRID (HCC)  
UNTUK PEMBINAAN LESTARI DI PERSEKITARAN AIR LAUT**

**ABSTRAK**

Perbalahan utama dalam komuniti pembinaan ialah untuk menghasilkan konkrit bertetulang gentian (FRC) yang mempunyai ciri-ciri kejuruteraan yang baik serta keupayaan lenturan yang lebih tinggi. Metakaolin (MK) mempamerkan potensi yang sangat baik sebagai bahan bersimen tambahan (SCM) kerana tahap kereaktifan pozzolan yang tinggi serta pengurangan  $\text{Ca(OH)}_2$  seawal satu hari untuk menghasilkan kekuatan awal. Demikian juga, ia menguatkan adunan campuran simen untuk menjalani proses pepadatan yang telah ditetapkan. Proses penerokaan eksperimen ini melibatkan penghasilan MK oleh makmal yang berasal daripada kaolin mentah dan pencirian MK dalam empat campuran adunan simen yang terdiri daripada simen, Coloids Nanosilica (CNS) dan Epoxy Resin. Komposisi kimia dan sifat fizikal MK telah dinilai menggunakan penganalisis laser partikel zarah, X-ray Fluorescence (XRF) dan X-ray Diffraction (XRD). Kajian ini menggunakan kriteria reka bentuk terhadap campuran konkrit berkomposit simen standard ECC M45 (dengan sedikit pengubahsuaian). Satu komposit simen hibrid (HCC) telah dihasilkan, didedahkan dalam persekitaran yang agresif iaitu dalam air laut dan air biasa untuk peringkat umur sehingga 365 hari. Sebanyak tujuh campuran termasuk kawalan telah direkabentuk dengan menggabungkan 10% MK, 1% CNS, 1% Epoxy Resin mengikut kiraan berat simen. Gentian barchip, serat kelapa dan serat buah kelapa sawit telah digabungkan pada 2% setiap satu mengikut sukatan berat pengikat. Penghibridan barchip dan setiap gentian semula jadi juga telah

digabungkan. Hasil kajian menunjukkan bahawa MK yang dihasilkan mempunyai alumina dan silika oksida yang lebih tinggi sebagai tambahan kepada penggredan halus terhadap saiz zarah. Penggabungan MK menyebabkan peningkatan dalam permintaan air untuk adunan dan masa set bagi keempat-empat adunan simen. MK, CNS dan Epoxy Resin meningkatkan sifat-sifat mekanikal pada awal usia dan sifat-sifat ketahanan HCC dengan penggabungan gentian hibrid. Di antara semua gentian, gentian barchip menunjukkan keputusan yang sangat memberangsangkan, manakala bagi hibrid barchip dan gentian kelapa gentian juga menunjukkan prestasi yang lebih baik berbanding barchip dan buah kelapa sawit. Sampel yang diawet di dalam air laut menunjukkan prestasi dan korelasi yang lebih baik daripada sampel yang diawet di dalam air. Panel-panel HCC dan rasuk yang direkabentuk telah mempamerkan ciri-ciri retak pertama yang lebih baik dan kekuatan lenturan yang lebih tinggi berbanding dengan kawalan. Walau bagaimanapun, panel gentian barchip dan rasuk menunjukkan prestasi yang lebih baik daripada yang lain.

**DEVELOPMENT OF HYBRID CEMENTITIOUS COMPOSITE (HCC)  
FOR SUSTAINABLE CONSTRUCTION IN SEA WATER  
ENVIRONMENT**

**ABSTRACT**

The major challenge in the construction community is to advance a new type of fibre reinforced concrete (FRC) which possesses favourable engineering features that yield a high flexural ability. Metakaolin (MK) display great potentials as a supplementary cementitious material (SCM) because of its high pozzolanic reactivity as well as reduction of  $\text{Ca(OH)}_2$  as early as one day to produce early strength. Likewise, it intensifies the blended cement paste to undergo definite densification. The experimental exploration involves the laboratory production of MK from raw kaolin and characterization of MK quaternary blended cement mortar consists of cement, colloids nanosilica (CNS) and epoxy resin. The chemical compositions and physical properties of the MK were appraised using a laser particle size Analyzer, X-ray Fluorescence (XRF) and X-ray Diffraction (XRD). The study adopts the design criteria and mix proportion of engineered cementitious composites standard ECCM45 (with some modifications). A hybrid cementitious composite (HCC) was produced, exposed to both water and sea water for ages up to 365 days. A total of seven mixes including control were fabricated with the incorporation of 10% MK, 1% CNS, 1% of epoxy resin replacement of cement by weight. Barchip fibre, coconut and oil palm fruit bunch fibres were incorporated at 2% each by weight of binder. Hybridization of barchip and each of natural fibres were also incorporated. The results showed that the MK produced has higher alumina and silica oxides and

very fine particle size grading. The incorporation of MK causes an increase in water demand of the mortar and the setting time of the quaternary cement mortar. The MK, CNS and epoxy resin enhance the early age mechanical properties and durability properties of the HCC even with the incorporation of the fibres and their hybridization. Among all the fibres, the barchip fibre generated very encouraging results while the hybridized barchip and coconut fibre likewise showed better performance over the samples of barchip and oil palm fruit bunch. The samples exposed in sea water revealed better performance and correlations of results than the samples exposed in water. The HCC panels and beams fabricated exhibited better first crack and ultimate flexural strength, multiple micro cracks width and crack spacing than the control. However, the barchip fibre panels and beam performed better than others.

# **CHAPTER ONE**

## **INTRODUCTION**

### **1.1 Introduction**

This study focuses on the development of Metakaolin influence hybrid Cementitious Composite (HCC) made of natural materials. The main materials incorporated in the production of this natural HCC are Metakaolin, natural fibres, natural and localized fine sand, cement, nano silica and epoxy. This is done to take advantage of the abundance of natural materials to minimize cost, reduce energy expended into the production of cement and other byproduct and also minimize environmental degradation hence contribute to the level of sustainability in the civil and construction industry.

This chapter of the thesis discusses the research study background, statement of the problem, the aim and objectives of the study, the significance of the research, the scope of the study and finally the layout of the thesis.

### **1.2 Background of the Research Study**

The world is witnessing a high current of revolution in construction practices and materials production along with a new face of development. This is fuelled by rapid economic growth and a high rate of urbanization coupled with the issue of environmental management and sustainability (Suresh, 2004)..

In order to assist in the sustainable development challenges facing concrete industry, civil and construction industry, environmental friendly and sustainable concrete technology must be engaged including improved cement production process. This must also include the use of supplementary cementing materials, recycling concrete materials and other materials that can enhance the service life cycle of concrete structures. This will give credibility to the concrete and construction industry.

In tune with this realization and in accordance to the current technological advancements in the field of sustainable construction materials, various researches and studies have been carried out and still ongoing to meet up with the challenges. Lightweight concrete of various types was developed to control some of the shortcomings of traditional concrete, especially in the area of total mass and flexibilities, then the production of high performance and high strength concrete with the introduction of fibre and polymer materials in concrete (Nagaraj, et al., 1993, Naaman 2000, Kearsley and Wainwright 2002, Gesoğlu, et al., 2004, Jones and McCarthy 2006, Kurama, et al., 2009, Bedoya-Ruiz, et al., 2010, Cheah and Ramli, 2012). In most of these new developments, additives, cementitious and pozzolans were used and fibres, wire mesh were equally engaged as reinforcement in many of the newly innovated concrete.

These rapid developments of innovative reinforced concrete support the development of fibre reinforced concrete, Ferrocement mortar and concrete and newly adopted Engineered Cementitious Composites. Fibre reinforced concrete, FRC, is made primarily of hydraulic cements, aggregates, water and discrete

reinforcing fibres. It was developed with the view that the inclusion of fibres in concrete, mortar and cement paste can bring about improved engineering properties of the materials, such properties includes, flexural strength, fracture toughness, impact, thermal shock, resistance to fatigue and spalling, (Balaguru and Shah 1992, Nataraja, et al., 2005, Aruntaş, et al., 2008).

In the last decade, the technology of concrete has been experiencing fast development. Many endeavour to alter the unique, all known brittle performance of conventional plain concrete materials like cement paste or mortars and concrete has brought about a contemporary notion of high performance fibre reinforced cementitious composites (HPFRCCs) which showcase a special ductile behaviour. Hence, guarantee to be useful in various ranges of civil, building and infrastructure construction and applications as sum up by Concrete Institute in Japan (Naaman, 2003) and (Kunieda and Rokugo 2006). One out of many areas of practical application of this class of fibre reinforced cementitious composites material is the retrofitting, repairs and strengthening of concrete infrastructure and civil/ building structures.

Contemporary techniques of placing large amounts of fibres between 5-20% by volume into bulk structures such as columns, beams and connections have been successfully introduced. Some examples of this are SIFCON which has between 5-20% steel fibres and slurry infiltrated (Schneider 1992, Brandt 2008), SIMCON, of which 6% steel fibre mat was employed and slurry infiltrated (Li, et al., 2002, Habel, et al. 2006); slurry infiltrated steel wool and Compact reinforced concrete, CRC, matrix which has a volume contents of 5-10% fine steel fibres (Guerrini, 2000).

These materials have excellent mechanical properties coupled with strength properties improvement, fracture toughness and sometimes even appear to exhibit strain-hardening behaviour as in some thin-sheet FRCs. They also share primary importance with the main reinforcement in certain structural members as a result of their exhibited features. For instance, they have been considered for providing structural ductility in over-reinforced beams and likewise in brittle carbon FRP R/C structures (Naaman, 2003).

Furthermore, the quest for revolutionary building and civil engineering material that meets the standard structural strength and durability challenges without compromising sustainability features brought about the evolution of Engineered Cementitious Composite materials (ECC).

Engineered Cementitious Composites (ECC) is a type of high performance fibre-reinforced cementitious composite material that is characterized by a strain capacity of more than 3%, hence acts more like a ductile metal rather than like a brittle glass. It is a bendable concrete composed of all the ingredients of a traditional concrete with the exception of coarse aggregates or crushed stones and it is reinforced with micromechanically design polymer fibres. Micromechanically, in the sense that the mechanical interactions between ECC's fibre and matrix are described by a micromechanical model, which takes into account material properties and helps predict properties and guide ECC development. It has been optimized through the use of micromechanics in order to attain high ductility and tight micro-crack width even with moderate use of fibre contents, (Li, 2003, Wang, 2006). The volume

content of fibre is 2% of short discontinuous fibres differs from what was used in FRC.

ECC incorporates super fine (100 microns in diameter) silica sand and tiny Polyvinyl Alcohol-fibres cover with a very thin, slick coating. This slick coating of the surface allows the fibre to begin slipping when they are overloaded so they are not subjected to fracturing and prevent the fibre from rupturing which could lead to large cracking in the components. According to micromechanics theory, ECC is tailored by fibre geometry interface properties and matrix toughness (Abdeen and Hodhod, 2010).

The Engineered Cementitious composite has 500 times more resistant to cracking and 40% lighter in weight compared to normal concrete. It is generally designed for maximum flexibility. And comparison studies result made available by School of Natural Resources and Environment's Center for Sustainable Systems, in conjunction with the University of Michigan's research group, reveals that over 60 years of service on a bridge deck, the ECC is 37% less expensive, consumes 40% less energy, and produces 39% less carbon dioxide (a major cause of global warming) than regular concrete.

ECC is a crack self- healing material, hence the crack damage recovers any stiffness lost when the material is damaged. The average crack width in ECC concrete is below 60 micrometers and that was considered to be about half the width of a human hair. Extra dry cement in the concrete exposed on the crack surfaces can react with water and carbon dioxide in air to heal and form a thin white scar of

calcium carbonate (Li, 2003, Qian, et al., 2009, Kan and Shi, 2012). The application of this material is finding its way into precast plants, construction sites, and repair and retrofits jobs.

The most fundamental differences in the area of mechanical property between ECC and FRC is that while ECC is strain-harden, FRC is tension-softens after first cracking. In FRC, the first crack continues to open up as the fibres are ruptured or pull out and the stress-carrying capacity decreases. This post-peak tension-softening deformation is often represented by a softening stress-crack opening relationship. While, in ECC, a rising stress accompanies by increasing strain followed up the first crack. This strain-hardening response of ECC replaces the well known FRC tension-softening response only after several percent of straining has been attained, thus achieving a stress-strain curve with a shape similar to that of a ductile metal material. In addition to these, the material is considered to be extremely damaging tolerant and remains ductile even in severe shear loading conditions, (Lim and Li, 1997, Li, et al., 2002, Shang, 2006).

Fibres are made up of thread or filament formed from vegetable tissue, mineral substances or textile materials. Fibres can be employed in self compacting concrete, natural or artificial lightweight aggregate concrete and expanded polystyrene concrete (Corinaldesi and Moriconi, 2004, Düzgün, et al., 2005). The current technological development in term of various types of fibre has led to the creation of more new opportunities for the improvement of fibre reinforced cementitious composite materials. Most often the strategy employed in the materials design is targeted at composites design with improved tensile response. This is by

taking advantage of the effectiveness of combined contribution of various types of fibres to the comprehensive tensile response of the composites. The usage of fibres of different features and natures is combined with distinct features and geometrical and material properties in such a composite as hybrid fibre reinforced cementitious composites have been studied and reported in literatures to improve the material properties of many fibre reinforced cementitious composites (Lawler, et al., 2003, Bantia and Gupta, 2004, Ahmad, et al. 2007). Generally, studies shows that the most important benefit derived from the appropriation of hybrid fibre reinforcement techniques in the fibre reinforced cementitious composites is the potentials to constrain or confine cracking at different scales of the cracking process (Ahmed, et al., 2007). Likewise, it was confirmed that micro fibre improves the pull out the response of macro fibre as well, hence produce high strength composites (Ahmed and Maalej, 2009). This dictates the utilization of hybrid fibre in this study.

However, with the new innovated ECC, it is somehow revealed that composite material properties depend on three groups of constituent properties, namely; the fibre, matrix and the interface properties. Composite optimization requires that the combined influence of all relevant parameters on composite properties be known and this can lead to a good composite material with excellent performance and contain only a moderate fibre volume fraction. Hence, the desire to study a hybrid cementitious composite was produced based on ECC design and with natural features.

The advent of this composite material has led to many research studies with various focuses on the mechanical properties, durability, micromechanics properties

and many others. Most of these based their matrix design on mono-fibre and hybrid fibre. A handful research knowledge is known about the properties and durability of sustainable hybrid fibre reinforced ECC made of natural cementitious materials and fibres.

Supplementary cementitious materials (SCM) are considered to be finely ground solid materials that are engaged for cement replacement partially, in a concrete mixture. This class of materials reacts with hydrating cement chemically to produce a modified microstructure paste. SCM may either possess pozzolanic or latent hydraulic reactivity but in some instances it may possess both. Pozzolans are finely silicious material which can react chemically with cements' calcium hydroxide (CH), in the presence of water to produce a cementitious compound. The origin of pozzolans can either be natural or industrial. Volcanic ash, diatomaceous earth and kaolin are few examples of natural pozzolans while, fly ash, which is the most extensively used SCM, Silica fumes, granulated blast furnace slag are few examples of industrial waste pozzolans.

Metakaolin (MK) is a type of SCM that is unique in nature in the sense that it is not entirely natural and not a by-product of an industrial process, it is extracted from a naturally occurring mineral and it is manufactured explicitly for cementing application purposes. It is an SCM that conforms to ASTM C 618, class N pozzolan specification. MK is procured through the process of calcinations of kaolinitic clays over a certain period of time at a specific temperature range. It is a pozzolanic material which, when added to lime mortar mixes can result in improved mechanical properties.

In this modern age, MK, based on its high pozzolanic properties and its' high surface area, coupled with its amorphous structure has been used as an effective and highly active pozzolan for partial cement replacement in concrete and concrete mortar (Frias and Cabrera, 2000, Asbridge et al., 2002). Studies by various researchers has shown the capability of MK has been used as a cementitious material and additive to improve both the durabilities and mechanical properties of concrete and concrete mortar (Fraire-Luna, et al., 2006, Kim, et al., 2007, Janotka, et al., 2010). Likewise, in the production of high strength concrete Yu, et al., (2010) and high – ultra high performance concrete (Vejmelkova, et al., 2010). Despite the cost factor which is not favourable to the use of MK, there are potentials of the high utilization of the pozzolans due to the fact that there is a current shortage of mineral admixture such as high quality slag and silica fumes. Even fly ash, which is most generally used mineral admixtures will soon fade away with the invention of the biomass fuel production. Hence, the need for naturally available cementitious material.

Nanotechnology is currently considered as one of the twenty – first century's key technology Gammampila, et al., (2010), its economic importance is sharply on the rise. The meaning of Nanotechnology varies from one field to the other and also it varies based on country to country. Nanotechnology is commonly defined as the understanding, control, and restricting of matter in the order of nanometers (i.e., less than 100 nm) to create materials with fundamentally new properties and functions (Roco, 2007, Roco, 2011). Concrete, which is most pervasive material for construction in the world is a nanostructured material with multiple phase and composite that wears over a period of time, (Sanchez and Sobolev, 2010). It consists

of an amorphous phase, which are in nanometre to micrometer crystal size and bound with water. It has properties that exist in multiple length scales, i.e. from nano to micro and micro to macro. Hence, concrete nanoengineering can take place in one or more of the highlighted three phases such as solid phases, liquid phases and interfaces between liquid and solid or solid to solid (Garboczi, 2009).

Concrete material mechanical behaviour depends to some great extent on the structural elements and exceptional that are active on micro and nanoscale as the size of the calcium silicate hydrate (C-S-H) phase falls within few nanometers. This eventually has an indicative effect on the concrete performance as the structure is more sensitive to movement of moisture content hence shrinkage and cracking consequently when there are constraints in elements sizes (Jennings, et al., 2007). Therefore, nanoparticle, such as nanosilica (powdery and colloidal types), may have potential to manipulate concrete with superior properties by means of optimization of material behaviour and performance necessary for significant enhancement of concrete mechanical, durability and sustainability performance. This determines the use of nanosilica in this study to enhance the performance of HCC.

### **1.3 Statement of Problem**

In contemporary human dispensation, concrete is the most accepted widely used construction material with estimated annual consumption of approximately ten billion metric tonnes (Yaprak, et al., 2011). Ordinary Portland cement is the main components of concrete, that is, the major binder agent. But study shows that the production of cement accounted for 5% of the global anthropogenic carbon dioxide

emission. The main source of carbon dioxide emission is from the calcinations process of limestones and combustion of fuel in the kiln. Recently, the cement industry through the production of cement, is ranked third highest in world energy consumption, which contributes up to 19.7 % of the whole global industrial energy consumption as stipulated by (Kolip and Savas, 2010). Literature also confirmed that for every tonne of ordinary Portland cement produced, an approximate of 222 kg of carbon dioxide are emitted and discharged into the atmospheric air, this resulted into a serious environmental problem (Worrell, et al., 2001, Boden, et al., 2009).

The contemporary normal concrete is considered to be very sensitive to crack formation and as the cracks grow wide, the more the endanger of the durability of such concrete hence the need for repair. But this repair works always raises the life-cycle cost of the concrete as it involves intense labour works and as the structure become redundant during the period of damages and in the course of repairs (Van and De Belie, 2013).

Plain concrete consists of a very low tensile strength, very low ductility and little measures of crack resistance. It contains inherent internal micro-cracks which are due to drying shrinkage and the propagation of these cracks occurs because of its poor tensile strength, all these combine, eventually leads to brittle failure of the concrete. In the same vein, infrastructures can as well experience a wide range of dynamic loads, severe structural failure and eventual damage even catastrophic failures have occurred in some extreme cases, hence Yang and Li, (2012) suggested that there is a need to design civil infrastructure that are resilient to seismic, impact, and dynamic loading to enhance public safety.

A remarkable advanced development of high performance cementitious materials (HPC) has taken place in the past years. This includes high strength concretes with low water to binder ratio, high performance fibre reinforced cementitious composites (HPFRC) which exhibit improved strength and ductility, green concrete, which are more environmental friendly and contain increase contents of by-products and mineral admixtures. It makes use of different mineral admixtures to partially replace cement (Zhongwei, 1998, Chen and Liu, 2008). The most widely available and mostly used admixtures are silica fume (SF), fly ash (FA) and ground granulated blast furnace slag (GGBS). But despite all the favourable properties and high performance attributes to these composites, their wider applications are highly hindered by their special processing requirement due to high fibre volume fractions and they are often restricted to precast members, hence costly. In furtherance of this, a major challenge to the research community is to develop a unique new class of FRC that possesses some outstanding features of all various classes of FRC's that are in use today. The features should include, among others, flexible processing, and short fibres of moderate volume fractions, isotropic properties and high performances as a structural member. This led to the study of the flexural property of HCC.

Nonetheless, in order to achieve better strain capacity and multiple cracking, restriction is made for the use of only fine sand in ECC (Zhang and Leng, 2008), this however, resulted to the elimination of coarse aggregates hence the higher cement content compared to conventional structural concrete. A typical ECC cement content can be as high as  $1000 \text{ kg/m}^3$ . Each tonne of cement produced emits an equal tonne of carbon dioxide, which is responsible for five percent (5%) global green house gas emission (Van Oss and Padovani, 2002). Consequently, reasoning from global

sustainable development, it is crucial to advance a sustainable, natural material contained in ECC by incorporating naturally derived mineral admixture to partially replace cement in concrete materials.

In line with this is the use of fly ash in the ECC. Recent studies revealed that fly ash has been an essential content of ECC, to improve the engineering properties most especially, the mechanical properties and as well reduce drying shrinkage of ECC (Yang, et al., 2007, Zhu, et al., 2009, Zhu, et al., 2010) an alternative, sustainable material must be sought. Be that as it may, the lower strength in the early age hinders the application of ECC material in some application whereby early strength is the main focus.

The commonly used fibre in ECCs is Polyvinyl alcohol fibre (PVA), it is considered the most suitable polymeric fibres to be used as reinforcement. This is despite its deficiencies which has to do with its' microstructure characteristics and hydrophilic nature. This makes it to have a tendency to rupture instead of being pulled out, hence, poses challenges to material design, (Wang and Li, 2005). Also, the interfacial bond strength of PVA fibre in ECC was said to be excessive because of its' hydrophilic nature and this was suggested to be artificially lowered by the application of surface coating agents (Victor, 2002). This is apart from the demerits such as high cost, quality balance to the highly cost sensitive construction sector and the scarcity of the fibre in some developing countries. Also, the current version of ECC clearly outperforms concrete in terms of mechanical properties yet its production has greater environmental burdens than concrete due to the high cement content and the inclusion of polymeric fibres, (Li, et al., 2004) Moreso, the bond

properties of PVA fibre without any treatment are far above the optimal values which is currently established to be between the ranges of 1.5 – 2.5 N/mm<sup>2</sup>, Wang and Li, 2005).

Above all, the design of ECC M45 which form the basis of ECC design, has been performed based on the micro-mechanical design theory constraining the alteration of ingredients' type and amount. Water-binder ratio, fibre and sand-binder ratio can be considered as mixture constraints of ECC design, (Şahmaran, et al., 2012).

All these stipulated points mentioned above brings about the agitation for the development of HCC for sustainable construction.

#### **1.4 Aim and Objectives**

This research is aimed towards the investigation of flexural resistance of hybrid cementitious composites (HCC) developed for sustainable construction most importantly in a marine or aggressive environment. This will embrace among others the production of MK in the laboratory and the optimization of composite materials including natural and synthetic fibre, analysing the features and structures, including mechanical, engineering and durability properties of the develop sandwich composite materials.

To achieve this aim, the following objectives are set;

1. To produce MK and study the particle morphology, chemical compositions, mineralogy, particle size distribution, specific gravity, rheology and engineering properties of the HCC.

2. To investigate the influence of the incorporation of MK as partial cement replacement on the HCC's durability properties.
3. To study the effect of both sea water and water environment on the engineering properties and performance of HCC.
4. To investigate the flexural property of the produced HCC structural panels and beam.

### **1.5 Research significance**

Considering the numerous kaolin mines in local areas around the world, this research study is executed to gather experimental information on the physical and chemical properties of MK produced from natural kaolin clay in the laboratory. It also touches on the investigation of the flexural performance of HCC mixtures that contain laboratory produced MK. The rheological, mechanical, durability properties and characteristics of the HCC were also studied. This is to justify the use of MK as a supplementary binder material in the HCC.

Focusing on mechanical properties, the concepts of introducing discontinuous hybrid fibres which include local natural fibres and synthetic fibres in HCC to provide the needed pseudo strained flexural strain is scarce hence the bridging of the knowledge gap through this study.

In addition, contemporary construction practices in relation to reinforced concrete or concrete materials such as HCC have been in need of high performance, low cost and durable type of materials. The two main criteria of high performance

concrete always sought to include high strength and an improved durability. Since shrinkage and permeability are directly related to the durability of the concrete, the improvement, realization and rehabilitation of these features through the use of some high reactivity mineral admixture such as MK comes into preeminent.

Hence, the research study is designed with the main focus of bridging these knowledge gaps and supply specific conclusive results. An effort was made to improve the ductility performance and deflection capacity of a structural beam by the incorporation of steel reinforcement with hybrid natural and synthetic fibres.

Experimental data on flexural response, crack patterns, ductility and mechanical behaviour collected from the testing of the structural panels and beams made of sustainable HCC will definitely contribute towards a better understanding of the responses to structural load, ductility capacity, load compressive strain behaviour, service load capacity, cracking behaviour, failure mode and serviceability property upon being subjected to various degrees of load capacity. This in turn can be used for the prediction of both mechanical and engineering behaviour of a structural beam in infrastructure, civil and building engineering industry.

## **1.6 Scope of work**

The centre focus of this research includes the following;

1. The production of MK from refined kaolin clay and the characterization of the binder materials.

2. The study of the rheological, engineering properties of HCC with the incorporation of MK.
3. Investigating the influence of MK incorporation into HCC, as a partial cement replacement, on durability properties.
4. Study the effect of sea water and ordinary water environment on the engineering properties and the performance capacity of the HCC.
5. Lastly, an assessment of the structural and flexural responses of structural beam panels in relation to load response, load compressive strain, ultimate load capacity, cracks development characteristics and failure modes.

The production of MK includes the process of calcination of kaolin clay using the small laboratory oven, then the chemical property assessment which includes evaluation of chemical composition, the mineral phases and loss on ignition of MK. The physical property assessment includes particle size grading determination, determination of specific gravity of MK and OPC.

The evaluation of the properties of MK blended cement, as well as MK- CNS and epoxy blended cement containing 10% of MK, 1% of CNS and 1% of epoxy with the remain percentage of binder content as cement.

Rheological study of the HCC includes a slump test and the flow value of the mixes in the fresh state. Meanwhile, the mechanical properties include, among others, the determination of characteristics compressive strength and flexural strength at various ages of samples. Velocity of pulse propagation through the hardened HCC mix is also investigated to study the quality of hardened HCC. The

dynamic and static modulus of elasticity of the hardened HCC was investigated for the assessment of stiffness features.

The durability properties study includes water absorption determination, air permeability properties of the hardened HCC, rates of carbonation and chloride diffusion. All these are determined to investigate the resistance to environmental aggressive agents. Since, it is a general assumption that durability are closely related to porosity and micro pore structure, the total porosity test is conducted on the hardened HCC with the inclusion of Scanning Electron Microscopy investigation to picture the micro-pore structure of the HCC.

The dimensional durability of high strength HCC includes the measurement of the changes in length via drying shrinkage. This is measured up till 365 days from the day of casting and drying exposure.

The assessment of structural behaviour is carried out on reinforced HCC beams with dimensions 1300 x 300 x 225 mm. The assessment parameter includes flexural and load-deflection response, bending load, service load capacity, the ultimate load capacity, and failure mode and crack development behaviour.

Hence, the limitation of this research study is as stated hereafter;

1. The maximum content of MK used in this experiment mixes is 10%, while, CNS and epoxy content is 1% each of the total binder.
2. This study does not consider the air exposure system as only sea water and portable water are considered.

3. The exposure period in the study is limited to 365 days and other days after this was not considered.

## **1.7 The thesis Layout**

This thesis consists of seven chapters that covers the introduction and the investigations on the engineering and durability properties of HCC.

The chapter One includes the background of the study where the details of the research were summarized laying emphasis on the developmental stages of sustainable fibre reinforced concrete and HPFRCC composites reinforced with discontinuous or discrete fibres which include the development of ECC. It also includes the scope of the study, major aim and objectives, the benefit of the research and concluded with the scope and limitation of the study.

In Chapter Two, detailed critical review of related literatures on ECC and MK and colloidal nanosilica (CNS) as a supplementary binder in concrete composites is presented. The physical and chemical properties of MK as natural additives and substitute of binding material are highlighted. The design criteria, mix proportion and the properties of ECC M45 are presented likewise. The influence of MK inclusion on the eventual mechanical strength of concrete and concrete materials as well as on both fibre and hybrid ECC, concrete and mortar, most importantly the compressive and flexural strength properties at early ages and prolonged ages of exposure under different exposure condition is discussed and reviewed.

The centre focus of chapter Three is the detailed report of the experimental programme and the appropriate test methodology. Apart from this, the substantial criterion of examination or exploration programme are explained.

Chapter Four detailed the rheological properties of MK blended cement paste namely standard consistency, initial and final setting time of paste, flow and slump test of fresh composite paste. Detailed explanation of the non-destructive and destructive examination, which involve ultrasonic pulse velocity using hardened sample, static and dynamic modulus of elasticity, compressive strength and flexural strength of the hardened HCC samples. Aside this, an all inclusive discourse on the drying shrinkage property of the HCC sample is analysed in this chapter.

A detailed assessment on water absorption, rate of carbonation, intrinsic air permeability and chloride permeability are presented in Chapter Five and all these are in the examination of the durability property of the HCC. In this chapter, total porosity and Scanning Electron Micrographs are presented for additional evidences to justify the durability properties of the study samples.

The Chapter six of the thesis emphasis on the structural behaviour of HCC beam subjected to a varying flexural load degree to the very ultimate failure of the sandwich composites. Details are also given on analytical method of approach for the prediction of serviceability moment capacity, the ultimate load capacity, crack width and crack spacings.

The last chapter, which is the Seventh chapter gives the comprehensive conclusion reports from the experimental works in summary. It also includes the recommendations for implementation and future research opportunities.

## **CHAPTER TWO**

### **LITERATURE REVIEW**

#### **2.1 General Appraisal**

This chapter contains a critical look at the past literatures on the integral elements of this research study. For a research study to be worthy, a constructive critical review of past research works of the notable professionals and researchers needs to be evaluated and reviewed. This chapter shall highlight the new technological inventions in relation to engineered cementitious composite, natural additives, kaolin and metakaolin. Likewise, it gives details of nanotechnology and their applications in concrete, natural and artificial fibres. The review shall also touch on their historical background and changes in the use of these materials over time.

A general overview of sea water and portable water exposure was done. The penetration effect and consequences of both sea water and portable water was reviewed, such effects as chloride ions, sulphate and salt crystallization. The later part of this chapter shall be the summary of the literature review.

#### **2.2 Historic issues about Kaolin**

Kaolin is one of the most abundant natural minerals in the world. It is a fine, white clay that has been used in the manufacture of porcelain and paper coating traditionally. Fundamentally, the term kaolin is derived from the name of the Chinese

town known as Kao-ling, which is translated loosely as ‘High ridge’. This town is home to the mountain that yielded the first kaolin that was sent to Europe. It is from this that MK is obtained.

The first ever use of MK as contain in record was in 1962, when it was incorporated in concrete mix in Jupia Dam located in Brazil. Kaolin has been available in commercial quantity in most countries of the world since mid-1990s. It is usually white or nearly white in colour and not lined and consists of the mineral kaolinite with slight content of quartz, mica and feldspar derived majorly through the weathering process. There are different grades of kaolin, it includes premium grade which is used majorly as coating agent and ceramic manufacturing like high quality dishes, porcelain and some electrical insulation. The regular grade of kaolin is suitable for use in fillers and paper, paints etc.

Kaolin physical and chemical characteristics regulate its eventual application. Although it is concluded through studies that some of these physical and chemical features are usually hinged on the immediate environment of deposition, geological origin, method of processing, and geographic source (Murray and Kogel 2005). In some instances, the presence of impurities, mainly iron oxide and hydroxide and titanium- bearing materials diminish the kaolin quality and affects its usefulness for different type of application, industrial or commercial purposes. Few of the properties of kaolin are highlighted in Table 2.1.

Table 2.1 Properties of kaolin (Prasad, et al.,1991)

<b>Properties</b>	<b>Description</b>
Color	Usually white, colourless, greenish or yellow
Luster	Earthy
Transparency	Crystals are translucent
Cleavage	Perfect in one direction,basal
Fracture	Earthy
Hardness	1.5-2 (can leave marks on paper)
Specific gravity	2.6 (average)

Kaolin formation has a significant effect on its industrial applications. For instance, sedimentary kaolin has a higher economic value compared to primary kaolin (Hadi, 2008).

The major constituent of kaolinite are a hydrous aluminium silicate with an approximate compound composed of  $2\text{H}_2\text{O} \cdot \text{Al}_2\text{O}_3 \cdot 2\text{SiO}_2$ . Kaolinite is regarded as the clay minerals, which produce the plasticity features of the raw material and at the same time change properties during the heating process to produce another more beneficial material. In structural view, the kaolinite consists of alumina octahedral sheets and also silica tetrahedral sheets, well starched interspersely with the theoretical composition of  $\text{SiO}_2$  which is 46%,  $\text{Al}_2\text{O}_3$  is 39.5%, and  $\text{H}_2\text{O}$  is 13.96%. The crystal of kaolinite is pseudo-hexagonal along with plates, few larger books and stacks of vermicular (Murray, 2000). Kaolin has particle sizes which range from 0.2 to 15  $\mu\text{m}$  with 10,000-29,000  $\text{m}^2/\text{kg}$  specific area.

According to studies, Kaolin is considered as one of the most widely used industrial minerals, its' total output in the world is estimated to be 25 million tonnes and above (Nkoumbou, et al., 2009). Its deposit is found in many parts of the world with United State of America and Uzbekistan having the largest formation of kaolin. Figure 2.1 shows the colour of kaolin. It is largely used in different industrial