

**THE CURING CHARACTERISTICS AND MECHANICAL PROPERTIES
OF WASTE TYRE DUST AND WASTE TYRE DUST HYBRID FILLED
NATURAL RUBBER COMPOUNDS**

By

NURUL FARHANA BINTI OMAR

**Thesis submitted in fulfilment of the requirements
for the degree of
Master of Science**

June 2012

ACKNOWLEDGEMENTS

I am grateful to Allah SWT with the permission and the gift; I was able to complete this thesis for the requirements of degree of Master of Science. I would like to extend my warmest appreciation to my advisor and co-advisor Prof Hanafi Ismail and Dr Nadras Othman for their encouragement, guidance, support, patience and understanding during the research and writing of this dissertation. Not the least are the dean Prof Dr Ahmad Fauzi Mohd Noor, lecturers who are involved directly or indirectly to advice, discuss ideas, and provide encouragement. May Allah SWT bless for all. A warm appreciation to my research group and for those took a part in many helpful technical, experimental and discussions especially regarding the entitled research. I wish all of them success in their careers. I would like to thank the excellent technicians as well as School of Materials and Mineral Resources Engineering who have assisted me in the characterization of many samples. I would like to thank them for their contributions and times.

Finally, specials thank to my father and mother, Omar Md Yusuf and Sariah Abd Karib, and my siblings for their love and inspiration. Thanks for believing in me when I did not believe in myself. This would not have been possible if it were not for the love of my savior ALLAH SWT and His messenger Muhammad SAW. *“Who is trying to, he will succeed”*

TABLE OF CONTENTS

ACKNOWLEDGEMENT	ii
TABLE OF CONTENTS	iii
LIST OF TABLES	vii
LIST OF FIGURES	vii
LIST OF ABBREVIATIONS	xiii
LIST OF SYMBOLS	xvi
ABSTRAK	xvii
ABSTRACT	xviii
CHAPTER 1- INTRODUCTION	
1.1 Overview	1
1.2 Problem statement	4
1.3 Research objectives	5
CHAPTER 2- LITERATURE REVIEW	
2.1 Tyre	6
2.1.1 Tyre recycling	6
2.1.2 Consumption of recycled tyre	10
2.1.3 Waste tyre dust (WTD)	12
2.2 Natural Rubber (NR)	15
2.2.1 Origin of natural rubber	15

2.2.2	Standard Malaysian Rubber (SMR)	16
2.3	Hybrid fillers	19
2.4	Carbon black	24
2.4.1	Classification of carbon black	24
2.4.2	Carbon black as reinforcing filler for elastomer	25
2.5	Calcium carbonate	30
2.5.1	Calcium carbonate as filler	32
2.6	Kenaf fibre	32
2.6.1	Kenaf tree	33
2.6.2	Application of kenaf	34
2.7	Factors affecting the properties of natural rubber compound	36
2.7.1	Curing of rubber	36

CHAPTER 3- MATERIALS AND METHODOLOGY

3.1	Materials	40
3.2	Preparation of rubber compound	42
3.3	Determination of tensile properties	42
3.4	Determination of fatigue life	43
3.5	Measurement of rubber-filler interaction	43
3.6	Morphological study	44
3.7	Fourier Transform Infra Red (FTIR) analysis	44
3.8	Particle Size analysis	45

CHAPTER 4- RESULTS AND DISCUSSION

4.1	Performance of waste tyre dust as filler in natural rubber compound	46
4.1.1	Curing characteristics	46
4.1.2	Tensile properties	49
4.1.3	Fatigue life	52
4.1.4	Rubber-filler interaction	53
4.1.5	Morphological study	54
4.2	The effect of waste tyre dust/ carbon black hybrid as filler in NR compound	58
4.2.1	Curing characteristics	58
4.2.2	Tensile properties	61
4.2.3	Fatigue life	65
4.2.4	Rubber-filler interaction	66
4.2.5	Morphological study	67
4.3	The effect of waste tyre dust/ calcium carbonate hybrid as filler in NR compound	70
4.3.1	Curing characteristics	70
4.3.2	Tensile properties	74
4.3.3	Fatigue life	78
4.3.4	Rubber-filler interaction	79
4.3.5	Morphological study	80
4.4	The effect of waste tyre dust/ kenaf fibre hybrid as filler in NR compound	83
4.4.1	Curing characteristics	83
4.4.2	Tensile properties	86

4.4.3	Fatigue life	90
4.4.4	Rubber-filler interaction	90
4.4.5	Morphological study	91
4.5	Comparison on effects of hybrid between waste tyre dust and three different filler (carbon black, calcium carbonate and kenaf fibre)	95
4.5.1	Curing characteristics	95
4.5.2	Tensile properties	99
4.5.3	Fatigue life	104
4.5.4	Rubber-filler interaction	105
4.5.5	Morphological study	106
CHAPTER 5- CONCLUSIONS AND SUGGESTION FOR FUTURE WORKS		
5.1	Conclusions	115
5.2	Suggestions for future works	118
REFERENCES		119

LIST OF TABLES

Table 2.1	Criteria used for grading the properties of rubber	17
Table 2.2	Standard Malaysian rubber specifications (from 1979)	18
Table 2.3	Effects of surface area and particle size of 50 bsg of carbon black on physical properties of SBR	27
Table 2.4	Minerals and rocks associated with calcium carbonate	31
Table 2.5	The comparison of aspect ratio short and bast kenaf fibre	34
Table 2.6	Influence of di- and polysulphide crosslinks on properties	39
Table 3.1	Formulation of WTD loading on SMR L compounds	41
Table 3.2	Formulation of waste tyre dust/hybrid filler-filled natural rubber compounds	41

LIST OF FIGURES

Figure 2.1	Carbon black structure	30
Figure 2.2	Kenaf fibre: bast fibre on left and core fibre on right	33
Figure 2.3	The internal structure of vegetable or plant fibre	35
Figure 2.4	Cross-section (left) and longitudinal section (right) of kenaf fibre	36
Figure 2.5	A diagrammatic presentation of the network structure of sulphur vulcaniate (x, y, a and b = 1-9)	37
Figure 2.6	Dependence of network structure on vulcanizing system. A, High accelerator: sulphur ratio (sulphur donor/accelerator system) and high soluble zinc concentration; B, low accelerator: sulphur ratio or low soluble zinc concentration	38
Figure 4.1	The effect of WTD loading on the cure time (t_{90}) of NR compounds	47
Figure 4.2	The effect of WTD loading on the scorch time (t_2) of NR compounds	47
Figure 4.3	The effect of WTD loading on the maximum torque (M_{HR}) of NR compounds	48
Figure 4.4	The effect of WTD loading on the tensile strength of NR compounds	49
Figure 4.5	The effect of WTD loading on elongation at break of NR compounds	50
Figure 4.6	The effect of WTD loading on stress at 100% elongation (M_{100}) of NR compounds	51
Figure 4.7	The effect of WTD loading on stress at 300% elongation (M_{300}) of NR compounds	52
Figure 4.8	The effect of WTD loading on fatigue life of NR compounds	53
Figure 4.9	The effect of WTD loading on the rubber–filler interaction of NR compounds	54
Figure 4.10	SEM micrograph of tensile fractured surface of NR compounds: (a) NR/WTD (0 phr), (b) NR/WTD (5 phr), (c) NR/WTD (30 phr) (Magnification 100x)	55

Figure 4.11	SEM micrograph of fatigue fractured surface of NR compounds: (a) NR/WTD (0 phr), (b) NR/WTD (10 phr), (c) NR/WTD (30 phr) (Magnification 100x)	57
Figure 4.12	The effect of WTD/CB hybrid filler loading on the cure time (t_{90}) of NR compounds	58
Figure 4.13	IR spectrum of a sample of WTD	59
Figure 4.14	The effect of WTD/CB hybrid filler loading on the scorch time (t_2) of NR Compounds	60
Figure 4.15	The effect of WTD/CB hybrid filler loading on maximum torque (M_{HR}) of NR compounds	61
Figure 4.16	The effect of WTD/CB hybrid filler loading on tensile strength of NR compounds	62
Figure 4.17	The effect of WTD/CB hybrid filler loading on elongation at break of NR compounds	63
Figure 4.18	The effect of WTD/CB hybrid filler loading on stress at 100% elongation (M_{100}) of NR compounds	64
Figure 4.19	the effect of WTD/CB hybrid filler loading on stress at 300% elongation (M_{300}) of NR compounds	64
Figure 4.20	The effect of WTD/CB hybrid filler loading on fatigue life of NR compounds	65
Figure 4.21	The effect of WTB/CB hybrid filler loading on the rubber–filler interaction of NR compounds	66
Figure 4.22	SEM micrograph of tensile fractured surface of WTD/CB hybrid filler filled NR compounds: (a) 30WTD/0CB, (b) 20WTD/10CB, (c) 0WTD/30CB (Magnification 100x)	68
Figure 4.23	SEM micrograph of fatigue fractured surface of WTD/CB hybrid filler filled NR compounds: (a) 30WTD/0CB, (b) 20WTD/10CB, (c) 0WTD/30CB (Magnification 100x)	69
Figure 4.24	The effect of WTD/ CaCO_3 hybrid filler loading on the cure time (t_{90}) of NR compounds	71
Figure 4.25	The effect of WTD/ CaCO_3 hybrid filler loading on the scorch time (t_2) of NR compounds	72
Figure 4.26	IR spectrum of a sample of CaCO_3	73

Figure 4.27	The effect of WTD/CaCO ₃ hybrid filler loading on maximum torque (M_{HR}) of NR compounds	74
Figure 4.28	The effect of WTD/CaCO ₃ hybrid filler loading on tensile strength of NR Compounds	75
Figure 4.29	The effect of WTD/CaCO ₃ hybrid filler loading on elongation at break of NR compounds	76
Figure 4.30	The effect of WTD/CaCO ₃ hybrid filler loading on stress at 100% elongation (M_{100}) of NR compounds	77
Figure 4.31	the effect of WTD/CaCO ₃ hybrid filler loading on stress at 300% elongation (M_{300}) of NR compounds	77
Figure 4.32	The effect of WTD/CaCO ₃ hybrid filler loading on fatigue life of NR compounds	78
Figure 4.33	The effect of WTB/CaCO ₃ hybrid filler loading on the rubber–filler interaction of NR compounds	79
Figure 4.34	SEM micrograph of tensile fractured surface of WTD/CaCO ₃ hybrid filler filled NR compounds: (a) 30WTD/0CaCO ₃ , (b) 20WTD/10CaCO ₃ , (c) 0WTD/30CaCO ₃ (Magnification 100x)	80
Figure 4.35	SEM micrograph of fatigue fractured surface of WTD/CaCO ₃ hybrid filler filled NR compounds: (a) 30WTD/0CaCO ₃ , (b) 20WTD/10CaCO ₃ , (c) 0WTD/30CaCO ₃ (Magnification 100x)	82
Figure 4.36	The effect of WTD/kenaf fibre hybrid filler loading on the cure time (t_{90}) of NR compounds	83
Figure 4.37	The effect of WTD/kenaf fibre hybrid filler loading on the scorch time (t_2) of NR compounds	84
Figure 4.38	IR spectrum of kenaf fibre	85
Figure 4.39	The effect of WTD/kenaf fibre hybrid filler loading on maximum torque (M_{HR}) of NR compounds	86
Figure 4.40	The effect of WTD/kenaf fibre hybrid filler loading on tensile strength of NR compounds	87
Figure 4.41	The effect of WTD/kenaf fibre hybrid filler loading on elongation at break of NR compounds	88
Figure 4.42	The effect of WTD/kenaf fibre hybrid filler loading on stress at 100% elongation (M_{100}) of NR compounds	89

Figure 4.43	the effect of WTD/kenaf fibre hybrid filler loading on stress at 300% elongation (M300) of NR compounds	89
Figure 4.44	The effect of WTD/kenaf fibre hybrid filler loading on fatigue life of NR compounds	90
Figure 4.45	The effect of WTD/kenaf fibre hybrid filler loading on the rubber–filler interaction of NR compounds	91
Figure 4.46	SEM micrograph of tensile fractured surface of WTD/kenaf fibre hybrid filler filled NR compounds: (a) 30WTD/0Ke, (b) 20WTD/10Ke, (c) 0WTD/30Ke (Magnification 100x)	92
Figure 4.47	SEM micrograph of fatigue fractured surface of WTD/Ke hybrid filler filled NR compounds: (a) 30WTD/0Ke, (b) 20WTD/10Ke, (c) 0WTD/30Ke (Magnification 100x)	94
Figure 4.48	The effect of filler type and WTD/hybrid-filler loading on cure time, t_{90} of WTD/hybrid-filler filled NR compound	95
Figure 4.49	The effect of filler type and WTD/hybrid-filler loading on scorch time, t_2 of WTD/hybrid-filler filled NR compound	97
Figure 4.50	The effect of filler type and WTD/hybrid-filler loading on maximum torque (M_{HR}) of WTD/ WTD/hybrid-filler filled NR compound	98
Figure 4.51	The effect of filler type and WTD/hybrid-filler loading on tensile strength of WTD/ WTD/hybrid-filler filled NR compound	99
Figure 4.52	The effect of filler type and WTD/hybrid-filler loading on elongation at break of WTD/hybrid-filler filled NR compound	100
Figure 4.53	The effect of filler type and WTD/hybrid-filler loading on stress at 100% elongation (M100) of WTD/hybrid-filler filled NR compound	102
Figure 4.54	The effect of filler type and WTD/hybrid-filler loading on stress at 300% elongation (M300) of WTD/hybrid-filler filled NR compound	102
Figure 4.55	The effect of filler type and WTD/hybrid-filler loading on fatigue life of WTD/hybrid-filler filled NR compound	104
Figure 4.56	The effect of filler type and WTD/hybrid-filler loading on rubber-filler interaction of WTD/hybrid-filler filled NR compound	106

Figure 4.57	SEM micrograph of tensile fractured surface of 30 phr WTD filled NR compound (Magnification 100x)	106
Figure 4.58	SEM micrograph of tensile fractured surface of WTD20/hybrid-filler 10 filled NR compounds: (a) WTD/CB, (b) WTD/ CaCO ₃ , (c) WTD/kenaf (Magnification 100x)	108
Figure 4.59	SEM micrograph of tensile fractured surface of WTD20/hybrid-filler30 filled NR compounds: (a) WTD/CB, (b) WTD/CaCO ₃ , (c) WTD/kenaf (Magnification 100x)	110
Figure 4.60	SEM micrograph of fatigue fractured surface of 30 phr WTD filled NR compound (Magnification 100x)	111
Figure 4.61	SEM micrograph of fatigue fractured surface of WTD20/hybrid-filler10 filled NR compounds: (a) WTD/CB, (b) WTD/ CaCO ₃ , (c) WTD/kenaf (Magnification 100x)	112
Figure 4.62	SEM micrograph of fatigue fractured surface of WTD20/hybrid-filler30 filled NR compounds: (a) WTD/CB, (b) WTD/CaCO ₃ , (c) WTD/kenaf (Magnification 100x)	114

LIST OF ABBREVIATIONS

ASTM	American Standard Test Method
BKF	2, 2'-Methylene-bis (4-methyl-6-tert-butylphenol)
BS	British standard
CB	Carbon black
CBS	N-cyclohexyl-2-benzothiazole sulfonamide
CH ₂	Methylene
CMF	Cellulose micro fibrils
CO ₃ ²⁻	Carbonate
CV	Conventional Vulcanization
DOE	Design of experiments
EFC	Elementary fibrous cells
EV	Efficient Vulcanization
FBR	Fraction of bounded rubber
FEF	Fast extrusion furnace
FF	Fine furnace
FRIM	Forest Research Institute of Malaysia
FT	Fine thermal
FTFT	Fatigue-to-Failure Tester
FTIR	Fourier Transform Infra Red
FTIR-ATR	Fourier Transform Infra Red in attenuated total reflection mode
GPF	General purpose furnace
H	Hydrogen

HMF	High modulus furnace
IR	Infrared
ISAF	Intermediate super abrasion furnace
JIS	Japanese Industrial Standard
KBr	Potassium bromide
MDR	Moving die rheometer
MT	Medium thermal
MT-NS	Medium thermal non-staining
N	Nitrogen
N100-N990	Normal cured carbon black
NBR	Acrylonitrile-butadiene rubber
NR	Natural rubber
O	Oxygen
RMA	Rubber modified asphalt
RRIM	Rubber Research Institute Malaysia
S	Sulphur
s.d.	standard deviation
SAF	Super abrasion furnace
SEBS-g-MA	Maleic anhydride-grafted styrene-ethylene-butylene-styrene
SEM	Scanning electron microscopy
SMR	Standard Malaysian Rubber
SMR-CV	Constant-viscosity Standard Malaysian Rubber
SMR-L	Light coloured Standard Malaysian Rubber
SMR LV	Lower-viscosity Standard Malaysian Rubber

SMR GP	General purpose Standard Malaysian Rubber
SMR WF	Darker coloured Standard Malaysian Rubber
SRF	Semi-reinforcing furnace
TC	Technical Classification
TMTD	Tetra methyl thiuram disulfide
TOR	<i>Trans</i> -polyoctylene rubber
WTD	Waste tyre dust
XCF	Conductive furnace
ZnO	Zinc Oxide

LIST OF SYMBOLS

$^{\circ}\text{C}$	Degree celcius
d_{50}	Mean particle size
D_{agg}	Aggregate diameter
D_{pp}	Particle diameter
Eb	Elongation at break
kgcm^{-2}	kilograms force per square centimeter
L/D	Length over diameter
lbf/in^2	Pound-force per square inch
m^2g^{-1}	Square meter per gram
M100	Stress at 100% elongation
M300	Stress at 300% elongation
M_{HR}	Maximum torque
MPa	MegaPascal
phr	Part per hundred rubber
ppsi	pounds force per square inch
Q_f/Q_g	Rubber-filler interaction
revmin^{-1}	Revolution per minute
t_2	Scorch time
t_{90}	Cure time
Wd	Dried weight
Wi	Initial weight
Ws	Swollen weight

**SIFAT-SIFAT PEMATANGAN DAN MEKANIKAL SEBATIAN GETAH
ASLI TERISI SERBUK SISA TAYAR DAN HIBRID SERBUK SISA TAYAR**

ABSTRAK

Ciri-ciri pematangan, sifat-sifat tensil, kelesuan, kelakuan pembengkakan dan morfologi getah asli (NR) terisi serbuk sisa tayar (WTD) telah dikaji. Sebatian-sebatian NR terisi WTD dibandingkan pada pelbagai pembebanan pengisi mulai dari 0-30 phr. Ciri-ciri pematangan seperti masa skorj (t_2), masa pematangan (t_{90}) dan tork maksimum (M_{HR}) menurun dengan peningkatan pembebanan WTD. Sifat-sifat mekanikal seperti sifat-sifat tensil dan hayat fatig berkurang secara umumnya dengan penambahan pembebanan WTD. Penambahan pembebanan WTD juga menyumbang kepada penurunan nilai interaksi getah-pengisi, Q_f/Q_g . Dalam kajian ini, WTD dihibridkan bersama tiga pengisi berbeza iaitu hitam karbon (CB), kalsium karbonat ($CaCO_3$) dan gentian kenaf. Sebatian NR terisi dengan 30 phr hibrid WTD disebatikan mengikut peningkatan penggantian separa WTD dengan CB, $CaCO_3$ dan gentian kenaf pada 0, 10, 15, 20 dan 30 phr. Keputusan dari sifat-sifat yang disebutkan di atas seperti tork maksimum, sifat-sifat mekanikal dan interaksi getah-pengisi secara umumnya menunjukkan peningkatan nilai dengan peningkatan pembebanan CB dan $CaCO_3$ serta pengurangan nilai dengan peningkatan pembebanan gentian kenaf. Mikrograf-mikrograf SEM untuk permukaan retak semua sebatian menyokong keputusan-keputusan bagi sifat mekanikal.

Katakunci: Getah asli, Serbuk sisa tayar, Hibrid, Sifat-sifat mekanikal, Morfologi

**THE CURING CHARACTERISTICS AND MECHANICAL PROPERTIES
OF WASTE TYRE DUST AND WASTE TYRE DUST HYBRID FILLED
NATURAL RUBBER COMPOUNDS**

ABSTRACT

Curing characteristics, tensile properties, fatigue, swelling behaviour and morphology of waste tyre dust (WTD) filled natural rubber (NR) compounds were studied. The properties of WTD filled NR compounds were studied at various filler loading ranging from 0-30 phr. The curing characteristics such as scorch time (t_2) and cure time (t_{90}) and maximum torque (M_{HR}) decreased with increasing WTD loading. The mechanical properties such as tensile properties and fatigue life generally decreased with increasing amount of WTD loading. Increment of WTD loading also contributed to decreasing value of rubber-filler interaction, Q_f/Q_g . In this work, WTD is hybridized with three different fillers i.e. carbon black (CB), calcium carbonate ($CaCO_3$) and kenaf fibre. NR compounds filled with 30 phr of WTD hybrid are compounded with increasing partial replacement of WTD by the three fillers at 0, 10, 15, 20 and 30 phr. The results of the aforementioned properties like maximum torque, mechanical properties and rubber-filler interaction generally showed increment of values with increasing loading of CB and $CaCO_3$ as well as decreasing value after the addition of kenaf fibre. The SEM micrographs of fractured surface of all of the compounds supported the results for the mechanical properties.

Keywords: Natural rubber, Waste tyre dust, Hybrid, Mechanical properties, Morphology

CHAPTER 1

1 INTRODUCTION

1.1 Overview

Ever since the Scottish born John B. Dunlop made a discovery for pneumatic tyre in 1887 (Mount & List, 1994), the sale and consumption of tyre show no sign of slowing down. Tyre became big necessity for people worldwide as the number of vehicles likewise growing. The record of car production in 2008 alone stated that 52,940,559 cars have been produced worldwide (Worldometers, 2009). The cars production phenomenon is closely related to the tyre sales and demands. Sumitomo Rubber Industries Limited, the Japanese-based and also the second biggest tyre maker in China had estimated 10% growth of tyre sales a year from almost 150 million tyres in 2009.

The demands of tyres are not focusing merely on the newly produced cars but also on replacements. The motorists in China replaced about 100 million tyres in 2009 (Agencies, 2010). These big numbers of tyre sales and demands contribute to big number of tyre consumption as well as big number of waste. Hence those wastes drive major problem of pollution since all the waste would be dumped into landfills. Since waste tyres are non-biodegradable items, the landfills will be packed with the ever-increasing number of waste tyres. Thus, this matter should be overcome by promoting tyre recycling purposely to reduce the amount of waste tyre as well as amount of pollution.

Moreover, ASEAN state members like Malaysia, Indonesia and some other countries have reinforced Waste Management Policies. In Malaysia, legislation such as Solid Waste and Public Cleansing Management Corporation Act 2007 was drafted purposely to enforce solid waste management laws and related matters. In Indonesia, the handling of waste is governed by the Act of the Republic of Indonesia Number 18 Year 2008 (ASEAN Secretariat, 2009). Therefore, in reinforcing the aforementioned legislations, many methods are promoted in recycling used tyres such as pyrolysis which is a process involving thermal decomposition of waste tyres. There are also companies who rethreaded used tyres and sold them. Besides, other method of waste tyres recycling is also performed by processing them into small chips or crumbs or even dust.

Waste tyres or waste tyre dust (WTD) have been widely used in industry lately with the growing interest in environmental consciousness among industrialists and researchers nowadays. As reported by Gotteland et al. (2007), waste tyres possess many good properties like hydrophobic nature, high strength, low thermal conductivity etc. However, recycled products have major drawbacks that they are not able to perform like the virgin materials. Therefore, there are works done in saving the WTD from being unused. One of those works is by applying shredded waste tyre or waste tyre crumbs in light applications for example playground mat in recreation application. Despite the drawbacks of waste tyre as waste or recycled material, there are still efforts done by researchers in utilizing the good properties in waste tyre as mentioned before.

One of the efforts to apply the good properties of WTD is by fitting it in a hybrid system. Hybrid system, which comes from the word meaning something that is the product of different things is a system with combination of more than one substance or material. In fact, hybrid system is beneficial for a compound because there are contributions of properties from every substances or materials in the hybrid. The usage of hybrid fillers has proven improvements on composite performance. In addition, there are many studies (Ghosh et al., 2008; Jian et al., 2010 & Kudus et al., 2011) done regarding the usage of hybrid compounds. Through such studies, there are many discoveries of superiority of hybrid system such as the enhancement of thermal conductivity (Yu et al., 2008 & Lee et al., 2006), reduction of environmental degradation (Leong et al., 2003), improvement of mechanical properties (Kundu et al., 2004), chemical resistance (Kudina & Burya, 2010) and others.

In this project, WTD is paired with three well known, different reinforcement materials i.e. carbon black (CB), calcium carbonate (CaCO_3) and kenaf fibre. These three materials are highly available in Malaysia. Besides availability, they are also well known as filler or reinforcement materials in industry. Thus, these three materials are suitable to be chosen to be paired with WTD as hybrid. In addition, WTD and WTD hybrid will be compounded with virgin natural rubber (NR) in this work where the curing characteristics and mechanical properties of the compounds will be investigated.

1.2 Problem statement

In Singapore, there were around 25,100 tonnes waste tyres generated in 2008 alone (Tay, 2008). Waste tyres create environmental problems because of their non-biodegradable properties (El- Gammal et al., 2010). Therefore, one way to solve the problems is by recycling or reutilizing the waste tyre. As previously mentioned, waste tyres became well known among industrialists and researchers as the increase of environmental conscious occurs globally. Moreover, recycled materials are cheaper in term of price. Thus, the production cost of products will be reduced with the usage of recycled materials. Besides using waste tyre, cost reduction may occur through utilization of hybrid materials or hybrid fillers. For example, some industrialists use calcium carbonate in most part of the hybrid filler as the cost reducer (Bregg, 2006).

Hybridization also functions in upgrading the performance of composites or engineering materials. This concept has been studied by Lee et al. (2006) where aluminium nitride/wollastonite hybrid filler was used in enhancing the thermal conductivity for microelectronics application. Besides Lee et al. (2006), Nigam et al. (2001) had utilized the concept of hybridization through the usage of carbon black/phenolic resin hybrid filler in their nitrile rubber vulcanizates in their study. They had discovered that the usage of hybrid filler had increased the physico-mechanical properties of the vulcanizates. Besides the enhancement of the aforementioned properties, the utilization of hybrid filler is capable in optimizing weight reduction, swelling reduction and other desirable properties.

1.3 Research objectives:

The objectives of this project are listed below:

1. To study the effect of WTD loading on the curing characteristics, mechanical properties which are inclusive of tensile properties and fatigue life, rubber-filler interaction and morphological study of WTD filled NR compounds.
2. To study the effect of CB, CaCO₃, and kenaf fibre loading on the curing characteristics, mechanical properties which are inclusive of tensile properties and fatigue life, rubber-filler interaction and morphological study of WTD/CB hybrid filler filled NR compounds.
3. To study and compare the effect of CB, CaCO₃ and kenaf fibre loading on the curing characteristics, mechanical properties which are inclusive of tensile properties and fatigue life, rubber-fibre interaction and morphological study of WTD/kenaf fibre hybrid filler filled NR compounds.

CHAPTER 2

2 LITERATURE REVIEW

2.1 Tyre

2.1.1 Tyre recycling

The growth of development happens throughout the globe turn out to be the reason of the big necessity for raw materials especially materials from natural resources. The natural resources well known to equip the industrial needs are natural rubber, crude petroleum oil, mineral resources (like limestone etc.), natural fibres (like jute etc.) etc. The number of those natural resources that are previously mentioned is sometimes not growing but keep lessening like crude petroleum oil which are obtain through decomposition of fossil that takes million years of process. Furthermore, there are products from natural sources like natural rubber that cannot be biodegraded.

Therefore to prevent growing number of waste and rubbish and also to avoid the natural resources from running out, people have discovered ways like reusing, retreading, recovery or recycling. Those aforementioned methods can be considered a step in environmental saving, by reducing the consumption of virgin or natural rubber. In addition, tyre industry occupied one half of global natural rubber production (Food & Agriculture Organization of the United Nations, 1989). A few regions like Western Europe, Central Europe and North America are dominant consumers of natural rubber and at least half of the world's total rubber productions are from tyre industry (Booth, 1999).