

**EFFECTS OF EXPOSURE TO ELEVATED
TEMPERATURES ON THE BOND
CHARACTERISTICS BETWEEN NORMAL
CONCRETE SUBSTRATE AND ULTRA HIGH
PERFORMANCE FIBER REINFORCED
CEMENTITIOUS COMPOSITES**

NUR LIYANA BINTI ZAINAL

**UNIVERSITI SAINS MALAYSIA
2016**

**EFFECTS OF EXPOSURE TO ELEVATED TEMPERATURES
ON THE BOND CHARACTERISTICS BETWEEN NORMAL
CONCRETE SUBSTRATE AND ULTRA HIGH PERFORMANCE
FIBER REINFORCED CEMENTITIOUS COMPOSITES**

by

NUR LIYANA BINTI ZAINAL

**Thesis submitted in fulfilment of the
requirements for the degree of
Master of Science**

August 2016

ACKNOWLEDGEMENTS

I would like to express my special thanks of gratitude to my main supervisor of this study, Associate Professor Dr. Norazura Muhamad Bunnori for her guidance, motivation, endless encouragement and immense knowledge throughout the period of this research. Her guidance helped me in all the time of research and writing of this thesis. I am also thankful to my Co-supervisor Associate Professor Dr. Megat Azmi Megat Johari for his remarkable and support. His dedication and patience will be remembered and appreciated.

I would like to thank to my parents (*Zainal Saidin and Akhirin Mohamed Arof*) and to my siblings for their continuous support, endless love and to my beloved husband (*Muhammad Haidil*) for supporting me spiritually throughout writing this thesis. Not forgotten, thank you should be said to my best friends (*Mohd Helmi and Wan Norsariza Wan Husin*) for the stimulating discussions, their energy in helping me a lot in preparation of samples and their endless support.

Last but not least, I would like to extend my appreciation to the technicians (*En.Mohd Fauzi Zulkifle and En.Shahril Izham Md Noor*) from Concrete Laboratory School of Civil Engineering. Their kindly helps and time dedication during my lab work have made my research successful. Without their precious support, it would not be possible to conduct this research. Thank you for giving guidance, sharing and providing information and also help in carrying out this project from start to finish. Everything needs cooperation and it is hard to complete anything without help from each other. Again, my sincere gratitude goes to them for their efforts and encouragement.

TABLE OF CONTENTS

	Page
ACKNOWLEDGEMENTS	ii
TABLE OF CONTENTS	iii
LIST OF TABLES	ix
LIST OF FIGURES	xi
LIST OF SYMBOLS	xv
LIST OF ABBREVIATIONS	xvi
ABSTRAK	xix
ABSTRACT	xxi
CHAPTER ONE: INTRODUCTION	
1.1 Background	1
1.2 Problem statement	3
1.3 Research objectives	4
1.4 Research scope	4
1.5 Thesis structure	5
CHAPTER TWO: LITERATURE INTERVIEW	
2.1 Introduction	7
2.2 Ultra high performance fiber reinforced concrete (UHPFRC)	7

2.2.1	UHPFRC application in concrete structure and as repair material for rehabilitation.	10
2.2.2	Application of UHPFRC	11
2.3	Green Universiti Sains Malaysia Reinforced Concrete (GUSMRC)	16
2.3.1	GUSMRC materials content	17
2.3.1.1	Cement	17
2.3.1.2	Densified silica fume (DSF)	18
2.3.1.3	Ultrafine palm oil fuel ash (UPOFA)	18
2.3.1.4	Sand	21
2.3.1.5	Superplasticizer (SP)	21
2.3.1.6	Steel fibers	21
2.3.1.7	Water	22
2.4	Surface roughness treatment	23
2.5	Bonding strength between repair material and concrete substrate	25
2.5.1	Splitting tensile strength test	28
2.5.2	Flexural strength test	31
2.5.3	Pull-off test	32
2.5.4	Slant shear test	33
2.6	Concrete at elevated temperatures	35
2.6.1	Chemical reaction in concrete exposed to elevated temperatures	37
2.6.2	Physical changes in concrete exposed to elevated temperatures	39
2.6.3	Evaluation of concrete structures exposed to fire	41
2.6.4	Effect of recycled materials on properties of concrete exposed to elevated temperatures	43
2.6.4.1	Performance of concrete containing fly ash at elevated temperatures	44
2.6.4.2	Performance concrete containing POFA at elevated temperatures	45

2.6.4.3	Performance concrete containing silica fume at elevated temperatures	47
2.6.4.4	Performance concrete containing blast furnace slag at elevated temperatures	49
2.7	Summary	52

CHAPTER THREE: METHODOLOGY

3.1	Introduction	54
3.2	Preparation of materials	56
3.2.1	Cement	56
3.2.2	Silica fume	57
3.2.3	Aggregate	57
3.2.3.1	Coarse aggregate	57
3.2.3.2	Sand	58
3.2.4	Ultrafine palm oil fuel ash (UPOFA)	58
3.2.5	Water	60
3.2.6	Steel fibers	60
3.2.7	Superplasticizers	61
3.3	Mix proportions for NC substrate and GUSMRC	61
3.3.1	Normal concrete	61
3.3.2	GUSMRC	63
3.4	Curing of GUSMRC	66
3.5	Surface roughness for NC substrate	67
3.5.1	Sand blasting	67
3.5.2	Grinding	68
3.6	Evaluation of properties of samples (NC substrate and GUSMRC) and composite samples of NC/GUSMRC	70
3.6.1	Properties of NC substrate and GUSMRC	70

3.6.1.1	Compressive strength test	70
3.6.1.2	Modulus of elasticity test	71
3.6.1.3	Ultrasonic pulse velocity (UPV) test	71
3.6.1.4	Surface hardness test	72
3.6.1.5	Initial surface absorption test (ISAT)	72
3.6.1.6	Splitting cylinder tensile test	74
3.6.1.7	Flexural strength test	75
3.6.2	Bonding properties of composite samples of NC/GUSMRC	76
3.6.2.1	Slant shear test of composite NC/GUSMRC specimen	76
3.6.2.2	Splitting tensile test of composite NC/GUSMRC specimen	78
3.6.2.3	Pull-off test of composite NC/GUSMRC specimen	79
3.6.2.4	Flexural strength test of composite NC/GUSMRC specimen	81
3.6.3	Exposure to elevated temperatures	83
3.7	Data collection and analysis	85
3.8	Summary	86
CHAPTER FOUR: RESULTS AND DISSCUSSIONS		
4.1	Introduction	87
4.2	Mechanical properties of NC substrate and GUSMRC	87
4.3	Compressive strength	87
4.3.1	Compressive strength of NC substrate and GUSMRC	88
4.3.2	Splitting tensile strength	89
4.3.3	Flexural strength	90

4.3.4	Modulus of elasticity	91
4.4	Mechanical properties of NC substrate and GUSMRC at elevated temperatures	91
4.4.1	Compressive strength	92
4.4.2	Initial surface absorption (ISA)	96
4.4.3	Surface hardness	98
4.4.4	Ultrasonic Pulse Velocity (UPV)	99
4.4.5	Mass loss	101
4.5	Mechanical properties of composite NC/GUSMRC	102
4.5.1	Bonding strength based on slant shear test before exposure to elevated temperatures	103
4.5.2	Bonding strength based on slant shear test after exposure to elevated temperatures	105
4.5.3	Bonding strength based on splitting tensile test before exposure to elevated temperatures	109
4.5.4	Bonding strength based on splitting tensile test after exposure to elevated temperatures	111
4.5.5	Bonding strength based on flexural test before exposure to elevated temperatures	115
4.5.6	Bonding strength based on flexural test after exposure to elevated temperatures	117
4.5.7	Bonding strength based on pull-off test before exposure to elevated temperatures	120

4.5.8	Bonding strength based on pull-off test after exposure to elevated temperatures	124
4.6	Effect of NC surface treatment / roughness	127
4.7	General discussion	129

CHAPTER FIVE: CONCLUSIONS AND RECOMMENDATIONS

5.1	General	130
5.2	The physical and mechanical properties of NC and GUSMRC before and after exposure to elevated temperature	130
5.3	Influence of NC roughness on bonding	132
5.4	The properties of the bonded NC/GUSMRC at elevated temperatures	132
5.5	Recommendation for future research	134

REFERENCES	135
-------------------	------------

LIST OF PUBLICATION

LIST OF TABLES

		Page
Table 2.1	UHPFRC compositions	10
Table 2.2	Summary of the mechanical properties of GUSMRC at 28 days	17
Table 2.3	Physical properties of OPC, DSF and UPOFA	20
Table 2.4	Chemical composition of ordinary Portland cement, densified silica fume and ultrafine POFA	20
Table 2.5	Classification of W/B and W/C ratio for UHPFRC	23
Table 2.6	The results of pull-off test at different surface treatment	32
Table 2.7	Changes in concrete properties	38
Table 2.8	A review summary of concrete containing recycled material at elevated temperatures	50
Table 3.1	Chemical composition of Ordinary Portland Cement (OPC)	56
Table 3.2	Mix proportion of normal concrete	62
Table 3.3	Mix proportion of GUSMRC	64
Table 3.4	Specifications of Therm Concept KC80/14 furnace	84
Table 4.1	Splitting tensile strength for NC substrate and GUSMRC	90
Table 4.2	Flexural strength for normal concrete and GUSMRC	90
Table 4.3	Modulus of elasticity of normal concrete and GUSMRC	91
Table 4.4	Compressive strength for NC substrate and GUSMRC at elevated temperature	93
Table 4.5	Initial Surface Absorption Test (ISAT)	97

Table 4.6	Initial Surface Absorption Test (ISAT) at age of 28 days after exposure to fire	97
Table 4.7	Rebound value and cube compressive strength	99
Table 4.8	Rebound value and cube compressive strength at age of 28 days after exposure to fire	99
Table 4.9	Ultrasonic pulse velocity value of concrete specimen	100
Table 4.10	Ultrasonic pulse velocity value of concrete specimen at age of 28 days after exposure to fire	100
Table 4.11	Mass loss of concrete specimen before and after exposed to elevated temperature	102
Table 4.12	Slant shear test and failure modes of composite NC/GUSMRC	104
Table 4.13	Bond strength quality	104
Table 4.14	Slant shear strength value and failure modes after exposure to elevated temperatures at age of 28 days	107
Table 4.15	Splitting tensile strength and failure modes of composite NC/GUSMRC	110
Table 4.16	Splitting tensile strength value and failure modes after exposure to elevated temperatures at age of 28 days	112
Table 4.17	Flexural strength and failure modes of composite specimen NC/GUSMRC	116
Table 4.18	Flexural strength value and failure modes after exposure to elevated temperatures at age of 28 days	118
Table 4.19	Pull-off test value and failure modes of composite specimen NC/GUSMRC	121
Table 4.20	Pull-off test value and failure modes after exposure to elevated temperatures at age of 28 days	125

LIST OF FIGURES

		Page
Figure 2.1	Pedestrian bridges, Sherbrooke, Quebec, Canada	12
Figure 2.2	Bridge cross section after rehabilitation	13
Figure 2.3	Kampung Limsun Bridge, Rantau, Negeri Sembilan.	14
Figure 2.4	Plus Toll Canopy Second Penang Bridge (Malaysia)	15
Figure 2.5	Wilson Hall	15
Figure 2.6	Five different surface textures for slant shear test	25
Figure 2.7	Group of bond strength under tension stress	27
Figure 2.8	Group of pure shear stress	28
Figure 2.9	Group of bond under a combined state of shear and compression stresses	28
Figure 2.10	Cylindrical splitting composite specimens	29
Figure 2.11	Failure modes of splitting tensile test	30
Figure 2.12	Dimension of flexural test composite section	31
Figure 2.13	Pull-off test	33
Figure 2.14	Failure modes of slant shear strength test	35
Figure 2.15	A schematic of concrete deterioration under heating and cooling	39
Figure 2.16	The colour changes of heated concrete of two types surface with exposed aggregates and external surface of concrete specimen	40

Figure 2.17	Strength retention with temperature for concrete	42
Figure 2.18	The compressive strength of the specimen ET1 until ET5 after exposure to elevated temperatures	45
Figure 2.19	Residual compressive strength at elevated temperature	46
Figure 2.20	Compressive strength of concrete containing different replacement of SF	48
Figure 3.1	The flow chart of methodology	55
Figure 3.2	Treatment process of UPOFA	59
Figure 3.3	Brass coated micro steel fibers with two different length	60
Figure 3.4	Mixing procedures for GUSMRC	65
Figure 3.5	Conditions of standard heat curing	66
Figure 3.6	Steam curing for the composite specimen of NC/GUSMRC	66
Figure 3.7	Normal concrete surfaces after sand blast operation	68
Figure 3.8	Grid preparations for grinding types of surface treatment	69
Figure 3.9	Half of cylindrical specimens for splitting tensile strength test with two different surface textures.	69
Figure 3.10	Initial surface absorption test	73
Figure 3.11	Splitting tensile test	74
Figure 3.12	Compression test set up for composite specimen and the geometry of half specimen for slant shear.	77
Figure 3.13	Composite specimens for slant shear test	78
Figure 3.14	Composite specimens NC/GUSMRC for splitting tensile testing	79

Figure 3.15	Schematic diagrams of the bonded samples after coring process	80
Figure 3.16	Pull-off test	81
Figure 3.17	Dimension of composite specimen	82
Figure 3.18	Diagrammatic views for flexural test of concrete by third point loading method	82
Figure 3.19	AG-X Shimadzu Universal testing machine	83
Figure 3.20	Therm Concept KC80/14 furnaces	84
Figure 3.21	Specimens in the furnace	85
Figure 4.1	Compressive strength of NC substrate and GUSMRC	89
Figure 4.2	Percentage loss of compressive strength for normal concrete substrate	94
Figure 4.3	Percentage loss of compressive strength for GUSMRC	94
Figure 4.4	GUSMRC in cube dimension after exposure to 200 ⁰ C	95
Figure 4.5	GUSMRC in cube dimension after exposure to 500 ⁰ C	95
Figure 4.6	Failure modes for slant shear strength test	106
Figure 4.7	Percentage loss of slant shear bond strength for composite NC/GUSMRC prepared by using different surface roughness	108
Figure 4.8	Failure modes	113
Figure 4.9	Percentage loss of splitting tensile bond strength for composite NC/GUSMRC prepared by using different surface roughness	114
Figure 4.10	Failure at normal concrete substrate for flexural strength test	116

Figure 4.11	Percentage loss of flexural bond strength for composite NC/GUSMRC prepared by using different surface roughness	119
Figure 4.12	Types of failure for pull-off test	122
Figure 4.13	Type A: Substrate failure	123
Figure 4.14	Type B: Interfaces failure	123
Figure 4.15	Percentage loss of pull off test for composite NC/GUSMRC prepared by using different surface roughness	126
Figure 4.16	Results of NC/GUSMRC that was made of sand blast surface treatment	128
Figure 4.17	Results of NC/GUSMRC that was made of grinding surface treatment	128

LIST OF SYMBOLS

D	Number of scale divisions
f	Flow
t	Test point time period
T	The splitting tensile strength
P	Maximum applied load
L	Length of specimen

LIST OF ABBREVIATIONS

AC	As cast
ACI	American Concrete Institute
ASTM	American Society for Testing and Materials
BS EN	British European Standards Specifications
Ca(OH) ₂ or CH	Calcium hydroxide
CaO	Calcium Oxide
CaCO ₃	Calcium carbonate
CO ₂	Carbon dioxide
CARDIFRC	CARDIF-reinforced concrete
COV (%)	Coefficient of variance
C-S-H	Calcium silicate hydrates
C ₃ A	Tricalcium aluminate
DR	Drilled holes
DSF	Densified silica fume
FA	Fly ash
GBFS	Ground blast furnace slag
GPOFA	Ground-POFA
GUSMRC	Green Universiti Sains Malaysia Reinforced Concrete
GR	Grooved
HPC	High performance concrete

HSC	High strength concrete
HSGC	High strength green concrete
HRWR	High range water reducer
H ₂ O	Water
ISAT	Initial surface absorption test
MOE	Modulus of elasticity
NC	Normal concrete
OPC	Ordinary Portland Cement
RC	Reinforced concrete
POFA	Palm oil fuel ash
UPV	Ultrasonic pulse velocity
SB	Sand blasted
SEM	Scanning electron microscope
SF	Silica fume
S.D	Standard deviation value
SP	Superplasticizer
SiO ₂	Silicon dioxide
TPOFA	Treated-POFA
UHPFC	Ultra high performance fiber reinforced concrete
UHPFRCC	Ultra-high performance fiber reinforced cementitious composites
UPOFA	Ultrafine-POFA

WB	Wire brushed
W/B	Water/binder ratio
W/C	Water/cement ratio

**KESAN PENDEDAHAN KEPADA SUHU YANG TINGGI TERHADAP CIRI-
CIRI IKATAN ANTARA KONKRIT BIASA DAN KOMPOSIT BERSIMEN
BERTETULANG GENTIAN BERPRESTASI ULTRA TINGGI**

ABSTRAK

UHPFRCC kebiasaannya digunakan dalam pembinaan jambatan, pembaikan empangan, bangunan dan struktur konkrit yang lain. Kekuatan ikatan yang bagus antara konkrit lama dengan lapisan bahan pembaikan yang baru merupakan salah satu faktor dalam meningkatkan prestasi pembaikan konkrit. Walaubagaimanapun, konkrit akan terjejas apabila didedahkan kepada suhu yang tinggi dan jaminan kualiti kekuatan ikatan memerlukan kaedah yang boleh menilai kekuatan serta mengenal pasti jenis kegagalan. UHPFRCC hijau baru yang mana telah dipatenkan sebagai Universiti Sains Malaysia konkrit hijau bertetulang (GUSMRC) telah dicipta. Konkrit ini mengandungi 50 peratus jumlah simen dengan bahan pozolanik, iaitu POFA ultra halus (UPOFA). Objektif kajian ini iaitu untuk menyiasat ikatan antara muka apabila dikenakan pada suhu antara 100°C, 200°C, 300°C, 400°C and 500°C terhadap konkrit lama dan bahan baikpulih baru. GUSMRC telah digunakan sebagai bahan baik pulih baru dimana dua jenis kekasaran permukaan digunakan iaitu letupan pasir (sand blast) dan berlurah (grinding). Perubahan sifat-sifat kejuruteraan keatas sampel tunggal bahan baikpulih serta konkrit biasa juga dikaji selepas didedahkan pada suhu ternaik. Untuk pengujian sifat-sifat mekanikal dalam ikatan, ia diuji dengan menggunakan kaedah lereng ricih (slant shear), ujian ketegangan (splitting tensile), pull-off test dan ujian lenturan (flexural strength) untuk menentukan pengaruh kekasaran permukaan dan menguji kesan terhadap konkrit apabila dikenakan pada suhu yang tinggi. Keputusan menunjukkan lapisan konkrit

hijau mencapai ikatan antara muka yang tinggi dan sesuai disamping konkrit biasa. Tekstur lapisan letupan pasir menunjukkan ikatan antara muka yang tinggi jika dibandingkan dengan jenis berlurah sebelum dan selepas dikenakan suhu yang tinggi. Kebanyakan mod kegagalan berlaku pada konkrit biasa dan secara automatik membuktikan ikatan antara dua muka adalah kuat. Kehilangan kekuatan konkrit yang kritikal untuk GUSMRC dicatatkan pada suhu 400°C and 500°C.

**EFFECTS OF EXPOSURE TO ELEVATED TEMPERATURES ON THE
BOND CHARACTERISTICS BETWEEN NORMAL CONCRETE
SUBSTRATE AND ULTRA HIGH PERFORMANCE FIBER REINFORCED
CEMENTITIOUS COMPOSITES**

ABSTRACT

UHPFRCC is usually applied to rehabilitation bridge of dam, building and other structures. Good bond strength between old concrete substrate and a newly overlaid repair material is a very important factor in assuring the performance of concrete repairs. However, the properties of concrete would be affected when it is exposed to high temperature. The quality assurance of the bond strength requires methods that can quantify the bond strength as well as identify the failure mode. A newly patented class of green UHPFRCC known as green Universiti Sains Malaysia reinforced concrete (GUSMRC) was developed. This concrete contains 50% of the cement total volume by pozzolanic material, ultra-fine POFA (UPOFA). The objective of this study is to evaluate the interfacial bonding characteristics between old concrete and new repair material after the composite is exposed to elevated temperatures of 100^oC, 200^oC, 300^oC, 400^oC and 500^oC. GUSMRC was applied as the new repair material on the normal concrete substrate and the surface has been prepared / roughened either by sand blasting (SB) or grinding (GR). In addition, changes on the mechanical properties of the monolithic samples of the repair material as well as the normal concrete substrate were also evaluated after the exposure to the elevated temperatures. The characteristic of interfacial bond were assessed using the slant shear, pull-off, splitting tensile, and flexural strength test to evaluate the influence of two types of surface roughness and to evaluate the effect after the exposure to

elevated temperatures. The results showed that the new green concrete overlay achieved good bond strength with the NC. Sand blasting surface treatment showed the excellent bonding properties compared to grinding before and after the exposure to the elevated temperatures. Mostly all the failure modes showed failures at NC substrate and automatically proved that the bondings between two layers are strong. The critical loss of strength for GUSMRC was recorded at 400⁰C and 500⁰C.

CHAPTER ONE

INTRODUCTION

1.1 Background

Ultra-high performance fiber reinforced concrete (UHPFRC) is a type of concrete which has a compressive strength reaching 150MPa by improving the mix proportion of raw materials. This type of concrete has a record with high value in strength, durability and advanced performance according to Fardis (2012). Plus, UHPFRC is a super plasticized concrete with fibres as an improvement to achieve homogeneous mixes by the replacement of coarse aggregate with fine sand as stated by Richard *et al.* (1995). UHPFRC is well known due to its qualities in comparison with normal concrete (NC) and high performance concrete (HPC). The proportion of cement, silica fume, steel fiber and chemical admixtures made it has potential to develop a dense structure of concrete according to Hertz (2003). This ultra-fine particle fill out the void space and it greatly becomes dense and the different physical and chemical changes occurred between normal concrete and a concrete with a dense microstructure. The compressive strength of the dense concrete increases due to the high cement content, however, the overproduction of cement will increase the greenhouse gas emission and cause global warming (Worrel *et al.*, 2001; Arshad *et al.*, 2010). By replacing a greater amount of the cement and silica fume in UHPFRC mixes while maintaining its mechanical properties could be the best key. The partial replacement of ordinary Portland cement (OPC) by manufacturing wastes as supplementary cementitious materials such as palm oil fuel ash (POFA) could enhance the transport properties of concrete (Tay *et al.*, 1990; Tangchirapat *et al.*,