

**CURING, MECHANICAL AND AGING PROPERTIES OF BENTONITE
FILLED ETHYLENE PROPYLENE DIENE MONOMER COMPOSITES**

by

NURUS SAKINAH BINTI CHE MAT

**Thesis submitted in fulfillment of the
requirements for Degree of
Master of Science**

June 2018

ACKNOWLEDGEMENT

First and above all, I am thankful and grateful to the Almighty for providing me this opportunity and granting me the capability to complete this thesis. This thesis appears due the assistance and guidance of several people. I would therefore like to offer my sincere thanks to all of them. My special thanks to my main supervisor, Prof. Hanafi Ismail for his support, guidance, his patience and faith in me throughout have been extremely helpful. He was always available for my questions, positive in any situation and generously spent his time and vast knowledge to me whenever I needed it. He always knew where to look for the answers to obstacles while leading me to the right source, theory, and perspective. I would also love to thank my co-supervisor, Assoc. Prof. Dr Nadras Othman for her time and effort in checking my works, for sharing her knowledge, her valuable comments, guidance and also her words of encouragement to me. Her inspiring suggestions have been precious to me for the development of this thesis. Every result described in this thesis was also accomplished with the help and support from Mr Mohd. Suharudin b Sulong, Mr Shahril Amir b Saleh, Mr Norshahrizol b Nordin, Mr Mohd Faizal b Mohd Kassim, Mr Mohamad Shafiq b Mustapa, Mr Abdul Rashid b Selamat and Mr Muhammad Khairi b Khalid. I would like to express my appreciation for their assistance given in machines, tools training, materials and especially their hard works in helping me throughout this study. I am also grateful for the funding sources that allowed me to pursue my degree of Master: MyBrain15. My seniors and friends for their advices are very much appreciated and finally the most special thanks go to my parents and siblings for their constant love, and unconditional support. Without their encouragement throughout my life, it is impossible for me to complete this thesis.

TABLE OF CONTENTS

	Page
ACKNOWLEDGEMENT	ii
TABLE OF CONTENTS	iii
LIST OF TABLES	vi
LIST OF FIGURES	vii
LIST OF ABBREVIATIONS	x
LIST OF SYMBOLS	xii
ABSTRAK	xiii
ABSTRACT	xv
CHAPTER ONE: INTRODUCTION	
1.1 Overview	1
1.2 Problem Statements	3
1.3 Objectives of Study	5
1.4 Scope of Study	5
1.5 Thesis Organization	7
CHAPTER TWO: LITERATURE REVIEW	
2.1 Introduction	8
2.2 Composites	9
2.3 Ethylene Propylene Diene Monomer Rubber (EPDM)	9
2.3.1 Properties and Applications of EPDM	11
2.4 Natural Rubber (NR)	12
2.5 Vulcanization of Rubber	14
2.6 Fillers	18
2.6.1 Bentonite	19
2.6.2 Calcium Carbonate	25
2.7 Bentonite Filled Rubber Composites	27
2.7.1 EPDM/clay composites	31
2.8 Modification of Clay Based Rubber Composites	34
2.9 Rubber Blend	36

CHAPTER THREE: MATERIALS AND METHODOLOGY

3.1	Materials	40
3.2	Preparations of EPDM/Bt Composites	41
3.3	Preparation of EPDM/Bt/CaCO ₃	42
3.4	Preparation of EPDM/Bt Composites Modified with Si69	43
3.5	Preparation of EPDM/NR/Bt Composites	44
3.6	Composite Testing and Characterization	45
3.6.1	Curing Characteristics	45
3.6.2	Tear Properties	45
3.6.3	Aging Properties	46
3.6.4	Fatigue Life	46
3.6.5	SEM Morphological Study	47

CHAPTER FOUR: RESULTS AND DISCUSSION

4.1	Microstructure of Bt	48
4.2	Effect of Filler Loading on the Properties of EPDM/Bt Composites	49
4.2.1	Curing Characteristics	49
4.2.2	Tear Properties	53
4.2.3	Aging Properties	57
4.2.4	Fatigue Life	62
4.3	Effect of Partial Replacement of Bt by CaCO ₃	65
4.3.1	Curing Characteristics	65
4.3.2	Tear Properties	68
4.3.3	Aging Properties	70
4.3.4	Fatigue Life	75
4.4	Effect of Silane Coupling Agent (Si69)	77
4.4.1	Curing Characteristics	77
4.4.2	Tear Properties	81
4.4.3	Aging Properties	84
4.4.4	Fatigue Life	89
4.5	The Effect of Blend Ratio of EPDM/NR on Properties of EPDM/NR/Bt Composites	92
4.5.1	Curing Characteristics	92

4.5.2	Tear Strength	94
4.5.3	Aging Properties	97
4.5.4	Fatigue Life	101
CHAPTER FIVE: CONCLUSIONS AND RECOMMENDATIONS		
5.1	Conclusions	104
5.2	Recommendations for Future Work	105
REFERENCES		107
CONFERENCE PROCEEDINGS		
LIST OF PUBLICATIONS		

LIST OF TABLES

		Page
Table 3.1	Formulations of EPDM/Bt composites	41
Table 3.2	Formulations for EPDM/Bt/CaCO ₃ composites	42
Table 3.3	Formulations for EPDM/Bt composites with different Si69 loading	43
Table 3.4	Formulations for EPDM/NR/Bt composites	44

LIST OF FIGURES

		Page
Figure 2.1	Molecular Structure of EPDM with ENB as diene monomer (Stickler & Richard, 2006)	10
Figure 2.2	Chemical structure of cis-1, 4- polyisoprene (Matar & Hatch, 2001)	13
Figure 2.3	Types of sulphur crosslink: (a) monosulphidic, (b) disulphidic, and (c) polysulphidic	17
Figure 2.4	Typical structure of Montmorillonite (MMT) (White & Kim, 2008)	21
Figure 2.5	Silane mechanisms with clay (Dai & Huang, 1999)	23
Figure 4.1	SEM micrograph of Bt particles at a) 1000, and b) 5000 x magnifications	48
Figure 4.2	Optimum cure time, t_{90} and scorch time, ts_2 at various Bt loading of EPDM/Bt composites	50
Figure 4.3	Maximum torque and minimum torque of EPDM/Bt composites	52
Figure 4.4	Tear strength of EPDM/Bt at different Bt loading	53
Figure 4.5	Tear fractured surfaces of EPDM/Bt composites with a) 0 phr, b) 10 phr, c) 30 phr, d) 90 phr and e) 120 phr Bt loading [100 x Magnifications]	56
Figure 4.6	Tear strength of EPDM/Bt composites before and after aging	58
Figure 4.7	Tear Strength Retention of EPDM/Bt composites	59
Figure 4.8	Tear fractured surfaces of EPDM/Bt composites before and after aging with a) 10 phr, b) 30 phr and c) 90 phr Bt loading [100 x Magnifications]	61
Figure 4.9	Fatigue life of EPDM/Bt composites	63
Figure 4.10	SEM micrograph of fatigue fractured surface of EPDM/Bt composite a) failure zone at 30 x magnifications, and at b) 10 phr, c) 30 phr and d) 90 phr Bt loading [100 x magnifications]	64

Figure 4.11	Optimum cure time and scorch time of EPDM/Bt/CaCO ₃ composites	65
Figure 4.12	Maximum torque and minimum torque of EPDM/Bt/CaCO ₃ composites	67
Figure 4.13	Tear Strength of EPDM/Bt/CaCO ₃ composites	69
Figure 4.14	SEM micrographs for EPDM/Bt/CaCO ₃ composites with (a) 30/0, (b) 15/15 and (c) 0/30 loading ratio of Bt/CaCO ₃	70
Figure 4.15	Tear strength of EPDM/Bt/CaCO ₃ composite before and after aging	71
Figure 4.16	Tear Strength retention of EPDM/Bt/CaCO ₃ composites	72
Figure 4.17	Tear fractured surface of EPDM/Bt/CaCO ₃ composites before and after aging with Bt/CaCO ₃ loading ratio of (a) 30/0, (b) 15/15 and (c) 0/30	74
Figure 4.18	Fatigue life of EPDM/Bt/CaCO ₃ composites	76
Figure 4.19	SEM micrographs of fatigue fractured surfaces of EPDM/Bt/CaCO ₃ composites at the loading ratio of Bt/CaCO ₃ of (a) 30/0, (b) 15/15 and (c) 0/30 [100 x magnifications]	77
Figure 4.20	Optimum cure time and scorch time of EPDM/Bt composites with different Si69 loading	79
Figure 4.21	Chemical structure of silane coupling agent (Si69) (Pongdong et al., 2015)	79
Figure 4.22	Maximum torque and minimum torque of EPDM/Bt composites with different Si69 loading	80
Figure 4.23	Tear Strength of EPDM/Bt composites with different Si69 loading	83
Figure 4.24	SEM micrographs of EPDM/Bt composites at a) 0.3 phr, b) 0.5 phr, and c) 1 phr of Si69 [100 x Magnifications]	84
Figure 4.25	Tear Strength of EPDM/Bt composites with different Si69 loading before and after aging	85
Figure 4.26	Retention of tear strength of EPDM/Bt composites with different Si69 loading	86
Figure 4.27	Tear fractured surfaces of EPDM/Bt composites before and	88

	after aging at a) 0 phr, b) 0.3 phr, c) 0.5phr, and d) 1 phr Si69	
Figure 4.28	Fatigue life of EPDM/Bt composites with different Si69 loading	89
Figure 4.29	SEM micrographs of fatigue fractured surfaces of EPDM/Bt composites with a) 0.3 phr, b) 0.5 phr, and c) 1 phr Si69 [100 x Magnifications]	91
Figure 4.30	Optimum cure time and scorch time of EPDM/NR/Bt composites	92
Figure 4.31	Maximum torque and minimum torque of EPDM/NR/Bt composites	94
Figure 4.32	Tear strength of EPDM/NR/Bt composite	94
Figure 4.33	Tear fractured surface of EPDM/NR/Bt composite at a) 75/25, b) 50/50, and c) 0/100 EPDM/NR blend ratio [100 x Magnifications]	96
Figure 4.34	Tear strength of EPDM/NR/Bt composites before and after aging	98
Figure 4.35	Retention of tear strength of EPDM/NR/Bt composites	99
Figure 4.36	Tear fractured surfaces of EPDM/NR/Bt composites at a) 75/25, b) 50/50, and c) 0/100 EPDM/NR blend ratio after aging	100
Figure 4.37	Fatigue life of EPDM/NR/Bt composites at different EPDM/NR blend ratio	101
Figure 4.38	Fatigue tear surfaces of EPDM/NR/Bt composites at a) 75/25, b) 50/50, and c) 0/100 EPDM/NR blend ratio [100 x magnifications]	103

LIST OF ABBREVIATIONS

ASTM	American Standard for Testing and Materials
EPDM	Ethylene Propylene Diene Monomer Rubber
NR	Natural Rubber
BR	Butadiene Rubber
SBR	Styrene Butadiene Rubber
NBR	Nitrile Butadiene Rubber
ENR	Epoxidised Natural Rubber
MBT	2 mercapto benzothiazole
MBTS	Dibenzothiazole disulfide
MMT	Montmorillonite
oMMT	Organomontmorillonite
phr	Part per hundred rubber
Si69	Bis-(3-triethoxysilylpropyl) tetrasulfide
APTES	3-(aminopropyl)triethoxysilane
FESEM	Field Electron Scanning Microscope
FTFT	Fatigue-to failure test machine
rpm	Rotation per minutes
J.I.S	Japanese Industrial Standard Average
Bt	Bentonite
CaCO ₃	Calcium Carbonate
Fe ₂ O ₃	Iron Oxide
MgO	Magnesium Oxide
Al ₂ O ₃	Aluminium Oxide

Bt/CaCO ₃	Ratio of Bentonite to Calcium Carbonate
EPDM/NR	Ratio of Ethylene Propylene Diene Monomer to Natural Rubber
Ca ²⁺	Calcium ion
CaO	Calcium Oxide
K ₂ O	Potassium Oxide
Na ²⁺	Sodium ion
K ⁺	Potassium ion
-OH	Hydroxyl group
-SiOH	Silanol group
Al ³⁺	Aluminium ion
Fe ²⁺	Iron ion
Mg ²⁺	Magnesium ion

LIST OF SYMBOLS

Å	Amstrong
g/mol	Gram per molecule
%	Percentage
g cm ⁻¹	Gram per centimeter
cm ⁻¹	Per cm
g/m ²	Gram per meter square
°C	Degree Celsius
mm	Millimeter
cm	Centimeter
g	Gram
µm	Micrometer
nm	Nanometer
t ₉₀	Optimum cure time
ts ₂	Scorch time
MH	Maximum torque
ML	Minimum torque
N/mm	Newton per millimeter
h	Hours
Hz	Hertz
dNm	Deci Newton meter
mm/min	Millimeter per minutes
N	Newton

SIFAT-SIFAT PEMATANGAN, MEKANIKAL DAN PENUAAN KOMPOSIT ETILENA PROPILENA DIENA MONOMER TERISI BENTONIT

ABSTRAK

Tujuan kajian ini adalah pertama, untuk menyiasat kesan pembebanan bentonit (Bt), kedua, pengantian separa Bt oleh kalsium karbonat (CaCO_3), ketiga, pengubahsuaian Bt oleh bis (3-trietoksisililpropil) tetrasulfida (Si69), dan akhir sekali, kesan campuran nisbah etilena propilena diena monomer (EPDM)/ getah asli (NR) atas sifat-sifat pematangan, sifat koyak dan penuaan serta hayat fatig komposit EPDM terisi Bt. Komposit EPDM terisi Bt disediakan dengan mesin penggiling bergulung dua dan dimatangkan pada 150^0C . Sifat-sifat pematangan komposit dikaji dengan menggunakan mesin Rheometer dan sifat-sifat mekanik ditentukan menggunakan Instron dan mesin ujian 'Fatigue-to-Failure'. Hasil kajian mendapati bahawa penambahan bentonit telah mengurangkan masa skorj (t_{s2}) dan meningkatkan masa pematangan (t_{90}), tork maksimum (MH), dan tork minimum (ML) komposit EPDM/Bt. Kekuatan koyak dan sifat penuaan (berdasar kepada peratusan pengekal) masing-masing bertambah baik sehingga 90 bsg dan 70 bsg Bt, tetapi hayat fatig komposit EPDM/Bt berkurang. Penggantian separa Bt oleh CaCO_3 telah mengurangkan ML dan meningkatkan t_{s2} , t_{90} , dan MH. Kekuatan koyak dan hayat fatig menurun tetapi sifat penuaan menaik dengan meningkatnya CaCO_3 di dalam nisbah pembebanan Bt/ CaCO_3 bagi komposit EPDM/Bt/ CaCO_3 . Hasil dari komposit EPDM/Bt yang telah diubahsuai dengan Si69, t_{s2} meningkat sedikit manakala t_{90} berkurang. Kedua-dua MH dan ML didapati meningkat sehingga 0.5 bsg Si69. Sifat penuaan komposit EPDM/Bt meningkat dengan meningkatnya Si69. Kekuatan koyak dan hayat fatig komposit EPDM/Bt meningkat sehingga 0.5 bsg Si69. Peningkatan

NR di dalam nisbah adunan EPDM/NR telah mengurangkan ts_2 , t_{90} , dan ML tetapi meningkatkan MH komposit EPDM/NR/Bt. Kekuatan koyak dan hayat fatig meningkat tetapi sifat penuaan berkurang dengan meningkatnya NR di dalam nisbah adunan EPDM/NR komposit EPDM/NR/Bt.

CURING, MECHANICAL AND AGING PROPERTIES OF BENTONITE FILLED ETHYLENE PROPYLENE DIENE MONOMER COMPOSITES

ABSTRACT

The aims of this research were firstly, to investigate the effect of bentonite (Bt) loading, secondly, the partial replacement of Bt by calcium carbonate (CaCO_3), thirdly, the modification of Bt by bis (3-triethoxysilylpropyl) tetrasulfide (Si69) and the last one, the effect of blend ratio of ethylene propylene diene monomer (EPDM)/natural rubber (NR) on the curing characteristics, tear and aging properties as well as fatigue life of bentonite filled EPDM composites. EPDM/Bt composites were prepared by two roll mills and vulcanized at 150°C . The curing characteristics of the composites were investigated by using rheometer and mechanical properties were determined by using Instron and fatigue-to-failure test machine. It was found that addition of Bt decreased scorch time (ts_2) and increased optimum cure time (t_{90}), maximum torque (MH) and minimum torque (ML) of EPDM/Bt composites. Tear strength and aging property (based on retention percentage) improved up to 90 phr and 70 phr Bt, respectively but fatigue life of EPDM/Bt composites decreased. The partial replacement of Bt by CaCO_3 decreased ML and increased ts_2 , t_{90} , and MH. The tear strength and fatigue life decreased but aging property increased with increasing of CaCO_3 in Bt/ CaCO_3 ratio loading of EPDM/Bt/ CaCO_3 composites. As EPDM/Bt composites were modified with bis (3-triethoxysilylpropyl) tetrasulfide (Si69), ts_2 was slightly increased meanwhile t_{90} decreased. Both MH and ML were found increased up to 0.5 phr Si69. The aging property of EPDM/Bt composites increased with increasing Si69. The tear strength and fatigue life of EPDM/Bt composites increased up to 0.5 phr Si69. Increasing NR in blend ratio of EPDM/NR

decreased ts_2 , t_{90} and ML while increased MH of EPDM/NR/Bt composites. The tear strength and fatigue life increased but aging property decreased as NR increased in EPDM/NR blend ratio of EPDM/NR/Bt composites.

CHAPTER ONE

INTRODUCTION

1.1 Overview

The improvement in properties obtained by Toyota groups on polymer/clay nanocomposites has made the study based on clay nanocomposites been a focus of attention for the other scientists to further explore and this include the studies on rubber/clay based nanocomposites. The great improvement in this rubber/clay nanocomposites being studied have been ascribed to the possible reinforcement exhibited by the addition of organoclay in the nanocomposites itself. Clays in general consist of layered silicates. One of the examples of layered silicate is Bentonite. Bentonite comprised of montmorillonite in major parts of its constituents, and with the presence of small amount of quartz, biotite and feldspar (Ismail and Mathialagan, 2012). Bentonite is hydrophilic in nature. This is attributed to the presence of MMT that consists of silanol groups on its surface, with relatively weak forces in between their interlayer and therefore they are hydrated and highly polar. The addition of clay in rubber composites can have a great effect on the mechanical properties and characteristics of the composites. Enhanced properties of the nanocomposites usually are obtainable at low amount of filler. There are many studies reported in the past to have utilized bentonite as filler in the polymeric material. The difference level of polarity between rubber and inorganic materials can be a matter of problem in the composites as the difficulty may arise from the effort in order to obtain optimum interfacial interaction between the two. It is essential that the clay is treated or modified as to enable the clay to be compatible to the rubber matrix. Several attempts

have been studied to explore for a suitable compatibilizer in corresponding to overcome this problem (Alkadasi et al., 2005; Ge et al., 2015; Sabatini et al., 2015). Researchers also try to hybrid between two or more fillers (Qian et al., 2008; Sikong et al., 2015; Razzaghi-Kashani & Samadi, 2015) and blending with other elastomeric materials (Sahakaro et al., 2008; Pticek et al., 2007; Vijayalekshmi & Abdul Majeed, 2013). All these methods are the alternatives in order to find new and cheap materials that can improve and maintain the desirable end properties of rubber/clay composites.

In some applications where cost is important, Bt is considered fairly expensive and high loading of Bt are also required to achieve certain properties (Mathialagan & Ismail, 2011). Partial replacement of Bt by a much cheaper non-black filler such as calcium carbonate is therefore needed in order to reduce the cost as well as the weight of the rubber composites, which in this research, ethylene propylene diene monomer (EPDM) rubber is used. EPDM is one of the most important synthetic rubbers that are widely used in the advance of rubber industry. They found their vast applications in commodity and also specialty products in the market such as in automotive application, construction, and building profiles. For example, EPDM is used widely as tire sidewalls, window and door seals, hose and tubing, roof membranes, wire and cable insulators, gasket and even in footwear (Salamone, 1999). EPDM is a very nonpolar type of rubbers having a saturated polymer backbone. Their low level of unsaturation makes them having an excellent resistance to heat, aging and oxidation. EPDM also has a high thermal stability and electrical resistivity, besides having a low temperature flexibility and ability to accept high filler loading.

1.2 Problem Statements

In order to optimize the properties of the composites so that it satisfies the requirement of certain applications, the uses of filler that have a reinforcing effect to the rubber composites are necessary. Among the reinforcing filler used to improve the processing characteristics and mechanical properties of the vulcanizate, carbon black has been the most important filler among many types of fillers. However, the inability to alter the final colour of the products limits the use of carbon black in certain application. Besides, carbon black also is very dependent on the petroleum feedstock which therefore increased the cost of the materials. These limitations have then shifted the interest of the researchers to find non-black filler that can give a significant improvement to the rubber vulcanizate.

Examples of non black fillers are such as silica, calcium carbonate, and clay. Bentonite is in smectite clay group that is reinforcing but in order to have certain properties, they need to be used in high loading. As compared to other type of clays such as kaolin and illite clay, bentonite has high absorption of water, able to adsorb and absorb toxin and impurities and has high pH making it the most advantageous clay and therefore is consider being costly in commercial, hence there is a need to hybrid bentonite with fillers that is much cheaper. Incorporation of CaCO_3 to replace partially the use of Bt able to reduce the cost of EPDM composites. In another aspect, eventhough Bt able to enhance the properties of the composites, the researchers found that the use of Bt can result in a poor dispersion especially in non-polar rubber matrix such as EPDM. This is attributed to the problem of polarity different between polar clay and nonpolar rubber matrix that results them to be incompatible to each other. Considering this setback, therefore, there is a need to modify the surface of Bt

so that the interaction between Bt and EPDM matrix can be improved. One of the ways that can be used are by using silane coupling agents such as (3-aminopropyl)triethoxysilane (APTES) and Bis-(3-triethoxysilylpropyl)tetasulfide (Si69). Si69 are reported to have a great capability to reduce a filler-filler interaction and improve the reinforcing ability of clay compared to APTES (Siriwong et al., 2013). The influence of filler though is important, yet in order to achieve desired properties in some cases, the blends of two or more elastomer are preferred. EPDM have low saturated rubbers with a small concentration of nonconjugated diene. They impart good resistance especially towards oxidation, ozone and heat. This thus made them being preferred the most in outdoor applications but their poor resistance to fatigue limits their use in vibration application such as automotive engine mounts. Therefore, in order for EPDM/Bt composites to have good properties in both fatigue life and also thermal stability, NR was blended with EPDM (which is widely known having an excellent resistance to fatigue). Earlier study from Mathialagan and Ismail, (2011) have been focusing on the improvement of properties of EPDM/Bt composites in term of its curing characteristics, tensile and thermal properties where the improvement in terms of their tear strength, aging resistance and fatigue life have not been touched. This research would be a continuous work based on similar EPDM/Bt composites used but with different approach of testing to further investigate the ability of incorporation of Bt as a reinforcing filler in EPDM composites. In this present work, Bt and Si69 loading, as well as the loading of Bt/CaCO₃ ratio and EPDM/NR blend ratio on the curing characteristics, tear strength, aging properties and fatigue life of EPDM composites are studied to further investigate the potential use of Bt as a reinforcing filler in EPDM composites.

1.3 Objectives of Study

1. To investigate the effect of Bt loading on the curing characteristics, tear strength, aging resistance, and fatigue life of EPDM/Bt composites.
2. To investigate the effect of partial replacement of Bt by CaCO_3 on the processing characteristics and properties of EPDM composites.
3. To determine the effect of silane coupling agent, Si69 on the processing characteristics and the properties of EPDM/Bt composites.
4. To determine the effect of EPDM/NR blend ratio on the processing characteristics and the properties of EPDM/Bt composites.

1.4 Scope of Study

The focus of the work was to investigate the curing characteristics, mechanical and aging properties based on bentonite filled EPDM composites. There are two mechanical properties investigated in this work which are tear strength and fatigue life. SEM morphology was studied to prove any development in the properties. The work was divided into several parts and as follows:

1. Effect of Bt loading on the properties of EPDM/Bt composites.

This part will focus on the preparation and the work to prove the possibility of Bt to be used as a filler in EPDM composites. The loading of Bt was varied in order to see any development in properties with increasing of Bt in rubber composites. SEM morphology was

used to prove the possible reinforcement by Bt. Optimum Bt loading that can obtain the highest properties of the composites was also determined along the study.

2. Partial replacement of Bt by CaCO_3 as filler in EPDM/Bt composites.
The use of CaCO_3 as a partial replacement to Bt was investigated. Loading ratio of Bt to CaCO_3 was varied to compare the possible reinforcement by these two fillers in EPDM/ CaCO_3 /Bt composites.
3. In situ addition of si-69 on the properties of EPDM / Bt composites
Silane coupling agent was utilized to improve the properties of the rubber composites. Si-69 was used and added via in-situ method to improve the adhesion of Bt to EPDM matrix. Optimum loading of Si-69 that can achieve highest reinforcement was determined from the study. SEM was used to prove any possible increase in the properties of EPDM/Bt composites.
4. The effects of EPDM/NR blend ratio on the properties of EPDM/NR/Bt composites.
Any possible reinforcement with the use of different blend ratio of NR and EPDM rubber on the curing characteristics and the properties EPDM/NR/Bt composites was determined in the study.

1.5 Thesis Organization

There are five chapters in this thesis. The chapters are as follows:

- **Chapter one** focuses on the introduction to the thesis. The introduction consists of the overview of the thesis in general, follows by problem statements, the main objectives, the importance of this research, as well as the scope of study and the thesis organization.
- **Chapter two** covers the literature reviews related to the research work particularly EPDM/Bt composites. It also includes the general introduction about EPDM and NR, and fillers used which are bentonite, and calcium carbonate.
- **Chapter three** gives the information about the materials used in this research. It also includes the compound formulations and experimental procedures to prepare the composites as well as the testing used to evaluate the properties obtained for each of the composites.
- **Chapter four** contains discussions on the effect of bentonite, Bt/CaCO₃ loading ratio, Si69 loading and EPDM/NR blend loading ratio on the processing characteristic and mechanical properties of the composites.
- **Chapter five** concludes the findings of this research work and some recommendations for future work.

CHAPTER TWO

LITERATURE REVIEW

2.1 Introduction

A rubber composite that is able to act as multi-functional materials is one of the reasons that there were a vast journal articles that can be found related to the study of rubber composites. This is because they are capable in improving not only one but some of the properties of the individual materials. This is a very desirable especially to the researchers in order for the materials to meet the requirement in certain applications especially the one that need the materials to be lightweight and durable such in aircraft. The use of rubber composites also is very useful in producing low-cost materials and this is why composites were actually being preferred more to be used as a replacement or combination to other materials in producing products. The use of clay able to enhance the properties of the nanocomposites and even better than the use of carbon black which was more established and popular among other type of filler due to its reinforcing capability. Not only that, the use of clay is very desirable as it can be used to alter the final colour of the product which is however limited with the use of carbon black. In this chapter, the overviews around clay based EPDM composites will be presented.