

**WOVEN CARBON FIBER EPOXY COMPOSITE LAMINATES
REINFORCED WITH CARBON NANOTUBE INTERLAYER USING
ELECTROSPRAY DEPOSITION METHOD**

by

MUHAMMAD RAZLAN BIN ZAKARIA

**Thesis submitted in fulfillment of the
requirements for the degree of
Doctor of Philosophy**

February 2020

ACKNOWLEDGEMENT

In the name of Allah, Most Gracious, Most Merciful. First and foremost, I would like to express my highest gratitude to the Almighty God, Allah swt for giving me the strength, healthy and opportunity to complete this thesis for the requirements of Doctor of Philosophy (PhD). I am extremely happy that I finished this dissertation. When you see your 3 years of work finally taking form, the feeling was enormous. I went through a gamut of emotions from depression to enlightenment during my PhD. The journey is definitely worth. I want to thank all of them who stood by me.

Special appreciation goes to my PhD supervisor, Professor Dr. Hazizan Md Akil for his inspiration and guidance. A good teacher is worth a million of books. I am lucky enough to have access to one million books. I am a researcher because of him. He encouraged me to learn many interdisciplinary research techniques, pushed me to perform and understood my strengths and limitations. During my PhD, I might have been frustrated with the results, impatient with my experiments but never felt bad about my work. To this very moment, I enjoyed my work. My heartfelt thanks to him for making me enjoy my PhD.

My warmest appreciation goes to my beloved parents. They are my first teachers; I am what I am because of their upbringing. I admire my father, Zakaria Bin Salleh and my mother, Hasnah Binti Darus. My parents have a great faith in my progress than anyone else. This gives a great boost for my confidence. No amount of thanks can acknowledge the sacrifices my parents made for educating me. It is not only my perseverance, which got me through the PhD, also theirs. I also thank my siblings for their unconditional support.

I am very grateful with special thanks to my wife, Noor Ashikin Binti Abidin who has been a constant source of support and encouragement. She has to go through everything with me during this PhD journey. One of the things I'm going to remember forever is that she almost lost her life when she gives birth to my son, Muhammad Aidil Zahran Bin Muhammad Razlan, just five months before this thesis complete. Looking at them also always made me stronger, better and encourage me to complete this PhD earlier.

Furthermore, I would like to express my special thanks of gratitude to University Sains Malaysia especially to School of Materials and Mineral Resources Engineering lead by Associate Professor Ir. Dr. Syed Fuad Bin Saiyid Hashim with former dean Professor Dr. Zuhailawati Binti Hussain for offering this great opportunity and providing enough resources, facilities, and instruments. Also, my thanks go to MyBrain scholarship under the Ministry of Higher Education Malaysia.

Finally, I have to acknowledge myself for hanging on there for 3 years. Only I can understand the emotional roller coaster I rode to come to this point. Above all, I have a great sigh of relief that it is done. I am very happy that I went through this unique PhD experience. These PhD years at USM will definitely be one of the great memories in my life.

TABLE OF CONTENT

	Page
ACKNOWLEDGEMENT	ii
TABLE OF CONTENTS	iv
LIST OF TABLES	ix
LIST OF FIGURES	xi
LIST OF ABBREVIATIONS	xv
LIST OF SYMBOLS	xvii
ABSTRAK	xix
ABSTRACT	xxi
CHAPTER ONE: INTRODUCTION	
1.1 Background of the Research	1
1.2 Problem Statement	3
1.3 Objectives	5
1.4 Scope of Research	6
1.5 Thesis Outline	8
CHAPTER TWO: LITERATURE REVIEW	
2.1 Carbon Fiber	9
2.1.1 History of Carbon Fiber	9
2.1.2 Structure of Carbon Fiber	10
2.1.3 Carbon Fiber Sizing	11
2.2 Carbon Nanotube	13
2.2.1 History of Carbon Nanotube	13

2.2.2	Structure of Carbon Nanotube	14
2.2.3	Properties of Carbon Nanotube	16
2.2.3(a)	Mechanical Properties	17
2.2.3(b)	Thermal Properties	18
2.2.4	Stability of the CNT in Solvent	19
2.3	Hybridization of Carbon Fiber and Carbon Nanotube	20
2.3.1	Chemical Vapour Deposition Method	21
2.3.2	Electrophoretic Deposition Method	28
2.3.3	Electrospray Deposition Method	35
2.3.4	Chemical Functionalization Method	40
2.4	Performance of the Hybrid CF-CNT	45
2.4.1	Mechanical Properties	45
2.5	Performance of the Hybrid CF-CNT reinforced Polymer Composites	50
2.5.1	Mechanical Properties	50
2.5.2	Thermal Properties	53
2.6	Summary of Literature Review	54

CHAPTER THREE: MATERIALS AND METHODOLOGY

3.0	Overview	56
3.1	Raw Materials	56
3.1.1	Carbon Fiber	56
3.1.2	Multi-Walled Carbon Nanotube (MWCNT)	57
3.1.3	N-Methyl-2-Pyrrolidone (NMP)	57
3.1.4	N,N-Dimethylformamide (DMF)	58
3.1.5	Tetrahydrofuran (THF)	58

3.1.6	UV Epoxy Adhesive	58
3.1.7	Epoxy Laminating System	59
3.1.7(a)	Epoxy Resin	59
3.1.7(b)	Epoxy Hardener	60
3.2	Experimental Method	61
3.2.1	Preparation of Woven Hybrid CF-CNT	61
3.2.2	Preparation of Woven Hybrid CF-CNT Epoxy Composites Laminates via Vacuum Assisted Resin Transfer Molding (VARTM)	64
3.3	Characterization of CNT Dispersion in Solvent	67
3.3.1	Zeta Potential Analysis	67
3.3.2	UV-Vis Spectroscopy	68
3.4	Characterization of the Meniscus of the Electrospray	68
3.4.1	Digital Microscope	68
3.5	Characterization of the Woven Hybrid CF-CNT	68
3.5.1	Field Emission Scanning Electron Microscope (FESEM)	68
3.5.2	High Resolution transmission electron microscope (HRTEM)	69
3.5.3	Raman Spectroscopy	69
3.5.4	X-ray Diffraction (XRD)	69
3.5.5	Fourier Transform-Infrared (FT-IR) Spectroscopy	70
3.5.6	X-ray Photoelectron Spectroscopy (XPS)	70
3.5.7	Single Fiber Test	71
3.6	Characterization of the Epoxy Composite Laminates	71
3.6.1	Density	71
3.6.2	Fiber Volume Fraction Measurement	71

3.6.3	Tensile Test	73
3.6.4	Flexural Test	74
3.6.5	FESEM	75
3.6.6	Short Beam Shear (SBS) Test	75
3.6.7	Thermal Conductivity	76
3.6.8	Dielectric Test	76

CHAPTER FOUR: RESULTS AND DISCUSSION

4.1	Degree of Stability of CNT in Various Types of Solvent	78
4.1.1	Optical Observation	78
4.1.2	Zeta Potential Analysis	80
4.1.3	UV-Vis Spectroscopy	83
4.2	Distribution of CNT Deposition on the Woven CF by Varying Voltage and Spray Time of ESD	87
4.2.1	Digital Microscope	87
4.2.2	FESEM Analysis	89
	4.2.2(a) Effect of Voltage	89
	4.2.2(b) Effect of Spray Time	93
4.3	Effect of ESD deposited CNT on the quality of the woven hybrid CF-CNT	96
4.3.1	HRTEM Analysis	96
4.3.2	XRD Analysis	98
4.3.3	Raman Spectroscopy Analysis	99
4.3.4	FT-IR Spectroscopy Analysis	101
4.3.5	XPS Analysis	104

4.4	Effect of ESD Deposited CNT on the Tensile Strength of Single CF using Single Fiber Test	106
4.5	Performance of woven CF reinforced epoxy composite laminates reinforced with ESD deposited CNT interlayer	108
4.5.1	The constituent volume fractions	108
4.5.2	Mechanical Properties	109
4.5.2(a)	Tensile Properties	109
4.5.2(b)	Flexural Properties	115
4.5.2(c)	Interlaminar Shear Strength (ILSS)	119
4.5.3	Thermal Conductivity	120
4.5.4	Dielectric Properties	122

CHAPTER FIVE: CONCLUSIONS AND RECOMMENDATIONS

5.1	Conclusions	126
5.2	Recommendations for Future Works	127

	REFERENCES	128
--	-------------------	-----

LIST OF PUBLICATIONS

LIST OF TABLES

		Page
Table 2.1	Sizing agents of TORAYCA fibers (Park, 2018)	12
Table 2.2	Designation of TORAYCA fibers (Park, 2018)	12
Table 2.3	Zeta potential of CNT in different types of solvents	20
Table 2.4	Summary of the tensile properties of the single fiber test on hybrid CF-CNT	46
Table 3.1	Properties of the purchased carbon fiber (Toray Industries Inc. datasheet)	56
Table 3.2	Properties of the purchased MWCNT (SkySpring nanomaterials, Inc. datasheet)	57
Table 3.3	Properties of the purchased NMP (Sigma-Aldrich datasheet)	57
Table 3.4	Properties of the purchased DMF (Sigma-Aldrich datasheet)	58
Table 3.5	Properties of the purchased THF (Sigma-Aldrich datasheet)	58
Table 3.6	Properties of the purchased UV epoxy adhesive (UV 367) (Penchem Technologies Sdn Bhd datasheet)	59
Table 3.7	Properties of the purchased of EpoxAmite 100 (Smooth-On, Inc datasheet)	60
Table 3.8	The chemical composition of EpoxAmite 103 slow (Smooth-On, Inc datasheet)	60
Table 3.9	Properties of the purchased of EpoxAmite 103 slow (Smooth-On, Inc datasheet)	61
Table 3.10	Electrospray deposition processing parameter	64
Table 3.11	Descriptions of the samples	67
Table 4.1	The dipole moment of DMF, NMP and THF (Hesse, 2008)	82
Table 4.2	Stability of suspension in relation to zeta potential (Aobrien, 1990)	83

Table 4.3	Lower wavelength limit of UV transparency for the DMF, NMP and THF based on Burdick & Jackson solvent (Snyder et al., 2012)	86
Table 4.4	Raman intensity of CNT, CF and hybrid CF-CNT	101
Table 4.5	Mass percentages and C/O ratio obtained by XPS on CNT, CF and hybrid CF-CNT	105
Table 4.6	Tensile properties of CF and Hybrid CF-CNT	108
Table 4.7	The fiber, matrix and void volume fractions for the CF/Epoxy and CF-CNT/Epoxy	108
Table 4.8	Density, specific tensile strength and specific tensile modulus of CF/Epoxy and CF-CNT/Epoxy	115

LIST OF FIGURES

	Page	
Figure 2.1	Crystal structure of graphite	10
Figure 2.2	Structural model for carbon fiber during graphitization process (Wu et al., 2012)	11
Figure 2.3	TEM images of carbon filaments (Tibbetts, 1984)	13
Figure 2.4	TEM image of MWCNT with a) five graphitic sheets b) two graphitic sheets and c) seven graphitic sheets (Iijima, 1991)	14
Figure 2.5	TEM image of SWCNT (Iijima and Ichihashi, 1993)	14
Figure 2.6	One-dimensional nanotubes	15
Figure 2.7	The sp^2 orbital hybridization of graphitic carbon (Ebbesen and Hiura, 1995).	15
Figure 2.8	Schematic diagram of graphene layer, and how it can be rolled to form a carbon nanotube (Katsnelson, 2007)	16
Figure 2.9	Graphene as SWCNT and MWCNT structures (Javey and Kong, 2009)	16
Figure 2.10	SEM images of CF surface with a) carbon filament growth and b) CNT growth	22
Figure 2.11	Schematic diagram of CVD process	23
Figure 2.12	SEM image of growth at (a-b) high concentration of catalyst solution (1 M) and (c-d) low concentration of catalyst solution (0.1 M) (Tzeng et al., 2006)	25
Figure 2.13	Schematic diagram of (a) EPD setup and (b) EPD types	29
Figure 2.14	Schematic diagram of (a) continuous EPD process and (b) combining continuous EPD and sizing process	31
Figure 2.15	SEM images of CNT deposited on CF surface (a-b) anodic EPD and (c-d) cathodic EPD (Lee et al., 2011)	35
Figure 2.16	Schematic diagram of ESD setup	37
Figure 2.17	SEM image of hybrid CF-CNT produce via ESD (Li et al., 2016b)	37

Figure 2.18	SEM image of hybrid CF-CNT produced by ESD as a function of deposition time: (a) 2 min and (b) 10 min (Li et al., 2016b)	39
Figure 2.19	Electrospray systems (a) horizontal nozzle setup, (b) reverse nozzle setup and (c) down-facing nozzle setup (Jaworek et al., 2018)	40
Figure 3.1	Chemical structure of oxirane, 2,2'-((1-methylethylidene)bis(4,1-phenyleneoxymethylene))bis-, homopolymer	59
Figure 3.2	Chemical structure of (a) Methylenebis(cyclohexanamine, 4,4'- and (b) Trimethylolpropane polyoxypropylene triamine	61
Figure 3.3	General view of electrospray deposition process	63
Figure 3.4	General view of the VARTM setup	66
Figure 3.5	The shape and dimensions of tensile test specimen	73
Figure 3.6	Schematic of the three point bending short beam shear test jig setup	75
Figure 3.7	(a) Sample dimension for thermal conductivity, (b) Diagram of a thermal conductivity sensor, (c) Experimental setup of sensor and samples	76
Figure 3.8	Experimental setup of sensor and samples for dielectric test	77
Figure 4.1	Digital photographs of CNT dispersed in DMF, NMP and THF solvent. Pictures were taken after (a) sonication, (b) one hour, (c) one day and (d) one week	79
Figure 4.2	Zeta potential of CNT dispersed in different types of solvent	81
Figure 4.3	Chemical structure of DMF, NMP and THF	81
Figure 4.4	UV-Vis spectrum of the CNT after sonication, one hour, one day and one week dispersed in (a) DMF, (b) NMP and (c) THF	85
Figure 4.5	Electrospray modes at different applied voltage of 2 – 20 KV	87
Figure 4.6	SEM images of CNT with magnification of (a) 5,000X and (b) 10,000X	90

Figure 4.7	SEM images of CF with magnification of (a) 5,000X and (b) 10,000X	91
Figure 4.8	SEM images of woven hybrid CF-CNT produced as a function of varying voltage (a-b) 6 kV, (c-d) 10 kV, (e-f) 15 kV and (g-h) 20 kV	92
Figure 4.9	SEM images of woven hybrid CF-CNT produced as a function of deposition time at 15 kV (a-b) 5 min, (c-d) 15 min and (e-f) 30 min	94
Figure 4.10	SEM images of optimized hybrid CF-CNT with magnification of (a) 100,000X, (b) 200,000X, (c) 100,000X and (d) 200,000X.	95
Figure 4.11	HRTEM images of (a) CNT, (b) CF and (c) Hybrid CF-CNT	97
Figure 4.12	XRD pattern of CNT, CF and hybrid CF-CNT	99
Figure 4.13	Raman spectrum of CNT, CF and hybrid CF-CNT	101
Figure 4.14	FTIR spectrum of CNT, CF and hybrid CF-CNT	103
Figure 4.15	XPS wide-scan spectrum of CNT, CF and hybrid CF-CNT	105
Figure 4.16	(002) reflection of XRD, G-band spectrum of Raman spectroscopy, C1s spectrum of XPS and C=C stretching of FTIR of (a) CNT, (b) CF and (c) hybrid CF-CNT	106
Figure 4.17	Tensile stress–strain curves of CF and hybrid CF-CNT	107
Figure 4.18	Tensile stress–strain curves of CF/Epoxy and CF-CNT/Epoxy	110
Figure 4.19	Tensile properties of the CF/Epoxy and CF-CNT/Epoxy (a) tensile strength and (b) tensile modulus	112
Figure 4.20	SEM images of the tensile fracture surfaces of (a, c and e) CF/Epoxy and (b, d and f) CF-CNT/Epoxy.	113
Figure 4.21	Schematic diagram of hybrid CF-CNT fracture or pullout from the epoxy matrix	114
Figure 4.22	Flexural stress–strain curves of CF/Epoxy and CF-CNT/Epoxy	116

Figure 4.23	Flexural properties of the CF/Epoxy and CF-CNT/Epoxy (a) flexural strength and (b) flexural modulus	117
Figure 4.24	SEM images of the flexural fracture surfaces of (a and c) CF/Epoxy and (b and d) CF-CNT/Epoxy	119
Figure 4.25	ILSS of the CF/Epoxy and CF-CNT/Epoxy	120
Figure 4.26	Thermal conductivity of CF/Epoxy and CF-CNT/Epoxy	122
Figure 4.27	Frequency dependence of the dielectric constants of CF/Epoxy and CF-CNT/Epoxy	124
Figure 4.28	Frequency dependence of the dielectric loss of CF/Epoxy and CF-CNT/Epoxy	125

LIST OF ABBREVIATIONS

1D	One-dimensional
3D	Three-dimensional
APS	Aminopropyltriethoxysilane
CF	Carbon fiber
CNF	Carbon nanofiber
CNT	Carbon nanotube
CVD	Chemical vapour deposition
DMF	N,N-Dimethylformamide
DSC	Differential scanning calorimetry
EDX	Energy dispersive X-ray
EPD	Electrophoretic deposition
ESD	Electrospray deposition
FESEM	Field emission scanning electron microscope
FTIR	Fourier transform infrared spectroscopy
HRTEM	High resolution transmission electron microscope
IFSS	Interfacial shear strength
ILSS	Interlaminar shear strength
KBr	Potassium bromide
MWCNT	Multi-walled carbon nanotube
NMP	N-Methyl-2-Pyrrolidone
PEI	Polyethyleneimine
POSS	Polyhedral oligomeric silsesquioxane
THF	Tetrahydrofuran
VARTM	Vacuum assisted resin transfer molding

XPS X-ray Photoelectron Spectroscopy

XRD X-ray diffraction

LIST OF SYMBOLS

%	Percentage
°	Degree
°C	Degree Celsius
Å	Angstrom
Ω	Ohm
σ	stress
ε	Dielectric constant
η	Viscosity
ζ	Zeta potential
λ	Radiation/wavelength
A	Area
A/g	Ampere/gram
cmHg	Centimeter mercury
cPs	Centipoise
D	Debye
eV	Electronvolt
<i>F</i>	Force
F/g	Farad/gram
g	Gram
g/cm ³	Gram/cubic centimeter
g/mol	Gram/mole
GPa	Gigapascal
Hz	Hertz

kV	Kilovolt
L	Length (mm)
MPa	Megapascal
Min	Minute
mm	Millimeter
mV	Millivolt
ml/h	Milliliter/hour
mW/cm^2	Milliwatt/square centimeter
$\mu\text{A}/\text{cm}^2$	Microampere/square centimeter
μm	Micrometer
nm	Nanometer
P	Maximum load
s/cm	Siemens/meter
T	Temperature
V	Volt
v	Speed of particle
V/cm	Volt/centimeter
V/nm	Volt/nanometer
w/w	weight/weight

**TENUNAN GENTIAN KARBON EPOKSI KOMPOSIT LAMINAT
DIPERKUAT DENGAN NANOTIUB KARBON DI ANTARA LAPISAN
MENGUNAKAN KAEDAH PEMENDAPAN SEMBURAN ELEKTRO**

ABSTRAK

Penghibridan tenunan gentian karbon-nanotub karbon mendapat banyak perhatian dari kalangan penyelidik dalam bidang epoksi komposit laminat. Dalam kajian ini, kaedah pemendapan semburan elektro digunakan untuk mendepositkan nanotub karbon pada permukaan tenunan gentian karbon. Pemendapan nanotub karbon pada permukaan tenunan gentian karbon bertujuan untuk meningkatkan kekasaran permukaan tenunan gentian karbon serta hubungan saling pengaruh mekanikal antara tenunan gentian karbon dan matrik epoksi. Untuk kaedah pemendapan semburan elektro, kestabilan nanotub karbon dalam pelarut adalah sangat penting semasa proses pemendapan semburan elektro dan N-metil-2-pirolidon adalah terbukti sesuai untuk penyebaran nanotub karbon kerana kestabilan yang tinggi. Kesan voltan dan masa semburan pemendapan semburan elektro pada morfologi tenunan gentian karbon-nanotub karbon hibrid telah dikaji. Voltan dan masa semburan optimum untuk mendapatkan lapisan nanotub karbon yang homogen dan rata pada permukaan tenunan gentian karbon adalah 15 kV dan 15 minit, masing-masing. Daripada ujian gentian tunggal, kaedah pemendapan semburan elektro didapati selamat tanpa sebarang kemerosotan ketara pada kekuatan tenunan gentian karbon-nanotub karbon hibrid. Epoksi komposit laminat dengan tenunan gentian karbon-nanotub karbon hibrid yang dioptimumkan dan tenunan gentian karbon tanpa didepositkan nanotub karbon kemudiannya dihasilkan dan dibandingkan dari segi sifat mekanikal, terma dan dielektrik. Penilaian menunjukkan gentian karbon-nanotub

karbon hibrid epoksi komposit laminat mempunyai sifat mekanikal, terma dan dielektrik yang lebih tinggi daripada tenunan gentian karbon epoksi komposit laminat. Keputusan menunjukkan bahawa gentian karbon-nanotub karbon hibrid epoksi komposit laminat mampu meningkatkan kekuatan tegangan, modulus tegangan, kekuatan lentur, modulus lentur, kekuatan ricih antara laminar, konduktiviti terma dan pemalar dielektrik masing-masing sebanyak 21 %, 37 %, 19 %, 27 %, 35 % and 22 %, berbanding tenunan gentian karbon epoksi komposit laminat.

**WOVEN CARBON FIBER EPOXY COMPOSITE LAMINATES
REINFORCED WITH CARBON NANOTUBE INTERLAYER USING
ELECTROSPRAY DEPOSITION METHOD**

ABSTRACT

The hybridization of woven carbon fiber-carbon nanotube (CF-CNT) received enormous attention from research communities in the field of epoxy laminates composites. In this study, electrospray deposition (ESD) method was used to deposit carbon nanotube (CNT) on the woven carbon fiber (CF) surface. The deposition of the CNT on the woven CF surface is intended to improve the surface roughness of the woven CF as well as to provide a mechanical interlocking between the woven CF and the epoxy matrix. For ESD method, the stability of the CNT in the solvent is very crucial during the ESD process and N-Methyl-2-Pyrrolidone is proven suitable for dispersing CNT due to high stability. The effect of voltage and spray time of ESD on the morphologies of the woven hybrid CF-CNT has been studied. The optimum voltage and spray time to achieve homogeneous and even CNT coating on the woven CF surface is 15 kV and 15 min, respectively. From single fiber test, the ESD method is found to be safe without any significant degradation on the tensile strength of the woven CF-CNT. The epoxy composite laminates with optimized woven hybrid CF-CNT and woven CF without deposited CNT were then prepared and compared in terms of mechanical, thermal and dielectric properties. The evaluation showed that woven hybrid CF-CNT epoxy composite laminates have greater mechanical, thermal and dielectric properties than woven CF epoxy composite laminates. The results demonstrate that the woven hybrid CF-CNT epoxy composite laminates are capable of improving tensile strength, tensile modulus, flexural strength, flexural modulus,

interlaminar shear strength, thermal conductivity and dielectric constant about 21 %, 37 %, 19 %, 27 %, 25%, 35 % and 22 %, respectively, compared to the woven CF epoxy composite laminates.

CHAPTER ONE

INTRODUCTION

1.1 Background of the Research

CF reinforced epoxy composites exhibit high strength and modulus to weight ratio and broadly used in the aerospace, automobile industries, military and sporting goods. Even though the CF epoxy composite laminates have been widely used in many applications, their potential is still governed by few factors. As is well known, the CF epoxy composite laminates in the form of laminates have poor strength in the direction of through thickness, as no fibers are oriented in the direction of thickness to support transverse load. Thus, CF epoxy composite laminates are vulnerable for the crack to initiate and propagate along the interface. The delamination is one of the frequent failure modes in the laminates composites, which may cause critical reduction in transverse direction strength and stiffness and can lead to catastrophic failure for the whole structure. During manufacturing or service life, the delamination may be introduced by external loading such as tension, static bending, impact loading, cyclic fatigue and compression.

In order for CF epoxy composite laminates to offer better design for advanced components, significant enhancement in the aforementioned properties are necessary. The incorporation of nanofiller, such as carbon nanotubes (CNT) into the matrix of composites has been developed as an efficient method for improving the mechanical and multifunctional properties of CF epoxy composite laminates. The exceptional mechanical and physical properties of CNT have inspired their utilization as additives to enhance the inadequate properties of CF epoxy composite laminates. CNT is one-dimensional with a cylindrical nanostructure of sp^2 hybridized carbon atoms that are densely packed in a honeycomb crystal lattice. CNT has been reported to possess

superior mechanical properties, with Young's modulus of 0.27 - 0.95 TPa and tensile strengths of 11 – 63 GPa (Trojanowicz, 2006). CNT is also expected to offer remarkable performances in areas such as thermal and electrical properties. Thermal and electrical conductivity of CNT is up to 3,000W/mK and 1800 S/cm, respectively (Kausar et al., 2016).

There are two common ways for incorporating CNT into the CF epoxy composite laminates. First, CNT is used as reinforcing fillers in the epoxy matrix of the CF epoxy composite laminates to improve their mechanical properties (Davis et al., 2010; Kim et al., 2011). The challenge of this approach is that the uniform dispersion of CNT in the epoxy matrix is difficult to achieve, especially at high concentrations, due to the dramatically increased viscosity of the resin. Highly viscous resin with agglomerated CNT is very difficult to process and always leads to poor performance of CF epoxy composite laminates. In addition, the direct incorporation of the CNT into the epoxy matrix is less effective in improving the interfacial bonding between the CF and epoxy matrix.

Another way is to grow or deposit CNT directly onto CF surface to form a hierarchical reinforcement. Several methods were successfully developed hierarchical hybrid carbon fiber-carbon nanotube (CF-CNT) such as chemical vapour deposition (CVD), electrophoretic deposition (EPD), chemical functionalization and electrospray deposition (ESD) (Susi et al., 2008; Li et al., 2013; Deng et al., 2015; Li et al., 2016). The main motivation for producing hybrid CF-CNT is to improve the interface properties and minimize the existing limitations associated with the matrix dominated properties. For example, CNT could offer interlaminar reinforcement, thus improving resistance to delamination and through thickness properties, without sacrificing the performance of longitudinal direction. In addition, the hybridization of CF with CNT