

**INVESTIGATION OF POTENTIAL WEATHERED
REE-BEARING GRANITOID CRUST FROM
DINDING DISTRICT OF WESTERN TIN BELT,
PENINSULAR MALAYSIA**

ALI YARAGHI

UNIVERSITI SAINS MALAYSIA

2020

**INVESTIGATION OF POTENTIAL WEATHERED
REE-BEARING GRANITOID CRUST FROM
DINDING DISTRICT OF WESTERN TIN BELT,
PENINSULAR MALAYSIA**

by

ALI YARAGHI

**Thesis submitted in fulfilment of the
requirements for the degree of
Doctor of Philosophy**

February 2020

ACKNOWLEDGEMENT

In God's Most Beneficent Name

First and foremost, I would like to express my heartfelt thanks and deepest gratitude to Associated Professor Dr. Kamar Shah Ariffin, my respectable supervisor for encouraging and supporting me with patience and for his invaluable counselling and advice from the very beginning stages of this research.

My boundless gratefulness is also due to my co-supervisor, Dr. Norlia Baharun for her precious comments. Their benevolent nature and moral support have been pivotal in motivating me to complete this work.

My acknowledgements are due also to the Dean of our school, Assoc. Prof. Ir. Dr. Syed Fuad B. Saiyid Hashim, and all the lecturers and staff members at the School of Materials and Mineral Resources Engineering (SMMRE) for their humanitarian support and kind cooperation during my academic PhD journey. Science and Engineering Research Centre (SERC), USM is acknowledged for the great help on samples ICP-MS analysis.

I am heartily thankful to my dear family for their endless love and heart-warming support and encouragement without whose support finishing this thesis would have been impossible.

TABLE OF CONTENTS

	Page
ACKNOWLEDGEMENT	ii
TABLE OF CONTENTS	iii
LIST OF TABLES	viii
LIST OF FIGURES	x
LIST OF SYMBOLS	xiv
LIST OF ABBREVIATIONS	xv
ABSTRAK	xvii
ABSTRACT	xix
CHAPTER 1 INTRODUCTION	1
1.1 Rare Earth Elements (REE)s	1
1.2 Research background	3
1.2.1 Malaysian REE resources potential in weathered granitic rocks.....	3
1.3 Location of Study Area	8
1.4 Problem statements	8
1.5 Research objectives	9
1.6 Scope of the study	10
1.7 The thesis outlines	10
CHAPTER 2 LITERATURE REVIEW	12
2.1 Introduction	12
2.2 REE history and definition	12
2.3 REE occurrences and deposits	12
2.3.1 REE igneous deposits.....	13

2.3.2	REE hydrothermal deposits	16
2.3.3	REE ion-Adsorption deposits.....	16
2.3.4	REE placer deposits	17
2.3.5	Other deposits.....	17
2.4	REEs Application.....	19
2.5	Granite significant classifications	19
2.5.1	IUGS classification	20
2.5.2	S-I-A-M classification.....	21
2.5.3	ASI classification	22
2.5.4	Magnetite or ilmenite-series classification.....	23
2.6	Regional geological setting of the area	25
2.6.1	South-East Asian tin belt.....	26
2.6.2	Plutonic rocks of Peninsular Malaysia.....	27
2.7	REE Mineralogy.....	28
2.7.1	REE minerals variation based on their crystal chemistry	28
2.7.1(a)	REE minerals with Zircon structure	33
2.7.1(b)	REE minerals with Monazite structure	34
2.7.2	REE minerals variation based on Evolution of Earth.....	34
2.8	Geochemistry of REEs	36
2.8.1	REEs geochemical behaviour	37
2.8.2	REE accumulation in the earth.....	39
2.8.2(a)	Whole earth REE concentration	39
2.8.2(b)	Mantle REE concentration	39
2.8.2(c)	Earth crust REE concentration	41
2.8.3	REE migration to fluids	44
2.8.3(a)	REEs complexation	45

2.8.3(b)	REE-contain minerals weathering.....	45
2.9	REE Ion-Adsorption deposits (IAD)s	46
2.9.1	Main features of Ion-Adsorption deposits.....	46
2.9.2	Parent granites REE geochemistry.....	49
2.9.3	REE minerals weathering.....	50
2.9.4	REE mobility and fractionation during weathering	51
2.9.5	REEs complexing.....	55
2.9.6	REEs adsorption by clays	56
2.10	Cation Exchange Capacity (CEC).....	57
CHAPTER 3 RESEARCH METHODOLOGY		60
3.1	Introduction.....	60
3.1.1	General flow chart of research activities.....	61
3.1.2	Scope and method of REE investigation.....	61
3.2	Field investigation and geological sampling.....	63
3.3	Sample preparation.....	65
3.4	Characterization	65
3.4.1	Petrographic Analysis	65
3.4.2	X-ray powder diffraction (XRD) analysis method.....	66
3.4.2(a)	Sample preparation with Ethylene-Glycol (EG)	68
3.4.3	Fourier-Transform Infrared (FTIR) spectroscopy	69
3.4.4	X-ray Fluorescence (XRF) spectroscopy	70
3.4.4(a)	Loss on Ignition (LOI) analysis.....	70
3.4.5	Scanning Electron Microscopy with Energy Dispersive X-ray (SEM-EDX) spectroscopy.....	71
3.4.6	Inductively coupled plasma-mass spectrometry (ICP-MS)	73
3.4.7	Cation Exchange Capacity (CEC) determination.....	75

3.4.7(a)	Ammonium Acetate method	75
3.4.7(b)	Methylene Blue Dye test	77
3.5	Trial leaching experiments	78
CHAPTER 4 RESULTS AND DISCUSSIONS		80
4.1	Introduction	80
4.2	Field investigation and geological sampling	80
4.3	Petrology and mineralogical study	88
4.3.1	Petrographic study of parent rocks	89
4.3.2	X-ray diffractometry studies of the samples	94
4.3.3	Fourier Transform Infrared (FTIR) spectroscopy analysis	97
4.3.4	Weathered crust profile studies using Scanning Electron Microscopy (SEM)	102
4.4	Mineral chemistry of granite from Lumut and Telok Murok sites	107
4.4.1	Lumut site	107
4.4.2	Telok Murok site	112
4.5	Whole-Rock and REE geochemistry of the granite weathered crust and the parent rocks	117
4.5.1	Lumut site	117
4.5.2	Telok Murok site	121
4.6	Cation Exchange Capacity (CEC) determination	125
4.7	Trial leaching experiments	126
4.8	Discussions	133
4.8.1	Alteration of rock-forming minerals in progressive weathering ..	136
4.8.2	Relationship between clay minerals and REEs accumulation	137
CHAPTER 5 CONCLUSION AND FUTURE RECOMMENDATIONS....		139
5.1	Conclusion	139
5.2	Recommendations for Future Research	142

REFERENCES..... 143

APPENDIX A: CODING, COORDINATION AND DETAILED
DESCRIPTION OF SAMPLES FROM LUMUT AND TELOK
MUROK SITES

APPENDIX B: CIPW-NORM CALCULATION RESULTS OF PARENT
ROCK SAMPLES a) LUMUT (LU-FR) AND b) TELOK
MUROK (TM-247FR)

LIST OF PUBLICATION

LIST OF TABLES

		Page
Table 2.1	Significant REE deposits categorization; modified <i>after</i> (Hoshino et al. 2016).	15
Table 2.2	Application of REEs in some important industries; Modified from (Hoshino et al., 2016).....	20
Table 2.3	S- type, I-type, A-type and M-type granitoids specifications; Modified <i>after</i> (Chappell and White, 2001; Ishihara, 1981; Winter, 2001)	24
Table 2.4	Significant REE minerals specifications.....	29
Table 2.5	Various REE minerals isostructures; modified <i>after</i> (Anthony et al., 1995, 1997, 2003)	33
Table 2.6	Mineral evolution levels and stages; modified <i>after</i> (Hazen et al., 2008)	36
Table 4.1	Coding, image and detailed description of samples from Lumut and Telok Murok sites	82
Table 4.2	Normative weight of major minerals in LU and TM sites fresh rocks.....	89
Table 4.3	FTIR frequencies and assignments of weathered crust samples from Lumut site.....	98
Table 4.4	FTIR frequencies and assignments of weathered crust samples from Telok Murok site	99
Table 4.5	FTIR frequencies and assignments of parent rocks samples	101
Table 4.6	Scanning electron photomicrographs of Lumut site samples	103
Table 4.7	Scanning electron photomicrographs of Telok Murok site samples	105

Table 4.8	Whole-rock major, trace and rare earth elements contents of Lumut weathered crust of granite and related parent rock.....	119
Table 4.9	Whole-rock major, trace and rare earth elements contents of Telok Murok weathered crust of granite and related parent rock	123
Table 4.10	Standard CEC of important clay minerals	125
Table 4.11	CEC determination using ammonium acetate method and methylene blue dye test.....	126
Table 4.12	pH of the solution after 20 minutes agitation.....	127
Table 4.13	REE content of Lumut representative samples (Bulk (B) and Orientated (O)) after leaching time of 0.5 to 16 hours. (ppm).....	129
Table 4.14	REE content of Telok Murok representative samples (Bulk (B) and Orientated (O)) after leaching time of 0.5 to 16 hours. (ppm).....	130
Table 5.1	Summary of research objectives, corresponding characterization techniques and the results for LU and TM sites	139
Table 5.2	Summary of chemical composition analysis using XRF and ICP-MS for LU and TM fresh rocks	140

LIST OF FIGURES

		Page
Figure 1.1	Simplified geological map of the Peninsular Malaysia; modified <i>after</i> (Hutchison and Tan, 2009).....	5
Figure 1.2	LREE, HREE and Y concentration of sampled areas of Tampin and Bukit Tinggi <i>after</i> (Ariffin et al., 2010; Kurumi, 2010a).....	6
Figure 1.3	LREE, HREE and Y concentration of sampled areas of Lumut, Taiping and Baling <i>after</i> (Ariffin et al., 2010; Kurumi, 2010a)	7
Figure 2.1	Global variety of REEs production in 2014; modified from (Roskillinteractive, 2018)).	18
Figure 2.2	QAPF diagram used for IUGS categorization of plutonic rocks; modified <i>after</i> (Le Bas and Streckeisen, 1991).....	22
Figure 2.3	Peninsular Malaysia and South East Asian great islands location in Sunda Shelf; modified <i>after</i> (Hutchison, 2007).....	25
Figure 2.4	Granitic provinces map of South-East Asian tin belts; modified <i>after</i> (Cobbing et al., 1986; Imai et al., 2013).....	26
Figure 2.5	REE partition coefficients in magma minerals; modified <i>after</i> (White, 2013)	38
Figure 2.6	Major sites of magma generation modified <i>after</i> (Hoshino et al., 2016)	40
Figure 2.7	MORB and OIB REE chondrite; modified <i>after</i> (White, 2013).....	42
Figure 2.8	Upper, middle and lower continental crust REE chondrite patterns; modified <i>after</i> (Rudnick and Gao, 2013).....	43
Figure 2.9	Ion-adsorption REE projects around the world based on climate variation; modified <i>after</i> (Hoshino et al., 2016; Peel et al., 2006)). ..	48

Figure 2.10	Weathering crust of granite representation profile; modified <i>after</i> (Hoshino et al., 2016).....	53
Figure 2.11	REE ion-adsorption orebody model; modified <i>after</i> (Hoshino et al., 2016)	54
Figure 3.1	Study flowchart for weathered crust of granite associated with REE	62
Figure 3.2	Maps showing sampling location in the study area; Modified <i>after</i> (Ariffin et al., 2010) and Google Earth Pro software.....	64
Figure 3.3	XRD analysis sample preparation, a) bulk sample, b) oriented sample before precipitation, c) oriented sample after precipitation and d) oriented sample after mounting; Dept. of Earth Resources Engineering, Kyushu University, Japan.....	68
Figure 3.4	Parent rocks and horizon -C samples prepared for OM & SEM-EDX analysis with arrow pointer.....	72
Figure 3.5	Approximate detection capabilities of the ICP-MS (Perkin Elmer, 2019)	74
Figure 3.6	Apparatus setup for distillation process for CEC determination	76
Figure 3.7	End-point of titration process color changed from blue to pale green.....	77
Figure 4.1	Geological map of Dinding (Manjung) district showing sampling points, Perak, Malaysia	81
Figure 4.2	Telok Murok (TM) sampled profiles and representative samples appearance from various horizons	85
Figure 4.3	Lumut (LU) sampled profiles and representative samples appearance from various horizons	87
Figure 4.4	QAP diagram for classification of plutonic rocks indicating Lumut and Telok Murok parent rock samples; modified <i>after</i> (Le Bas and Streckeisen, 1991).....	90

Figure 4.5	Geochemical characterization of the parent rocks. (A) Total alkalis vs. silica diagram and (B) The Shand Index diagram (A/NK vs. A/CNK) showing both parent rocks are peraluminous granite	91
Figure 4.6	Photomicrograph (40X-100X) of Lumut fresh rock (LU-FR) with the evidence of alteration and accessory minerals inclusions.....	92
Figure 4.7	Photomicrograph (40X-100X) of Telok Murok site fresh rock (TM-247FR) with the evidence of alteration and accessory minerals inclusions.....	93
Figure 4.8	X-ray diffraction pattern of Lumut granite and its weathered crust ..	95
Figure 4.9	X-ray diffraction pattern of Telok Murok granite and its weathered crust.....	96
Figure 4.10	(a) Photomicrographs taken under an optical microscope with burning texture; (b) and (c) backscattered electron by SEM from REE-bearing minerals of Lumut parent rock consisting of (b) zircon (c) with U/Th substitution (allanite).	109
Figure 4.11	(a) Photomicrographs taken under an optical microscope presents burning texture and (b and c) backscattered electron by SEM from REE-bearing minerals of Lumut parent rock consisting of (b) aluminosilicate mineral (titanite) and (c) apatite.	110
Figure 4.12	(a) Photomicrographs taken under an optical microscope showing burning feature resulted by radioactivity and (b and c) backscattered electron by SEM presenting (b) xenotime and (c) monazite.....	111
Figure 4.13	(a) Photomicrographs taken under an optical microscope and (b) backscattered electron by a scanning electron microscope of REE-bearing minerals of Telok Murok parent rock consist of apatite.....	113
Figure 4.14	(a) Photomicrographs taken under an optical microscope showing burning feature and (b and c) backscattered electron by a scanning	

	electron microscopes of REE-bearing minerals of Telok Murok parent rock consisting of (b) monazite and (c) zircon.	114
Figure 4.15	(a) Photomicrograph taken under an optical microscope (polished section) and (b) backscattered electron by a scanning electron microscopes of accessory minerals of Telok Murok parent rock consisting of (b) ilmenite.	115
Figure 4.16	(a) Photomicrographs taken under an optical microscope (polished section) and (b and c) backscattered electron by a scanning electron microscopes of REE-bearing minerals of Telok Murok parent rock consisting of (b) zircon and (c) monazite.	116
Figure 4.17	Chondrite-normalized REE diagram of weathered crust of granite and related parent rock from Lumut site (values of chondrite are from (Sun and McDonough, 2008)).....	120
Figure 4.18	Chondrite-normalized REE diagram of weathered crust of granite and related parent rock from Telok Murok site (values of chondrite are from (Sun and McDonough, 2008)).....	124
Figure 4.19	Influence of time on rare earth extraction levels of Lumut site representative samples.	131
Figure 4.20	Influence of time on rare earth extraction levels of Telok Murok site representative samples.....	132
Figure 4.21	LREE, HREE and Y concentration of weathered crusts at LU site.	134
Figure 4.22	LREE, HREE and Y concentration of weathered crusts at TM site	135
Figure 4.23	TRY (TRE+Y) concentration vs. depth in LU and TM site bulk samples.....	138

LIST OF SYMBOLS

°C	Degree Celsius or centigrade
Å	Angstrom
µm	Micrometre
LU	Lumut site
TM	Telok Murok site
cm	Centimetre
mm	Millimetre
Km	Kilometre
gr	Gram
mL	Millilitre
M	Molar
V	Volume
Ma	Mega Annum
Ga	Gallium

LIST OF ABBREVIATIONS

REE	Rare Earth Element
LREE	Light Rare Earth Element
HREE	Heavy Rare Earth Element
REO	Rare Earth Oxide
IAD	Ion-adsorption Deposit
Qtz	Quartz
Apt	Apatite
Mon	Monazite
Alla	Allanite
Zr	Zircon
Bt	Biotite group minerals
Chl	Chlorite
Plg	Plagioclase
kfs	K-feldspar
UTM	Universal Transverse Mercator coordinate system
IOA	Iron Oxide–Apatite deposits
IUPAC	International Union of Pure and Applied Chemistry
SIAM	Sedimentary-Igneous-Anorogenic-Mantle
IUGS	International Union of Geological Science
ppm	Part Per Million
wt. %	weight percentage
f	Fugacity
PC	Partitioning Coefficient
ASI	Aluminium Saturation Index
CIA	Chemical Index of Alteration
MALI	Modified Alkali Lime Index

XRF	X-ray Fluorescence Spectroscopy
XRD	X-ray diffraction
OM	Optical Microscopy
SEM-EDX	Scanning electron microscope - energy-dispersive X-ray
FTIR	Fourier Transform Infrared
ICP-MS	Inductively Coupled Plasma Mass Spectrometry
CEC	Cation Exchange Capacity
MORB	Mid-Oceanic Ridge Basalt
OIB	Oceanic Island Basalts
IMA	International Mineralogical Association
GOE	Great Oxidation Event
PZC	Point of Zero Charge
GPa	Giga Pascal
EMPA	Electron Microprobe Analysis
LA-ICP-MS	Laser Ablation Inductively Coupled Plasma Mass Spectrometry
ASTM	American Society for Testing and Materials
CI	Carbonaceous Ivuna chondrite
LOI	Loss on Ignition
kgf	Kilogram Force
IDL	Instrumental Detection Limit
EG	Ethylene-Glycol
HDD	Hard Disc Drive
Dep.	Department
CNMMN	Commission on New Minerals and Mineral Names
SI	International System of units
SERC	Science and Engineering Research Centre
SMMRE	School of Materials and Mineral Resources Engineering
IPS	Institute of Postgraduate Studies
USM	Universiti Sains Malaysia

**KAJIAN POTENSI GRANIT TERLULUHAWA BAGI UNSUR NADIR
BUMI (REE) DARI DAERAH DINDING, JALUR TIMAH BARAT
SEMENANJUNG MALAYSIA**

ABSTRAK

Penyelidikan strategik ini menafsirkan penerokaan hijau dan mampan unsur nadir bumi (REE) endapan tanah jenis penjerapan ion dengan isu radioaktif minimum atau bebas di beberapa kawasan barat Semenanjung Malaysia. Kajian pencirian intensif dijalankan terhadap dua set sampel dari daerah Dinding yang terletak di bahagian barat jalur granit timah Malaysia. Memahami ciri-ciri dan perlakuan geokimia REE di kalangan granitoid terluluhawa serta kebole proses larutlesap adalah objektif utama kajian ini. Kajian ini dijalankan berdasarkan maklumat lapangan dan kajian teknik mikroskopik, XRD, Spectroscopy FTIR, SEM-EDX, XRF, ICP-MS, penentuan CEC dan kebole larutlesap REE yang dihoskan oleh tanah. Kajian petrografi dan analisis geokimia menunjukkan granitoid di tapak Lumut (LU) dan Telok Murok (TM) adalah siri ilmenit, terutamanya peraluminous, jenis-S yang diklasifikasikan sebagai syeno-granit dan monzo-granit, masing-masing dengan k-feldspar, kuarza, plagioklas dan mika sebagai mineral utama. Apatit, monazit, zirkon, allanit, titanit dan ilmenit adalah mineral aksesori utama di tapak LU manakala tapak TM mengandungi terutamanya zirkon, apatit dan allanit. Analisis XRD menunjukkan kehadiran kumpulan tanah liat kaolin dan smektite, manakala phlogopite merupakan mika lazim dalam granit induk. Di kedua-dua lokasi, pengurangan kandungan REE+Y (REY) di horizon A agak ketara, manakala REY meningkat di horizon B dan / atau C. Kandungan maksimum REY boleh setinggi 3500 ppm di horizon B2 dan / atau C dari analisis ICP-MS. Jumlah kandungan

REE (TRE) bagi lempung terluluhawa adalah agak tinggi secara relative berbanding dengan batuan induk (3 hingga 7 kali), pada kedua-dua lokasi di horizon B dan C. Gambarajah normilasi konderit menunjukkan kecenderungan Ce menurun dari anomali positif kepada negatif dengan pengkayaan LREE di kedua-dua lokasi. Walaubagaimanapun, jisim keseimbangan komponen mineral REE di antara setiap horizon di kedua-dua tapak adalah berbeza. Dalam eksperimen pelarutlesapan kelompok, kecekapan pengekstrakan TRE adalah sebanyak ~ 70% - 90% bagi kedua-dua tapak manakala kadar pengekstrakan yang lebih rendah sebanyak 50-80% diperolehi bagi HREEs.

**INVESTIGATION OF POTENTIAL WEATHERED REE-BEARING
GRANITOID CRUST FROM DINDING DISTRICT OF WESTERN TIN BELT,
PENINSULAR MALAYSIA**

ABSTRACT

This research interpreted a green and sustainable exploration strategy of ion-adsorption type REE clay potential deposits with minimum or free radioactive issues in some prone districts of western Peninsula Malaysia. An intensive characterization study was conducted on two sets of samples from Dinding district located within the western part of Malaysian tin granite belt. Understanding REEs characterization and geochemical behaviour among weathered crusts of granitoids as well as their leachability were the main objectives of this study. The study was conducted based on the field and microscopic investigations, XRD, FTIR Spectroscopy, SEM-EDX, XRF, ICP-MS, CEC determination and batch leaching of clay hosted REEs. Petrographical study and geochemical analysis showed granitoids in Lumut (LU) and Telok Murok (TM) sites were ilmenite-series, mainly peraluminous, S-type which were classified into syeno-granite and monzo-granite, respectively with k-feldspar, quartz, plagioclase and mica group as major minerals. Apatite, monazite, zircon, allanite, titanite and ilmenite were accessory minerals in LU site whilst, TM site was indicated by zircon, apatite and allanite. XRD analysis showed the presence of kaolin and smectite rich clay groups, whilst phlogopite was common mica in parent granites. In both sites, depletion of REE+Y (REY) content in horizon A was considerably apparent, whilst REY enriched in horizon B and/or C. The maximum content of REY could be as high as 3500 ppm in horizon B2 and /or C analyzed by ICP-MS. Total REE content (TRE) of the weathered

crust is relatively elevated compared to the parent rocks (3 to 7 times), in horizon B and C of both sites. The chondrite normalized diagrams showed a downward tendency of positive to negative Ce anomaly with LREE enrichment in both sites. However, the mass balance of REE mineral components between each horizon in both sites are different. In batch leaching experiments, TRE extraction levels of ~70% ~ 90% for both sites were achieved with relatively lower extraction of 50-80% for HREEs.

CHAPTER 1

INTRODUCTION

1.1 Rare Earth Elements (REE)s

Rare earth elements (REEs) stand for the set of seventeen elements including fifteen lanthanides: lanthanum (La), cerium (Ce), praseodymium (Pr), neodymium (Nd), promethium (Pm), samarium (Sm), europium (Eu), gadolinium (Gd), terbium (Tb), dysprosium (Dy), holmium (Ho), erbium (Er), thulium (Tm), ytterbium (Yb), lutetium (Lu) along with yttrium (Y) and scandium (Sc) (Meija et al., 2016; Xiao et al., 2016). They are normally grouped depending on the atomic number, into “light” rare earth elements (LREE) - La, Ce, Pr, Nd, and into “middle and heavy” (HREE) - Sm, Eu, Gd, Tb, Dy, Ho, Er, Tm, Yb, Lu. Notwithstanding their name, REEs - except for the radioactive Pr – are relatively abundant in Earth’s crust, with cerium being the 25th most abundant element at 68 parts per million (ppm), more abundant than copper. Even, the two least abundant REE (Tm, Lu) are nearly 200 times more common than gold. Conversely, because of their very similar geochemical properties, REEs are typically very difficult to be separated from each other (Haxel et al., 2002).

Geologically, excluding continental rifts which are the host of carbonatite and kimberlites (Hoshino et al., 2016), it was proven that REEs enriched in REE-bearing minerals of igneous rocks such as apatite, allanite, monazite, titanite, xenotime and etc. in the lower mantle during magmatic differentiation (Castor and Hedrick, 2006). Generally, REEs deposits divide up according to their mineralogy and geneses into two types of primary deposits associated with igneous and hydrothermal activities and secondary deposits assembled by sedimentary processes and weathering (Lusty and

Walters, 2010). Two significant types of secondary deposits are the placer and ion-adsorption clays deposits. The latter which called “regolith-hosted REEs” is originated from high REE content plutonic or volcanic rocks weathering process resulted in accumulation of REEs in igneous weathering profiles (Hoshino et al., 2016). Ion-adsorption clay deposits consider being the host of more than 80% of middle and heavy REEs (Hu et al., 2017).

However, Koppen-Geiger climate classification suggested that temperate and tropical sites are potential zones for weathered granite or ion-adsorption clay type REE resources, thus promoting of intensive chemical weathering and breakdown of REE-bearing minerals by such climate conditions (Peel et al., 2006; Sanematsu and Watanabe, 2016). Malaysia with the wide distribution of S/I-type granite and annual rainfall of 2500 ml, has a high potential in the occurrence of this type of deposits.

Thailand-Malaysia-Western Indonesia has been known as the Southeast Asian tin-granite belt, a major metallogenic province of Sn deposits associated with Ilmenite, S and/or I-type series of granitic rocks (Ishihara, 1981, 1998; Chappell and White, 2001; Imai et al., 2013;). Three granitic belts to be exact “Eastern belt” with a high portion of I-type granites, “Central belt” with a high portion of S-type granites and “Western belt” with a mixture of I and S-type granites were indicated in that region (Figure 1.1). A line parallel to Bentong-Raub closure considered to be the separator of the Western and Eastern Malaysian granite (Metcalf, 2013) which is presented in Figure 1.1.

Geochemically, vertical fluctuation of REE grade among profile is utilized to study of REE behaviour in granitic weathering profiles and yield an evaluation of geochemical mechanisms for REE fractionation and mobilization.

This research reports the first intensive study on characteristics, whole-rock geochemistry and mineral chemistry of REEs associated with weathered crust of western Malaysian granite belt (Dinding granite) and their parent rocks.

1.2 Research background

Malaysia already has a long experience in the upstream REE industry, used to be a producer of REE minerals for several decades from alluvial tin granite mining by-product in Kinta Valley (5% of world production in 1993). Malaysian xenotime used to be the main source of yttrium before 1988 (The academy of Science of Malaysia and The National Professors' Council, 2011). Xenotime, monazite, zircon, ilmenite and struverite were produced as the by-product of tin-mining in Malaysia for several decades. Ti minerals were subjected to further processing to produce TiO₂, meanwhile the efforts to REE extraction from monazite and other heavy minerals was hampered by strong presence of Th/U in the minerals (Kamar Shah Ariffin, 2011).

The country also has the experience of being involved in midstream chemical processing of REE minerals to produce REE compounds.

1.2.1 Malaysian REE Resources potential in weathered granitic rocks

South East Asian weathered granitic crusts located in the countries such as Vietnam, Thailand, Laos, Indonesia and Malaysia were subjected to investigate mostly after 2009 under ASEAN Universities Network (AUN) program leaded by Kyushu University, Japan. Previously, no intensive exploration project has been reported on Malaysian “weathered granitic crust associated with REE” potential.