

**CO₂ REMOVAL USING POLYVINYLIDENE
FLUORIDE MIXED MATRIX MEMBRANE IN
MEMBRANE GAS ABSORPTION**

NOR AINI AHMAD

UNIVERSITI SAINS MALAYSIA

2019

**CO₂ REMOVAL USING POLYVINYLIDENE
FLUORIDE MIXED MATRIX MEMBRANE IN
MEMBRANE GAS ABSORPTION**

by

NOR AINI AHMAD

**Thesis submitted in fulfilment of the requirements
for Doctor of Philosophy**

JUNE 2019

ACKNOWLEDGEMENT

First and foremost, a great thankul to Allah SWT for blessing, opportunity, strength and patient in finishing my PhD research in USM Engineering Campus. After facing challenges, hard works and trainings; this work is ready to be submitted to USM IPS. Special thanks to my parents (Ahmad Wali and Hjh Salmah binti Hj Majid) and family members (Maria, Noridah, Nor Harmin, Yuslaila, Mulianis, Soleha and others) for their help, support and share the sweet and sour in these years.

Apart from my family, a very special gratitude goes out to Assoc. Prof. Ir. Dr. Leo Choe Peng as main supervisor and Prof Dr. Abdul Latif Ahmad as co-supervisor since my master degree until PhD research from 2011-2019. With their great supports in term of technical and motivations; finally we complete this work together. Besides that, I would like to acknowledge the Ministry of Higher Education Malaysia (MOHE) for providing MyPhD scholarship and research grants to support my PhD research. Aslo, to all USM staffs for technical assitance and admistration.

Besides USM and MOHE, great thanks Prof Kang Li's research group and Imperial College London for providing equipment and facilities to complete the collaborative works in 2016 at Department of Chemical Engineering. Special thanks to postdocs (Dr Bo Wang, Dr Xinlei), Izwanne, Fairuz Rabuni, Yunsi Lucy Chi, Farrah Diana, Nasrul Hadi, Syifa and Chris Wang for their help in Imperial College London. All Beumont House's roomates and dormmates in Bay's Water, London.

Furthermore thanks to my friends in USM; Naimah, Melvin, Haziyana, Usman, Hani, Wani, Atiyah, Aishah, Siva and others. Without them, my life in USM is boring and lonely. Last but not least, thanks to Excellent Generation (EG) Learning

management for allowing me to gain some experiences and skills through teaching and management. Also, to everyone who is not listed and others that I missed to list, thank you. May Allah bless and rewards them.

Nor Aini Ahmad

April 2019

TABLE OF CONTENTS

ACKNOWLEDGEMENT	ii
TABLE OF CONTENTS	iv
LIST OF TABLES	x
LIST OF FIGURES	xii
LIST OF PLATES	xvii
LIST OF SYMBOLS	xvii
LIST OF ABBREVIATIONS	xxiii
ABSTRAK	xxi
ABSTRACT	xxiii
CHAPTER 1 INTRODUCTION	1
1.1 Carbon Dioxide (CO ₂) Emission	1
1.2 CO ₂ Capture Technologies	4
1.3 Problem Statement	8
1.4 Research Objectives	10
1.5 Scope of Study	11
1.6 Organization of Thesis	13
CHAPTER 2 LITERATURE REVIEW	15
2.1 Membranes for Membrane Gas Absorption_	15
2.2 Polymers Blending	17
2.2.1 Blending with surface modifying macromolecule (SMM)	19
2.2.2 Blending with hydrophobic polymer	20
2.2.3 Polybenzimidazole (PBI) as copolymer	21
2.3 Inorganic Blending	23
2.3.1 Porous inorganic particles	26
2.3.2 Nonporous inorganic particles	28
2.3.3 Organic–inorganic particles	29

2.4	Post Modification of Membrane	32
2.4.1	Membrane grafting using organosilane	32
2.4.2	Polymer coating	36
2.4.3	Plasma treatment	37
2.5	Membrane Wetting in Membrane Gas Absorption	39
2.5.1	Membrane properties affecting membrane wetting	41
2.5.2	Absorbent properties affecting membrane wetting	42
2.5.3	Operating conditions affecting membrane wetting	44
2.6	CO ₂ Mass Transfer in Membrane Matrix	45
2.7	Research Gap in MGA	50
	CHAPTER 3 METHODOLOGY	51
3.1	Overview of Methodology	51
3.2	Materials and Chemicals	54
3.3	Polyvinylidene Fluoride (PVDF) Membrane Blended with Varied PBI Loadings	56
3.3.1	Preparation of PVDF membrane blended with varied PBI loadings	56
3.3.2	Characterizations of PVDF membrane blended with varied PBI loadings	58
3.3.2 (a)	Water contact angle to determine surface hydrophobicity	58
3.3.2 (b)	Membrane structure	58
3.3.2 (c)	Membrane pore size measurement	58
3.3.2 (d)	Polymer thermal transition behavior	59
3.3.3	Performance test of PVDF membrane blended with varied PBI loadings	60
3.4	PVDF Membrane Blended with SAPO-34 Zeolite	62
3.4.1	Preparation of modified and unmodified SAPO-34 zeolite particles	62

3.4.2	Preparation of PVDF membrane blended with SAPO-34 zeolite	63
3.4.3	Characterizations of PVDF membrane blended with SAPO-34 zeolite	64
3.4.3 (a)	Water contact angle to determine surface hydrophobicity	64
3.4.3 (b)	Surface roughness measurement	64
3.4.3 (c)	Membrane structure	65
3.4.3 (d)	Membrane porosity and thickness measurement	65
3.4.3 (e)	Membrane pore size measurement	66
3.4.3 (f)	Chemical properties analysis	66
3.4.4	Performance test of PVDF membrane blended with SAPO-34 zeolite	67
3.5	PVDF Membrane Blended with Polyhedral Oligomeric Silsesquioxane (POSS)	67
3.5.1	Characterizations of PVDF membrane blended with POSS	69
3.5.1 (a)	Water contact angle to determine surface hydrophobicity	69
3.5.1 (b)	Surface roughness measurement	69
3.5.1 (c)	Membrane structure and chemical elemental analysis	69
3.5.1 (d)	Membrane pore size measurement	69
3.5.1 (e)	Membrane porosity and thickness measurement	70
3.5.1 (f)	CO ₂ adsorption affinity	70
3.5.1 (g)	Chemical properties analysis	71
3.5.2	Performance test of PVDF membrane blended with POSS	71
3.6	PVDF/SAPO-34 Mixed Matrix Membrane (MMM) with Post Silane Modification	71
3.6.1	Preparation of PVDF/SAPO-34 mixed matrix membrane with post silane modification	71

3.6.2	Characterizations of PVDF/SAPO-34 mixed matrix membrane with post silane modification	72
3.6.2 (a)	Water contact angle to determine surface hydrophobicity	72
3.6.2 (b)	Surface roughness measurement	72
3.6.2 (c)	Membrane pore size measurement and liquid entry pressure (LEP)	73
3.6.2 (d)	Membrane structure	73
3.6.2 (e)	Chemical properties analysis	73
3.6.2 (f)	Membrane porosity and thickness measurement	73
3.6.3	Performance test of PVDF/SAPO-34 mixed matrix membrane with post silane modification	74
3.6.4	Amine wetting evaluation	75
3.7	PVDF/SAPO-34 Hollow Fiber Membranes for Membrane Gas Absorption	75
3.7.1	Preparation of PVDF/SAPO-34 hollow fiber membranes	75
3.7.2	Characterizations of PVDF/SAPO-34 hollow fiber membranes	77
3.7.2 (a)	Membrane structure	77
3.7.2 (b)	Membrane porosity and thickness measurement	77
3.7.2 (c)	Water contact angle to determine surface hydrophobicity	77
3.7.2 (d)	Membrane pore size measurement and liquid entry pressure (LEP)	78
3.7.2 (e)	Surface roughness measurement	78
3.7.2 (f)	Chemical properties analysis	78
3.7.2 (g)	Polymer thermal transition behavior	79
3.7.3	Performance test of PVDF/SAPO-34 hollow fiber membranes	79

3.7.4	Mass transfer study of PVDF/SAPO-34 hollow fiber membranes for mixed gas study	82
3.7.5	Membrane wetting and swelling on PVDF/SAPO-34 hollow fibers membrane	85
CHAPTER 4 RESULTS AND DISCUSSION		86
4.1	PVDF Membrane Blended with Varied PBI Loadings	86
4.1.1	The effects of varied PBI loadings on membrane characteristics	86
4.1.2	The effects of varied PBI loadings on CO ₂ absorption performance	92
4.2	PVDF Membrane Blended with SAPO-34 Zeolite	94
4.2.1	The effects of SAPO-34 zeolite on membrane characteristics	94
4.2.2	The effects of SAPO-34 zeolite on CO ₂ absorption performance	104
4.3	PVDF Membrane Blended with POSS	108
4.3.1	The effects of POSS on membrane characteristics	108
4.3.2	The effects of POSS on CO ₂ absorption performance	118
4.4	PVDF/SAPO-34 Mixed Matrix Membrane with Post Silane Modification	126
4.4.1	The effects of post silane modification on membrane characteristics	126
4.4.2	The effects of post silane modification on CO ₂ absorption performance	133
4.4.3	The effects of post silane modification on evaluation of amine wetting	138
4.5	PVDF/SAPO-34 Hollow Fiber Membranes for Membrane Gas Absorption	143
4.5.1	Effects of SAPO-34 on hollow fiber characteristics	143
4.5.2	Effects of SAPO-34 zeolite on hollow fiber CO ₂ absorption performance	149
4.5.3	Effects of SAPO-34 zeolite on hollow fibers swelling evaluation	157

CHAPTER 5 CONCLUSION AND RECOMMENDATIONS	163
5.1 Conclusion	163
5.2 Recommendations	166
REFERENCES	168
APPENDICES	
LIST OF PUBLICATIONS	

LIST OF TABLES

		Page
Table 1.1	Biogas plants using different sources to generate electricity in Malaysia (Malaysia, 2017, Shafie et al., 2012)	3
Table 2.1	The PVDF blended membranes with various inorganic for MGA applications	24
Table 2.2	Effect of PVDF membranes blended with hydrophobic ZnO and ZIF8 (Salehi et al., 2018)	30
Table 2.3	Properties of liquid absorbent and the contact angle values on PVDF membranes at 20 °C (Rongwong et al., 2009)	43
Table 3.1	List of chemicals and reagents used in this work	54
Table 3.2	The chemical composition for PVDF and PBI blending	57
Table 3.3	The chemical composition for PVDF/PBI membrane incorporated with hydrophilic and hydrophobic SAPO-34 zeolite	64
Table 3.4	Chemical composition of PVDF membrane incorporated with POSS and SAPO-34 zeolite	68
Table 3.5	The chemical composition of silane modified PVDF/SAPO-34 membrane	72
Table 3.6	The composition of PVDF/SAPO-34 hollow fiber membrane	75
Table 3.7	PVDF/SAPO-34 hollow fiber spinning conditions	76
Table 3.8	MGA setup for hollow fiber membrane	81
Table 4.1	Description of the preparation method, water contact angle of the PVDF blended membranes with varied PBI loadings	87
Table 4.2	Comparison absorption flux of P-20PBI membrane with other PVDF membranes reported in literature	94
Table 4.3	Contact angle and the mean pore size of the PVDF membrane blended with different fillers (SAPO-34 zeolite and PBI)	95

Table 4.4	Comparison of CO ₂ fluxes among PVDF membranes with fillers (SAPO-34 zeolite) and additional polymer (PBI) reported in literatures	107
Table 4.5	A comparison of the surface hydrophobicity of M-0 membrane to the surface hydrophobicity of PVDF membranes reported in literature	110
Table 4.6	Membrane thickness, porosity and the atomic percentage of elements in PVDF membranes blended with POSS and SAPO-34 zeolite	117
Table 4.7	The CO ₂ absorption flux of PVDF membranes reported in the recent literature and this work (PVDF membranes blended with POSS and SAPO-34 zeolite)	123
Table 4.8	The overall mass transfer coefficient (K_o) comparison of PVDF membrane blended with POSS and SAPO-34 zeolite with literature	125
Table 4.9	Characteristics of PVDF, PVDF/SAPO-34 and post-modified membranes	126
Table 4.10	Thickness and porosity of Characteristics of PVDF, PVDF/SAPO-34 and post-modified membranes	136
Table 4.11	The overall mass transfer coefficient for PVDF, PVDF/SAPO-34 and silane modified membranes tested at CO ₂ flowrate of 100 ml/min and liquid absorbent flowrate of 204 ml/min	137
Table 4.12	Characteristics of PVDF and PVDF/SAPO-34 hollow fiber membranes	146
Table 4.13	Comparison between the CO ₂ absorption flux through hollow fiber membranes reported in the literature and this work using distilled water as the liquid absorbent	152
Table 4.14	Wilson equation, membrane resistance and mass transfer coefficient (K_m) for different membranes	155
Table 4.15	The overall mass transfer coefficient (K_o) and percentage of CO ₂ removal in MGA with DEA using D0 or D3 hollow fiber membrane. (Operating condition: 100 ml/min of mixed gas (CO ₂ /CH ₄ = 80%:20%) and 70 ml/min of 2 M DEA as the absorbent)	157

LIST OF FIGURES

		Page
Figure 1.1	CO ₂ emissions in Malaysia from 1987 to 2017 (Ychart, 2018)	2
Figure 1.2	Gas absorption via physical or chemical scrubbing	6
Figure 1.3	MGA mechanism for CO ₂ removal	7
Figure 2.1	Some hydrophobic polymers used as membrane material	16
Figure 2.2	Structure of surface modifying macromolecule (SMM)	19
Figure 2.3	Structure of PBI repeat unit	22
Figure 2.4	The structure of SAPO-34 zeolite (Structures, 2016). The yellow lines represent Si (or Al) bonds to O which is represented by red lines	27
Figure 2.5	The structure of POSS material (a) trisilanolisobutyl POSS and (b) aminopropylisobutyl POSS. The yellow lines represent Si (or Al) bonds to O which is represented by red lines, green lines represent C-H bond, pink lines represent OH bond, and blue line represents NH ₃ group	32
Figure 2.6	Chemical grafting on inorganic surface and effect of chemical grafting mixed on membrane matrix	34
Figure 2.7	Conditions of liquid absorbent in wetted membrane	40
Figure 2.8	Mass transfer route and resistance in series in MGA	47
Figure 2.9	Hollow fiber membrane (PVDF/ 2 wt% SMM) spun without air gap using a mixture of water/dimethylacetamide (40/60) as bore fluid (Mansourizadeh et al., 2014)	49
Figure 3. 1	Flowchart of overall methodology	52
Figure 4.1	SEM images PVDF membrane and PBI/PVDF membrane with different loadings	89
Figure 4.2	Pore size distribution of PVDF membrane and PBI/PVDF membrane with different loadings	90

Figure 4.3	The (a) melting temperature (T_m) and (b) crystallization temperature (T_c) of the PVDF/PBI blended membranes at their blend compositions	91
Figure 4.4	CO ₂ Absorption flux of membranes for pure CO ₂ -distilled water system	93
Figure 4.5	AFM images for the top view of P0, P-10PBI, P-10S34, P-10MS34 and P-5S34-5PBI	97
Figure 4.6	SEM images for the top view and the cross-sectional view of P0, P-10PBI, P-10S34, P-10MS34 and P-5S34-5PBI	99
Figure 4.7	FTIR transmittances of P0, P-10PBI, P-10S34, P-10MS34 and P-5S34-5PBI	103
Figure 4.8	CO ₂ absorption flux of PVDF blended membranes with different fillers (SAPO-34 zeolite and PBI) using distilled water as liquid absorbent. (Gas flow rate $Q_g = 100$ ml/min of pure CO ₂)	104
Figure 4.9	The water contact angles on different PVDF membranes blended with POSS and SAPO-34	109
Figure 4.10	AFM images for the top view of (a) M-0, (b) M-S34, (c) M-SP and (d) M-AP membranes	112
Figure 4.11	The structure of trisilanolisobutyl POSS, aminopropylisobutyl POSS and SAPO-34 zeolite added into PVDF membranes. The yellow lines represent Si (or Al) bonds to O which is represented by red lines, green lines represent C-H bond, pink lines represent OH bond, and blue line represents NH ₃ group	113
Figure 4.12	SEM images for the top view of (a) M-0, (b) M-S34, (c) M-SP and (d) M-AP membranes as well as the cross-sectional view of (e) M-0, (f) M-S34, (g) M-SP and (h) M-AP membranes	114
Figure 4.13	The pore size distribution of (a) M-0, (b) M-S34, (c) M-SP and (d) M-AP membranes	116
Figure 4.14	The CO ₂ sorption analysis for (a) SAPO-34 zeolite (b) trisilanolisobutyl POSS, and (c) aminopropylisobutyl POSS fillers	119
Figure 4.15	The effects of gas and liquid absorbent (distilled water) flow rates on the CO ₂ flux through M-0, M-S34, M-SP and M-AP membranes	120

Figure 4.16	AFM images for the top view of PVDF, PVDF/SAPO-34 and after post-modified membranes	128
Figure 4.17	SEM images of PVDF, PVDF/SAPO-34 and silane modified membranes	130
Figure 4.18	FTIR spectra of PVDF and PVDF/SAPO-34 membranes before and after silane post modification	132
Figure 4.19	Proposed mechanism of silane post-modification on SAPO-34 zeolite embedded in PVDF membrane matrix	133
Figure 4.20	CO ₂ fluxes at a feed gas flow rate of 100 ml/min using PVDF, PVDF/SAPO-34 membranes before and after silane post modification	135
Figure 4.21	The effects of CO ₂ feed flow rates on the absorption fluxes of P-5S34F membrane using distilled water as liquid absorbent	136
Figure 4.22	The effects of humidity in feed gas at 100 ml CO ₂ /min on the absorption fluxes of P-5S34F membrane	138
Figure 4.23	The water contact angle on PVDF, PVDF/SAPO-34 and silane modified membranes before and after immersed in 2 M of DEA solution for 50 hours	139
Figure 4.24	FTIR spectrum of PVDF, PVDF/SAPO-34 and post silane modified membranes after immersed 50 hours in 2 M of DEA solution	141
Figure 4.25	SEM images of PVDF, PVDF/SAPO-34 and post silane modified membranes after immersed 50 hours in 2 M of DEA solution	142
Figure 4.26	Cross-sectional structure of the hollow fiber membranes; (a-b) D0, (c-d) D1, (e-f) D3 and (g-h) D5	144
Figure 4.27	Surface roughness on the outer layer of hollow fibre membranes	147
Figure 4.28	FTIR spectra of the hollow fiber membranes	148
Figure 4.29	The melting temperature (T_m) and crystallization temperature (T_c) of the hollow fiber membranes	149
Figure 4.30	CO ₂ absorption fluxes through the hollow fiber membranes at CO ₂ gas flow rates of (a) 100 ml/min, (b) 200 ml/min using and (c) 300 ml/min distilled water as the liquid absorbent	151

Figure 4.31	CO ₂ absorption flux of D0 and D3 hollow membranes at a mixed gas (CO ₂ /CH ₄ = 80%:20%) flow rate of 100 ml/min using 2 M DEA as the liquid absorbent	153
Figure 4.32	Wilson plot for CO ₂ absorption for pure D0 and D3 membrane using 2 M DEA at (gas flow rate $Q_g =$ CO ₂ /CH ₄ = 20%:80% at 100 ml/min. DEA flow rate $Q_L =$ 40 to 100 ml/min)	154
Figure 4.33	(a) Sherwood number as function of the Reynolds number. (b) Liquid mass transfer coefficient, K_L (m/s) with different DEA flowrate on hollow shell for membrane of D0 and D3. (Liquid absorbent flow rate in range of 40 to 100 ml/min)	156
Figure 4.34	The effects of operation duration on CO ₂ absorption flux of D0 and D3 hollow membranes at a mixed gas (CO ₂ /CH ₄ = 20%:80%) flow rate of 100 ml/min using 2 M DEA (flowrate = 70 ml/min) as the absorbent	157
Figure 4.35	FTIR spectra of (a) D0 and (b) D3 hollow fiber membranes before and after being immersed into DEA (2 M) for 50 hours	158
Figure 4.34	SEM images D0 and D3 hollow fiber membranes before and after being immersed into DEA (2 M) for 50 hours	160
Figure 4.37	The swelling degree and water contact angle of PVDF and PVDF/SAPO-34 hollow fiber membranes wetted by DEA and water	162

LIST OF PLATES

		Page
Plate 3.1	Fabrication of flat sheet membrane: a) membrane casting machine, b) polymer solution and c) double coagulation baths	57
Plate 3.2	Porometer Porolux 1000 for pore size measurement	59
Plate 3.3	Schematic of MGA testing rig for flat sheet membrane	61
Plate 3.4	Preparation of SAPO-34 zeolite set up under hydrothermal process	62
Plate 3.5	Fourier Transform Infrared (FTIR)	67
Plate 3.6	Hollow fiber spinning set up; (a) spinneret and (b) spinning process	77
Plate 3.7	Schematic diagram of MGA testing rig with CO ₂ /CH ₄ mixed gas	81

LIST OF SYMBOLS

%	Percentage
θ	Angle ($^{\circ}$)
$^{\circ}\text{C}$	Temperature in degree celsius
A_i	effective membrane contact area
cm	Unit of length in centimetre
d_i	The inner diameter of the hollow fiber
d_o	The outer diameter of the hollow fiber
d_{ln}	The logarithm mean diameter of the hollow fiber
g	Weight in gram
H	Henry's constant
J_{CO_2}	CO ₂ absorption flux
K_L	The liquid mass transfer coefficient in liquid
K_m	The Membrane mass transfer coefficient in liquid
K_o	Overall mass transfer coefficient
ml	Millilitre
nm	Unit of length in nanometer (10^{-9} m)
Q_g	Gas flow rate
Q_L	Liquid flow rate
R_a	Average roughness
R_q	The root-mean-square roughness
R_m	Membrane resistance
Re	Reynold number
Sh_L	Sherwood number
V_L	Ratio of absorbent flow rate (m^3/s) per cross-sectional area (m^2)
$v\%$	Volume percentage
wt%	Weight percentage

LIST OF ABBREVIATIONS

AFM	Atomic force microscope
CaCO ₃	Calcium carbonate
CH ₄	Methane
CO ₂	Carbon dioxide
DEA	Diethanolamine
DMAC	Dimethylacetamide
DMF	N-, N-Dimethylformamide
DSC	Differential Scanning Calorimetry
D0	Neat PVDF hollow fiber membrane
D1	PVDF hollow fiber membrane with 1 wt% of SAPO-34
D3	PVDF hollow fiber membrane with 3 wt% of SAPO-34
D5	PVDF hollow fiber membrane with 5 wt% of SAPO-34
EDX	Energy-dispersive X-ray spectroscopy
FS	Flat Sheet membrane
FTIR	Fourier transform infrared
HF	Hollow fiber membrane
H ₂	Hydrogen
H ₂ S	Hydrogen sulphide
H ₃ PO ₄	Ortho-Phosphoric acid
LEP	Liquid entry pressure
LiCl	Lithium chloride
LDPE	Low density poly ethylene
M-AP	Aminopropylisobutyl
MEA	Monodiethanolamine
MGA	Membrane gas absorption
MOF	Metal-organic framework

M-SP	Flat sheet PVDF membrane contains 10 wt% of trisilanolisobutyl POSS and nonsolvent
M-S34	PVDF membrane contains 10 wt% SAPO-34 POSS and nonsolvent
MMT	Montmorillonite clays
M-0	PVDF membrane contains nonsolvent
NaOH	Sodium Hydroxide
NMP	n-methyl-2- Pyrrolidone
NH ₃	Ammonia
N ₂	Nitrogen
OH	Hydroxyl group
O ₂	Oxygen
PBI	Poly[2,2'-(m-phenylene)-5,5'-dibenzimidazole
PDMS	Polydimethylsiloxane
PE	Polyethylene
PEI	Polyethylenimine
PEEK	Poly(ether ether ketone)
PES	Polyethersulfone
POME	Palm oil mill effluent
POSS	Polyhedral oligomeric silsesquioxane
PP	Polypropylene
PSA	Pressure swing adsorption
PSf	Polysulfone
PTFE	Polytetrafluorethylene
PVDF	Polyvinylidene fluoride
P0	Neat flat sheet PVDF membrane
P-0F	Neat flat sheet PVDF membrane with post silane modification
P-10 PBI	Flat sheet PVDF membrane contains 10 wt% of PBI

P-10S34	Flat sheet PVDF membrane contains 10 wt% of SAPO-34
P-10S34F	Flat sheet PVDF membrane contains 10 wt% of SAPO-34 with post silane modification
P-10MS34	Flat sheet PVDF membrane contains 10 wt% of hydrophobic SAPO-34
P-15PBI	Flat sheet PVDF membrane contains 15 wt% of PBI
P-20PBI	Flat sheet PVDF membrane contains 20 wt% of PBI
P-25PBI	Flat sheet PVDF membrane contains 25 wt% of PBI
P-5S34	Flat sheet PVDF membrane contains 5 wt% of SAPO-34
P-5S34F	Flat sheet PVDF membrane contains 5 wt% of SAPO-34 with post silane modification
P-5S34-5PBI	Flat sheet PVDF membrane contains 5 wt% of SAPO-34 and 5 wt% of PBI
SEM	Scanning electron microscopy
SMM	Surface modifying macromolecule
SiO	Silica oxide
SAPO-34	Silicoaluminophosphate-34
TGA	Thermogravimetric analysis
ZSM5	ZSM5 zeolite

**PENYINGKIRAN CO₂ MENGGUNAKAN MATRIK CAMPURAN
MEMBRAN POLIVINILIDENA FLUORIDA DALAM MEMBRAN
PENYERAPAN GAS**

ABSTRAK

Teknologi penyingkiran karbon dioksida (CO₂) sangat penting untuk penulenan sumber tenaga seperti biogas. Antara teknologi penyingkiran CO₂, membran penyerapan gas (MGA) boleh digunakan untuk menyingkirkan CO₂ pada tekanan rendah. MGA mengintegrasikan kelebihan membran dan proses penyerapan kimia dalam satu unit. Namun, pembasahan membran semasa pengendalian jangka panjang menggalakkan peningkatan rintangan jisim walaupun menggunakan membran hidrofobik. Membran polivinilidena fluorida (PVDF) kerap kali digunakan untuk MGA, tetapi andaian ternyah fluoride PVDF ke dalam larutan amina menyebabkan berlakunya pembasahan membran. Dalam kajian ini, polimer poli[2,2'-(m-fenilena)-5,5'-dibenzimidazol (PBI) yang mempunyai rintangan kimia dan kestabilan haba yang tinggi telah diadun bersama polimer PVDF untuk meningkatkan sifat kimia dan fizik membran. Selain itu, zeolit SAPO-34 yang mempunyai sifat afiniti penyerapan terhadap CO₂ dicampur ke dalam membran PVDF untuk meningkatkan penyerapan CO₂. Gabungan membran PVDF dengan zeolit SAPO-34 juga diubahsuai menjadi hidrofobik menggunakan silana. Ikatan hydrogen dalam adunan polimer melalui penderma (-NH-) dan proton penerima (-N=) dari PBI menggalakkan penghasilan boleh-larut campuran. Membran PVDF/PBI dengan bebanan 20 wt% PBI menghasilkan penyerapan CO₂ tertinggi sebanyak 3.07×10^{-4} mol/m²s. Manakala, fluks CO₂ membran PVDF meningkat sehingga 60 % ke 4.53×10^{-4} mol/m²s apabila membran PVDF diadun bersama 10 wt% SAPO-34. Praubahsuai zarah zeolit SAPO-

34 menggunakan fluorokarbon salina mengagalkan pembentukan struktur membran berliang, kesannya rintangan membran semasa penyerapan CO₂ bertambah tinggi. Pascaubahsuai membran PVDF/SAPO-34 menggunakan silana meningkatkan penyerapan CO₂. Tambahan itu, peningatan ketara berlaku di mana sudut sentuhan dan tekanan kemasukan cecair meningkat kesannya keseluruhan pemindahan jisim (K_o) menjadi 12.46×10^{-6} m/s. Ujikaji CO₂ lembap ke sistem MGA dengan gabungan PVDF/SAPO-34 pascaubahsuai, mengurangkan sedikit telapan CO₂ menjadi 10.65×10^{-6} m/s. Namun, K_o untuk membran PVDF/SAPO-34 pascaubahsuai hampir sama dengan K_o membran PVDF/SAPO-34 tanpa pengubahsuaian silana. Ujikaji kebasahan membran dengan larutan 2 M dietahmolamina (DEA) menunjukkan adunan polimer dan zeolit dalam membran PVDF/SAPO-34 mengurangkan pembengkakan membran. Akan tetapi, interaksi tidak diinginkan berlaku antara kumpulan fluoroalkil dan amina mengaruhkan kebasahan membran PVDF/SAPO-34 pascaubahsuai oleh amina. Seterusnya, gentian geronggang PVDF/SAPO-34 dengan bebanan zeolit SAPO-34 berbeza (1, 3 dan 5 wt%) telah dihasilkan. Fluks CO₂ tertinggi dicapai sehingga 8.73×10^{-4} mol/m²s apabila 3 wt% zeolite SAPO-34 telah dimasukkan ke dalam adunan gentian geronggang PVDF/SAPO-34. Gentian geronggang PVDF/SAPO-34 menunjukkan rintangan jisim yang rendah berbanding membran kepingan rata PVDF/SAPO-34. Fluks CO₂ gentian geronggang PVDF/SAPO-34 meningkat 140 % kali ganda lebih tinggi berbanding fluks CO₂ gentian geronggang PVDF asli apabila 2 M DEA digunakan sebagai cecair penyerap. Gentian geronggang PVDF asli terampul hampir 71.0 % dalam DEA tetapi adunan gentian geronggang PVDF/SAPO-34 mengurangkan pembengkakan dengan amina sehingga 47.7 %.

CO₂ REMOVAL USING POLYVINYLIDENE FLUORIDE MIXED MATRIX MEMBRANE IN MEMBRANE GAS ABSORPTION

ABSTRACT

Carbon dioxide (CO₂) removal technology is important in the purification of energy source such as biogas. Among the CO₂ removal techniques, membrane gas absorption (MGA) can be used to separate CO₂ at low pressure. MGA integrates the advantages of membrane and chemical absorption process in a single unit. However, membrane wetting in the long operation can induce the increment of mass transfer resistance even using hydrophobic membranes. Polyvinylidene fluoride (PVDF) is the commonly used membrane in MGA, but PVDF defluorination in amine solutions was postulated to cause membrane wetting. In this research, poly[2,2'-(*m*-phenylene)-5,5'-dibenzimidazole (PBI) with the great chemical resistance and thermal stability was blended into PVDF membrane to enhance the physical and chemical properties membrane. Besides that, SAPO-34 zeolite with CO₂ absorption affinity was incorporated into PVDF membrane to improve CO₂ absorption. PVDF membrane incorporated with SAPO-34 zeolite was hydrophobically modified using silane. Hydrogen bonding in the polymer blend due to donor (-NH-) and proton acceptor (-N=) of PBI encouraged the formation of miscibility blend. PVDF/PBI membrane with 20 wt% of PBI showed the highest CO₂ flux of 3.07×10^{-4} mol/m²s. The CO₂ flux of PVDF membrane increased 60 % to 4.53×10^{-4} mol/m²s when it was blended with 10 wt% of SAPO-34 zeolite. The pre-modified SAPO-34 zeolite using fluorocarbon silane retarded the formation of porous structure, resulting in a great membrane resistance for CO₂ transfer. The post-modification of PVDF/SAPO-34 membrane using silane caused improvement in CO₂ absorption. The significant