

**BIOSYNTHESIS OF POLY(3-HYDROXYBUTYRATE)
BY *CUPRIAVIADUS NECATOR* DSM 428 UTILIZING
WASTE DATE FRUITS AS A CARBON SOURCE**

SITI NUR AQILAH BINTI ABDUL WAHAB

UNIVERSITI SAINS MALAYSIA

JUNE 2020



**PUSAT PENGAJIAN TEKNOLOGI
INDUSTRI UNIVERSITI SAINS
MALAYSIA**

**BORANG PENYERAHAN DISERTASI
MUTAKHIR SATU (1) NASKAH**

Nama penyelia: Dr. Siti Baidurah Binti Yusoff

Bahagian: Teknologi Bioproses

Saya telah menyemak semua pembetulan/pindaan yang dilaksanakan oleh Encik/Puan/Cik Siti Nur Agilah Binti Abdul Wahab mengenai disertasinya sebagaimana yang dipersetujui oleh Panel Pemeriksa di Viva Vocenya.

2. Saya ingin mengesahkan bahawa saya berpuashati dengan pembetulan/pindaan yang dilaksanakan oleh calon.

Sekian, terima kasih.

17 Julai 2020

(Tandatangan dan cop)

DR. SITI BAIDURAH YUSOFF
B.Sc (USM), M.Sc & PhD (Japan)
School of Industrial Technology
Universiti Sains Malaysia
11800 Penang, Malaysia
Tel : 04 - 653 6381

Tarikh



**BIOSYNTHESIS OF POLY(3-HYDROXYBUTYRATE)
BY *CUPRIAVIADUS NECATOR* DSM 428 UTILIZING
WASTE DATE FRUITS AS A CARBON SOURCE**


by

SITI NUR AQILAH BINTI ABDUL WAHAB

A dissertation submitted in the partial fulfilment of the requirements for the degree of
Bachelor of Technology (B.Tech) in the field of
Bioprocess Technology
School of Industrial Technology
Universiti Sains Malaysia
June 2020

DECLARATION BY AUTHOR

This dissertation is composed of my original work, and contains no material previously published or written by another person except where due reference has been made in the text. The content of my dissertation is the result of work I have carried out since the commencement of my research project and does not include a substantial part of work that has been submitted to qualify for the award of any other degree or diploma in any university or other tertiary institution.

{Signature} : 

{Full Name} : Siti Nur Aqilah Binti Abdul Wahab

{Month Year} : June 2020

ACKNOWLEDGEMENT

In the name of Allah, Most Gracious, Most Merciful. All praises be to Allah, for His grace and mercy that I had finally able to complete this final year project successfully. I would like to express my deepest appreciation and gratitude to my final year project supervisor, Dr. Siti Baidurah Binti Yusoff for her times, advice and guidance since the beginning until the end of my research. I would like to thank to master's student of Dr Siti, Miss Lydia and Miss Sharifah for their support throughout my project.

Heartiest gratitude to our lab assistance, Encik Azmaizan Yaakub and Puan Najmah Hamid for spending their time to prepared the chemicals and some equipment. Also not forgotten, I conveyed thanks to Encik Khairul Azhar Jaafar for his help along this research.

I would like to thank to my lab-mate, course mate and friends for the kind support and a lot of encouragement during my project. Finally, I would like to thank my beloved family for their Dua', moral and financial support, energy, advice and encouragement during my project to make sure I am doing well until the end of this project.



Siti Nur Aqilah Binti Abdul Wahab

June 2020

TABLE OF CONTENT

	Page
Declaration by author	ii
Acknowledgements	iii
Table of Contents	iv
List of Tables	vi
List of Figures	vii
List of Symbols	viii
List of Abbreviations	ix
Abstrak	xii
Abstract	xiii
CHAPTER 1 INTRODUCTION	
1.1 Research Background	1
1.2 Problem Statement	3
1.3 Objectives	4
CHAPTER 2 LITERATURE REVIEW	
2.1 Petrochemical-Based Plastic Affects The Health Of Earth.	5
2.2 Biodegradable Plastics	6
2.3 Bacteria For PHB Production	10
2.4 Date Fruits As Low-Cost Carbon Feedstock	12
CHAPTER 3 MATERIALS AND METHODS	
3.1 Flowchart Of Conducted Experiments.	16
3.2 Preparation Of Waste Date Fruits Solution As Fermentation Medium	17
3.3 Determination Of Sugar Content And Concentration In Waste Date Fruits Using HPLC	18

3.4 Determination Of Total Nitrogen Using Kjeldahl Method	18
3.5 Inoculum And Culture Medium Preparation	19
3.6 Bacterial Cultivation	20
3.7 Cell Growth Measurement	21
3.8 Determination Of PHB Content	22
CHAPTER 4 RESULTS AND DISCUSSION	
4.1 Date Fruits Characterisation	
4.1.1 Determination Of Sugar Content And Composition Using HPLC	24
4.1.2 Determination Of Nitrogen Content Using Kjeldahl Method	27
4.2 Fermentation Process Of <i>C. necator</i> Using Waste Of Dates Fruit	
4.2.1 Growth Profile	30
4.3 Production Of Polyhydroxybutyrate (PHB)	
4.3.1 Cell Dry Weight And PHB Content	33
4.4 Correlation Of Sugar And Nitrogen Content On The PHB Accumulation	36
4.5 Statistical Analysis	37
CHAPTER 5 CONCLUSIONS AND RECOMMENDATION	
5.1 Conclusion And Recommendation	38
REFERENCES	39
APPENDICES	43

LIST OF TABLES

Caption		Page
Table 2.1	Physical properties of PHB	9
Table 2.2	Comparison of various types of bacteria, carbon sources, PHA type and content (%)	10
Table 2.3	Comparison of PHB content by utilization of waste date fruits as carbon feedstock	14
Table 4.1	The analysis of the sugar content and composition before and after fermentation	25
Table 4.2	The percentage of nitrogen content determined using Kjeldahl method in various dates to water ratios	29
Table 4.3	Average amount of cell dry weight (CDW) and PHB content.	35

LIST OF FIGURES

Caption		Page
Figure 2.1	Chemical structure of Poly (3-hydroxybutyrate)	9
Figure 3.1	Flowchart of methodology conduct in this study	16
Figure 4.1	Bar graph represents the amount of sugars obtained in dates solution before and after fermentation	27
Figure 4.2	Average of nitrogen obtained in different ratios of dates solution before and after fermentation	29
Figure 4.3	Growth curve of <i>Cupriavidus necator</i> throughout 26 hours fermentation, with 200 rpm agitation at 30°C with various dates to water ratio: (a) 1:3, (b) 1:5, and (c) 1:8.	31

LIST OF SYMBOLS

Symbol	Caption
\pm	Plus-minus
%	Percentage
$^{\circ}\text{C}$	Degree Celcius
$^{\circ}\text{C}/\text{min}$	Degree Celcius per minute
X	Multiply

LIST OF ABBREVIATIONS

Symbol	Caption
PHB	Polyhydroxybutyrate
P3HB	Poly(3-hydroxybutyrate)
g/L	Gram per litre
PHA	Polyhydroxyalkanoate
K	Thousand
PE	Polyethelene
PP	Polypropelene
Kg	Kilogram
PLA	Poly lactid acid
kg/m ³	Kilogram per Cubic Meter
mPa	Mega pascal
UV	Ultraviolet
P(3HB-co-3HV)	Poly(3-hydroxybutyrate-co-3-hydroxyvalerate)
Scl	Short chain length
CDW	Cell dry weight
3HV	3-hydroxyvalerate
Mmt	Million metric tonnes
ml	Millilitre
Rpm	Revolutions per minute
HPLC	High Performance Liquid Chromatography
GC	Gas Chromatography
g	Gram
pH	Potion of hydrogen

Psi	Pound per square inch
μl	Microlit
μm	Micrometer
Mm	Millimeter
Min	Minutes
ml/min	Millilitre per minute
NaOH	Sodium Hydroxide
HCl	Hydrochloric Acid
Mg	Milligram
NB	Nutrient Broth
L	Litre
M	Molar
MSM	Mineral salt medium
$(\text{NH}_4)_2\text{SO}_4$	Ammonium sulfate
KH^2PO_4	Potassium dihydrogen phosphate
Na_2HPO_4	Sodium phosphate dibasic
$\text{MgSO}_4 \cdot \text{XH}_2\text{O}$	Magnesium sulphate hydrate
$\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$	Ferrous sulfate heptahydrate
$\text{ZnSO}_4 \cdot 7\text{H}_2\text{O}$	Zinc sulphate heptahydrate
$\text{CuSO}_4 \cdot 5\text{H}_2\text{O}$	Copper sulphate pentahydrate
$\text{MnSO}_4 \cdot \text{H}_2\text{O}$	Manganese sulphate monohydrate
$\text{CaCl}_2 \cdot 2\text{H}_2\text{O}$	Calcium chloride dihydrate
$\text{Na}_2\text{B}_4\text{O}_7 \cdot 10\text{H}_2\text{O}$	Sodium tetraborate decahydrate
$(\text{NH}_4)_6\text{Mo}_7\text{O}_{24} \cdot 4\text{H}_2\text{O}$	Ammonium molybdate tetrahydrate
OD	Optical Density

v/v	Volume to volume
kPa	Kilopascal
TCA	Tricarboxylic acid
Nm	Nanometre
H	Hour
ANOVA	Analysis of variance

BIOSINTESIS POLI (3-HIDROKSIBUTIRAT) OLEH *CUPRIAVIDUS NECATOR* DSM 428 MENGGUNAKAN BUAH KURMA TERBUANG SEBAGAI SUMBER KARBON.

ABSTRAK

Banyak penyelidikan telah dilakukan untuk mencari pengganti plastik yang dihasilkan dari petroleum konvensional. Polihidroksibutirat (PHB) adalah polimer biodegradasi yang dihasilkan dari sumber yang boleh diperbaharui telah mendapat perhatian untuk menggantikan plastik yang dihasilkan dari petroleum konvensional kerana ia memiliki sifat kimia dan fizikal yang sangat baik, dengan kelebihan kebolehbidegradasi yang lengkap. Batasan dalam menghasilkan PHB dalam skala besar adalah kerana kos sumber karbonnya yang mahal. Kajian ini memberi tumpuan kepada penghasilan PHB oleh *Cupriavidus necator* menggunakan sumber karbon yang berkos rendah seperti hasil buangan buah kurma. Tiga nisbah kepekatan larutan buah kurma terhadap air disediakan iaitu 1:3, 1:5, 1:8 dengan keadaan penapaian 30 °C, 200 rpm dan penapaian sehingga 29 jam. Analisis kandungan gula dalam larutan buah kurma dilakukan sebelum dan selepas proses penapaian. Kandungan glukosa menunjukkan jumlah tertinggi berbanding fruktosa dan sukrosa iaitu $48.5 \pm 6.3\%$ (v/v), $55.7 \pm 3.8\%$ (v/v) dan $60.6 \pm 5.1\%$ (v/v). Purata berat sel kering terhadap nisbah 1:3, 1:5 dan 1:8 adalah $0.179 \pm 0.03\text{g/L}$, $0.166 \pm 0.01\text{g/L}$ dan $0.180 \pm 0.01\text{g/L}$. Manakala kandungan PHB adalah, $7.9 \pm 3.0\%$, $4.1 \pm 3.4\%$ dan $10.4 \pm 9.6\%$. Nisbah 1:8 mencatatkan berat sel kering dan PHB tertinggi dibandingkan dengan semua nisbah walaupun ia adalah larutan buah kurma yang paling cair. Pemerhatian ini adalah berdasarkan penggunaan sumber karbon yang berkesan kerana mengandungi glukosa tertinggi dibandingkan dengan nisbah lain, dan jumlah nitrogen yang terhad ($1.45 \pm 1.06\%$) yang meningkatkan kesan positif terhadap penghasilan PHB.

**BIOSYNTHESIS OF POLY(3-HYDROXYBUTYRATE) BY *CUPRIAVIDUS*
NECATOR DSM 428 UTILIZING WASTE DATE FRUITS AS A CARBON SOURCE**

ABSTRACT

Many researches have been conducted to find a replacement for conventional petroleum-derived plastics. Poly(3-hydroxybutyrate) (PHB) is biodegradable polymers produced from a renewable source have gained many interest to replace conventional plastic, as it possesses excellent chemical and physical properties, with an advantages of complete biodegradability. The limitation in producing huge amount of PHB is due to its expensive cost of carbon sources. This study focus on the production of PHB by *Cupriavidus necator* using low-cost carbon sources such as waste of date fruits. Three concentration ratios of date fruits to water was prepared which are 1:3, 1:5, and 1:8 with the fermentation condition of 30°C, 200 rpm and up to 29 hours of fermentation. Analysis of sugar content in date fruits solution was performed prior and after the fermentation process. Glucose content shows the highest amount compared to fructose and sucrose which are $48.5 \pm 6.3\%$, $55.7 \pm 3.8\%$ and $60.6 \pm 5.1\%$. The average CDW of ratio 1:3, 1:5 and 1:8 are $0.179 \pm 0.03\text{g/L}$, $0.166 \pm 0.01\text{g/L}$ and $0.180 \pm 0.01\text{g/L}$. While the PHB content are, $7.9 \pm 3.0\%$, $4.1 \pm 3.4\%$ and $10.4 \pm 9.6\%$ respectively. Ratio 1:8 state the highest CDW and PHB in comparison to all ratios even it is the most diluted date fruits solution. This observation is due to effective utilization of carbon sources as it contained the highest glucose compared to other ratios, and limited amount of nitrogen ($1.45 \pm 1.06\%$) which enhanced the positive effect on PHB production.