SYNTHESIS AND PROPERTIES OF PHENOLIC BASED HYBRID CARBON NANOTUBE/INORGANIC FILLED COMPOSITES

SITI SHUHADAH BINTI MD SALEH

UNIVERSITI SAINS MALAYSIA 2017

SYNTHESIS AND PROPERTIES OF PHENOLIC BASED HYBRID CARBON NANOTUBE/INORGANIC FILLED COMPOSITES

by

SITI SHUHADAH BINTI MD SALEH

Thesis submitted in fulfilment of the requirement for the degree of Doctor of Philosophy

ACKNOWLEDGEMENTS

All praises belong to Allah, the Most gracious, the Most Merciful, who enables me to complete this research work successfully. This PhD thesis would not have been possible without the help of a number of people, and expressing gratitude to all of them is a must. First and foremost, I feel highly privileged here to have the honour to acknowledge my research supervisor Prof. Dr. Hazizan Md Akil for his guidance, patience and advice throughout this study. I also owe an intellectual debt to my cosupervisor Dr Ramdziah Md Nasir for her advice and crucial contribution in this research.

Not to forget, thanks to School of Materials and Mineral Resources Engineering (SMMRE), Universiti Sains Malaysia, for providing me the equipments, machine and facility to conduct my research. Also, not forgetting to acknowledge the financial support by Universiti Malaysia Perlis under the SLAB scheme and Universiti Sains Malaysia under the Postgraduate Research Grant Scheme (PRGS-8044022).

I would like to acknowledge the continuous encouraging attitude of my family especially my late dearest mother and father, Allahyarhamah Hajah Rahmah binti Senik and Allahyarham Haji Md Saleh bin Abdullah and my brothers and sisters, Siti Rodziah Md Saleh, Muhammad Radzi Md Saleh, Muhammad Adeli Md Saleh, Hajah Siti Rosilah Md Saleh and Haji Akhbarnezam bin Ahmad. My nieces and nephews, Siti Nurdinie Aliya binti Haji Akhbarnezam, Ahmad Akhtar bin Haji Akhbarnezam, Siti Nur Damia Aqilah binti Haji Akhbarnezam and Nurdurratul Aisya binti Haji Akhbarnezam. My Thank you for providing me with such loving and emotional support. My heart-felt appreciation extends to all my fellow friends Nur Hanim Naim, Syahriza Ismail, Norshahida Sharifuddin, Ervina Junaidi,

Norfarahiyah Mohamad, Zaid Aws Ghaleb, Emee Marina Saleh and Nurul Hidayah

Ismail and LVI group members, Chang Boon Peng, Anis Suraya Ahmad Bakhtiar,

Muhammad Helmi Abdul Kudus, Muhammad Razlan Zakaria, Hafiz Zamri, Norlin

Nosbi, Siti Zalifah Md Rasib and Tuan Noraihan Azila Tuan Rahim for always being

so encouraging and motivating and for the fruitful interaction over the study period.

Furthermore, a deep appreciation also should be expressed to the technicians

especially Mr. Shahrul Ami Bin Zainal Abidin, Mr. Kemuridan Bin Md Desa, Mr.

Mohd Azam Bin Rejab, Mr. Muhammad Khairi Bin Khalid, Mr. Mohamad Zaini

Bin Saari and Mr. Mohamad Shafiq bin Mustapa Sukri who have worked hard with

the project completion direct or indirectly. Besides that, I would also grab this chance

to thank the dean of SMMRE Professor Dr. Zuhailawati binti Hussain and the

administrative staffs for the great assistance in ensuring my work progresses steadily.

Thanks for continuous support and encouragement. No words are sufficient to

express my gratitude and thanks for their support and understanding.

SITI SHUHADAH MD SALEH

March 2017

iii

TABLE OF CONTENTS

ACK	NOWL	EDGEMENT	S		ii	
TAB	LE OF (CONTENTS			iv	
LIST	OF TA	BLES			X	
LIST	OF FIG	GURES			xii	
LIST	OF AB	REVIATION	IS		xvii	
	OF SY	MBOLS			xix	
	ABSTRAK ABSTRACT					
ABS	TRACT				xxii	
СНА	PTER C	ONE: INTRO	DUCTION			
1.1	Resear	rch Backgroun	d		1	
1.2	Proble	m Statements			4	
1.3	Resear	ch Objectives			6	
1.4	Scope	of the Researc	ch		6	
СНА	PTER T	TWO: LITER	ATURE RE	VIEW		
2.1	Introdu	uction			9	
2.2	Hybric	d Filler for Pol	ymer Compo	sites	9	
2.3	Introdu	uction to CNT	s		12	
	2.3.1	Properties of	of CNTs		14	
2.4	Synthe	esis of CNTs			15	
	2.4.1	Factors that	Affecting the	e CNTs Growth	17	
		2.4.1 (a)	Catalyst for	CNTs Growth	17	
			2.4.1 (a) (i)	The Catalyst Support Substrate	18	
			2.4.1 (a) (ii)	Calcination Duration and Calcination		
				Temperature	20	

		2.4.1 (b)	CNT Precursors or the Carbon Feedstock	
			(Hydrocarbon)	21
		2.4.1 (c)	Carrier Gases	21
		2.4.1 (d)	Reaction Temperature	21
2.5	Potenti	al Applicatio	ns of CNTs and their Composites	22
	2.5.1	The Develo	opment of CNTs Hybrid	23
	2.5.2	Inorganic N	Naterials as Catalyst Support Substrate	26
		2.5.2 (a)	Alumina (Al ₂ O ₃)	27
		2.5.2 (b)	Calcium carbonate (CaCO ₃)	27
		2.5.2 (c)	Dolomite (CaMg(CO ₃) ₂)	28
		2.5.2 (d)	Talc $(Mg_3Si_4O_{10}(OH)_2)$	29
	2.5.3	Advantages	s of using CNTs/Inorganic in Polymer Nanocomposit	es 29
2.6	Tribolo	gical Propert	ies and Applications	30
	2.6.1	Friction		31
	2.6.2	Wear		32
		2.6.2 (a)	Adhesive Wear	33
		2.6.2 (b)	Abrasive Wear	34
		2.6.2 (c)	Fatigue Wear	34
	2.6.3	Inorganic N	Materials and CNTs Based Polymer Composites in	
		Tribologica	l Application	35
		2.6.3 (a)	Phenolic	36
2.7	Design	of Experime	nt (DOE)	38
	2.7.1	Response S	urface Methodology (RSM)	39
	2.7.2	RSM in Tri	bological Behaviour of Materials	40

2.8	Resear	ch strategy for the synthesis of CN1s/morganic Hybrid Fined	
	Phenol	lic Composites Used in the Present Research	41
СНА	PTER T	THREE: METHODOLOGY	
3.1	Introdu	action	43
3.2	Materi	als	43
	3.2.1	Phenolic	43
	3.2.2	Support Materials	44
	3.2.3	Nickel (II) Nitrate Hexahydrate	45
	3.2.4	Sodium Hydroxide	45
	3.2.5	Alumina Powder	45
	3.2.6	Carbon Nanotubes (CNTs)	46
	3.2.7	Methane Gas	46
	3.2.8	Nitrogen Gas	47
	3.2.9	Hydrogen Gas	47
3.3	Synthe	esis of CNTs/Alumina Hybrid Compound	48
	3.3.1	Different Calcination Temperatures and Calcination Durations	50
3.4	Prepara	ation of Physical Mixed (PHY Hybrid)	52
3.5	Synthe	esis of CNTs/Inorganic Hybrid Compound	53
3.6	Prepara	ation of CNTs/Alumina Hybrid Filled Phenolic Composites	54
3.7	Charac	eterizations	55
	3.7.1	X-ray Diffraction Analysis (XRD)	56
	3.7.2	Field Emission Scanning Electron Microscopy (FESEM)	56
	3.7.3	High Resolution Transmission Electron Microscope (HRTEM)	56
	3.7.4	RAMAN Spectroscopy	57
	3.7.5	Hardness Test	57

	3.7.6	Density Mo	easurement	57
	3.7.7	Thermal C	Conductivity Measurement	58
	3.7.8	Friction an	d Wear Test Procedure	59
	3.7.9	Design of l	Experiment Using Response Surface Methodology	
		(RSM)		61
		3.7.9 (a)	Mathematically Modelling Based on RSM and	
			Optimization	62
СНА	PTER F	OUR: SYHT	THESIS AND PROPERTIES OF CARBON	
NAN	OTUBE	/ALUMINA	HYBRID FILLED POLYMER COMPOSITE	
4.1	Overvi	ew		64
4.2	Effect	of Catalyst (Calcination Temperatures on the Synthesised	
	CNTs/	Alumina Hyl	orid Compound via CVD Method	64
4.3	Effect	of Calcinatio	n Durations on the Synthesised CNTs/Alumina Hybrid	d
	Compo	ound via CVI) Method	73
4.4	Compa	arative Studie	s Between Phenolic filled with CNTs/alumina	
	Chemi	cally Hybrid	(HYB hybrid) Compound and Physically Mixed (PHY	Y
	Hybrid	1)		82
	4.4.1	Morpholog	y of HYB Hybrid Compound and PHY Hybrid	83
	4.4.2	Properties	of HYB Composites and PHY Composites	86
		4.4.2 (a)	Thermal Conductivity	86
		4.4.2 (b)	Wear and Friction Behaviour of HYB Composites	
			and PHY Composites	89
			4.4.2 (b) (i) Effect of Hybrid Filler Loading of	n
			Wear and Coefficient of Friction	1

			4.4.2 (b) (ii)	Effect of Sliding Speed on Wear and	
				Coefficient of Friction (COF)	93
			4.4.2 (b) (iii)	Effect of Applied Load on Wear and	
				Coefficient of Friction	95
		4.4.2 (c)	SEM of Worn	Surfaces of the Composites	97
		4.4.2 (d)	Hardness of tl	ne Composites	99
СНА	PTER FI	IVE: MODE	LLING AND	OPTIMIZATION THE	
				ARBON NANOTUBE/ALUMINA	
				OSITE USING RESPONSE SURFA	CE
	HOD (R				
5.1	Overvie	·			101
5.1	Develo	pment of Wear	r and Friction	Models of Carbon Nanotubes/Alumin	a
	•	-		Based on RSM	102
	5.1.1		t of the Model		102
	5.1.2	-	Mathematical		110
	5.1.3	Residual Plo	ts		111
5.2	Relatio	nship Between	n the Volume I	Loss of Phenolic Hybrid Composites	
	with the	e Variables			114
	5.2.1	Statistical Pa	ired Test for V	Volume Loss of Phenolic Hybrid	
		Composites			118
5.3	Relatio	nship Between	the Average	COF of Phenolic Hybrid Composites	
	with the	e Variables			119
	5.3.1	Statistical Pa	ired Test of A	verage COF of Phenolic Hybrid	
		Composites		•	123
5.4	Optimiz	zation of Mult	iple Responses	S	123

CHAPTER SIX: SYNTHESIS AND CHARACTERIZATION OF CARBON NANOTUBES/INORGANIC HYBRID AS POTENTIAL FILLER FOR POLYMER COMPOSITES

6.1	Overvie	ew	128
	6.1.1	Carbon Yields	128
	6.1.2	XRD Analysis of CNTs/Inorganic	129
	6.1.3	SEM Analysis of CNTs/Inorganic	130
	6.1.4	TEM Analysis of CNTs/Inorganic	134
	6.1.5	Raman Analysis of CNTs/Inorganic	137
6.2	Compa	rative Study Between Phenolic Filled with HYB _{CA} , HYB _{DO} and	
	HYB_{TA}	Hybrid Compound	139
	6.2.1	Effect of Different Carbon Nanotubes/Inorganic Hybrid on the	
		Thermal Conductivity of the Phenolic Composites	140
	6.2.2	Effect of Different CNTs/Inorganic Hybrid on the Hardness of t	he
		Phenolic Composites	142
CHAI	PTER S	EVEN: CONCLUSION	
7.1	Conclu	sion	144
7.2	Sugges	tion for future work	146
REFE	ERENCE	CS .	147
LIST	OF PUB	BLICATIONS	

LIST OF TABLES

		Page
Table 3.1	General properties of phenolic	44
Table 3.2	General properties of support materials	44
Table 3.3	Properties of the alumina powder	46
Table 3.4	Properties of the CNTs	46
Table 3.5	Properties of the methane gas	47
Table 3.6	Properties of the nitrogen gas	47
Table 3.7	Properties of the hydrogen gas	48
Table 3.8	Materials used for catalyst/alumina preparation	48
Table 3.9	Catalyst and hybrid samples with different calcination temperatures	52
Table 3.10	Catalyst and hybrid samples with different calcination durations	52
Table 3.11	Materials used for catalyst preparation with different types of support	53
Table 3.12	Sample descriptions for the CNTs hybrid with different type of inorganic	54
Table 3.13	Composites descriptions for CNTs hybrid filled phenolic	55
Table 3.14	The coded and the actual values of experimental conditions for wear and friction test of phenolic hybrid composites	62
Table 4.1	Raman intensity of CNTs/alumina hybrid synthesis using CVD method with different calcination temperatures	73
Table 4.2	Raman intensity of CNTs-alumina synthesis via CVD method with different durations	79
Table 4.3	Raman intensity of CNTs/alumina hybrid (HYB hybrid compound and PHY hybrid)	86

Table 5.1	Experimental design and result of 5HYB/PHENOLIC hybrid composites	103
Table 5.2	Experimental design and result of 5PHY/PHENOLIC hybrid composites	103
Table 5.3	Estimated regression coefficients and analysis of variance for volume loss of 5HYB/PHENOLIC hybrid composites	105
Table 5.4	Estimated regression coefficients and analysis of variance for average COF of 5HYB/PHENOLIC hybrid composites	106
Table 5.5	Estimated regression coefficients and analysis of variance for volume loss of 5PHY/PHENOLIC hybrid composites	107
Table 5.6	Estimated regression coefficients and analysis of variance for average COF of 5PHY/PHENOLIC hybrid composites	108
Table 5.7	Paired t-test for volume loss of 5PHY/PHENOLIC versus 5HYB/PHENOLIC hybrid composites	119
Table 5.8	Paired t-test for average COF of 5PHY/PHENOLIC versus 5HYB/PHENOLIC hybrid composites	123
Table 5.9	The target value and the upper value for 5HYB/PHENOLIC and 5PHY/PHENOLIC hybrid composites	124
Table 5.10	Predicted and measured volume loss and average COF of 5HYB/PHENOLIC hybrid composites	126
Table 5.11	Predicted and measured volume loss and average COF of 5PHY/PHENOLIC hybrid composites	127
Table 6.1	Raman intensity of CNTs/inorganic synthesis using CVD method	138

LIST OF FIGURES

		Page
Figure 2.1	Structures of single walled carbon nanotubes (SWCNTs) and multi walled carbon nanotubes (MWCNTs) (Aqel et al., 2012)	12
Figure 2.2	Three different structures of single-walled carbon nanotubes a) armchair, b) zigzag and c) chiral (Prasek <i>et al.</i> , 2011)	14
Figure 2.3	(i) The tip growth mechanism and (ii) the base growth mechanism (Ando, 2010; Ahmad <i>et al.</i> , 2013)	20
Figure 2.4	Stone wales defect (Pozrikidis, 2009)	24
Figure 2.5	Type of wear: (a) Adhesive wear, (b) Abrasive wear, (c) Fatigue wear and (d) Corrosive wear (Kato, 2002)	33
Figure 3.1	Schematic set up of CVD	49
Figure 3.2	The flow diagram of CNTs/alumina hybrid growth process using the CVD method	50
Figure 3.3	(a) Sample preparation for thermal conductivity measurement, (b) Diagram of a TPS sensor, (c) Experimental setup of sensor and samples	58
Figure 3.4	Pin on disk tester	60
Figure 3.5	Box-Behnken design (Cavazzuti, 2013)	62
Figure 4.1	Image of (a) dried NiO/Alumina powder, (b-d) CatalystA710, CatalystA910 and CatalystA1110 and (e-g) HYBA710, HYBA910 and HYBA1110	65
Figure 4.2	XRD pattern for CatalystA710, CatalystA910 and CatalystA1110 and HYBA710, HYBA910 and HYBA1110	66
Figure 4.3	FESEM micrograph of CNTs/alumina hybrid synthesis via CVD method with different calcination temperatures with 10000x magnification: a) HYBA710, b)HYBA1110 c) HYBA910	68
Figure 4.4	Weight percentages of carbon, oxygen, nickel and aluminium of CNTs/alumina hybrid synthesis via CVD method with different calcination temperatures	70

Figure 4.5	Raman spectrum of CNTs/alumina hybrid synthesis using CVD method with different calcination temperature: a) HYBA710 (700°C), HYBA910 (900°C) and HYBA1110 (1100°C)	72
Figure 4.6	Image of CNTs/alumina hybrid synthesis using CVD method with different calcination durations: a) HYBA96 (6 hours), b) HYBA98 (8 hours), c) HYBA910 (10 hours) and d) HYBA912 (12 hours)	74
Figure 4.7	XRD pattern of CNTs/alumina hybrid synthesis using CVD method with different calcination durations: a) 6 hours, b) 8 hours, c)10 hours and d)12 hours	75
Figure 4.8	FESEM image of CNTs/alumina hybrid synthesis using CVD method with different calcination duration: a) 6 hours, b)8 hours, c)10 hours and d)12 hours	76
Figure 4.9	Weight percentages of carbon, oxygen, nickel and aluminium of CNTs/alumina hybrid synthesis using CVD method with different calcination durations: HYBA96, HYBA98, HYBA910 and HYBA912	78
Figure 4.10	Raman spectrum of CNTs/alumina hybrid synthesis using CVD method with different calcination durations: a) HYBA96, HYBA98, HYBA910 and HYBA912	79
Figure 4.11	HRTEM micrograph of CNTs/alumina synthesis via CVD method: Calcined at 900°C for 10 hours and decomposition of methane at 800°C for 60 minutes	81
Figure 4.12	FESEM micrograph of (a-c) HYB hybrid compound with magnification of 5000x, 30000x and 100000x, respectively; and (d-f) PHY hybrid under magnification 5000x, 30000x and 100000x	84
Figure 4.13	Raman spectrum of CNTs/alumina hybrid: a) HYB hybrid compound and b) PHY hybrid	85
Figure 4.14	Thermal conductivity of HYB composites, PHY composites, and Pure phenolic	87
Figure 4.15	Schematic of the proposed heat flow in HYB composites and PHY composites	88
Figure 4.16	Properties of the HYB composites and PHY	90

	m/s sliding speed and 9.81 N applied load: a) volume loss b) average coefficient of friction	
Figure 4.17	HRTEM image of a) HYB composite b) PHY composite	92
Figure 4.18	Properties of the HYB composites and PHY composites after wear test with the variation of sliding speed (load: 9.81 N, Filler: 5wt%): a) volume loss and b) average coefficient of friction	94
Figure 4.19	Properties of the HYB composites and PHY composites after wear test with the variation of applied load (N) (Sliding speed: 1.022 m/s, Filler: 5 wt%): a) volume loss and b) average coefficient of friction	96
Figure 4.20	SEM micrographs of the worn surfaces for HYB composites and PHY composites under a sliding speed of 1.022 m/s and 30 N applied load (a) Pure phenolic, (b) 5 wt% PHY composite, (c) 5 wt% CVD composite. → sliding direction	98
Figure 4.21	Hardness of the HYB composites and PHY composites as a function of filler loading	99
Figure 5.1	Residual plot of volume loss 5HYB/PHENOLIC hybrid composites	112
Figure 5.2	Residual plot of average COF 5HYB/PHENOLIC hybrid composites	112
Figure 5.3	Residual plot of volume loss 5PHY/PHENOLIC hybrid composites	113
Figure 5.4	Residual plot of average COF 5PHY/PHENOLIC hybrid composites	113
Figure 5.5	Surface plots and contour plot of the combined effects of the independent variables on volume loss for 5HYB/PHENOLIC hybrid composites: (a) Load-Distance (b) Speed-Distance and (c) Load-Speed	116
Figure 5.6	Surface plots and contour plot of the combined effects of the independent variables on volume loss for 5PHY/PHENOLIC hybrid composites. (a) Load-Distance, (b) Speed-Distance and (c) Load-Speed	117
Figure 5.7	Surface plots and contour plot of the combined effect	121

	of the independent variables on average COF for 5HYB/PHENOLIC hybrid composites. (a) Load-Distance, (b) Speed-Distance and (c) Load-Speed	
Figure 5.8	Surface plots and contour plot of the combined effect of the independent variables on average COF for 5PHY/PHENOLIC hybrid composites. (a) Load- Distance, (b) Speed-Distance and (c) Load-Speed	122
Figure 5.9	Optimization plot of volume loss and average COF of 5HYB/PHENOLIC hybrid composites	125
Figure 5.10	Optimization plot of volume loss and average COF of 5PHY/PHENOLIC hybrid composites	125
Figure 6.1	The carbon $$ yield of the HYB_{CA},HYB_{DO} and HYB_{TA} hybrid compound synthesis via CVD method	129
Figure 6.2	XRD pattern of CNTs/inorganic hybrid compound	130
Figure 6.3	FESEM micrograph of HYB_{CA} synthesis via CVD method	131
Figure 6.4	FESEM micrograph of HYB_{DO} synthesis via CVD method	132
Figure 6.5	FESEM micrograph of HYB_{TA} synthesis via CVD method	132
Figure 6.6	EDX analysis result obtained from HBB_{CA} , HYB_{DO} and HBY_{TA} compound	133
Figure 6.7	HRTEM micrograph of HYB_{CA} synthesis via CVD method	134
Figure 6.8	HRTEM micrograph of HYB_{DO} synthesis via CVD method	135
Figure 6.9	HRTEM micrograph of HYB_{TA} synthesis via CVD method	136
Figure 6.10	Raman spectrum of CNTs/inorganic synthesis using the CVD method: a) HYB_{DO} , HYB_{TA} and c) HYB_{CA}	138
Figure 6.11	Thermal conductivity of the pure phenolic, and the phenolic composites with 1, 3, and 5 weight percent of PHY_{CA} , PHY_{TA} and PHY_{DO}	141
Figure 6.12	Rockwell hardness of pure phenolic and phenolic composite (P/PHY _{CA} , P/PHY _{TA} and P/PHY _{DO}) as	143

function of filler loading

LIST OF ABREVIATIONS

Al₂O₃ Alumina

ANOVA Analysis of variance

ASTM American Society for Testing Materials

BBD Box-Behnken Design

C Carbon

CaCO₃ Calcium carbonate

CaMg(Ca3)₂ Calcium magnesium carbonate

CF Carbon Fiber

CH₄ Methane

CNTs Carbon nanotubes

COF Coefficient of friction

CVD Chemical vapour deposition

DOE Design of experiment

DWCNTs Double walled carbon nanotubes

EDX Energy dispersive X-ray

FESEM Field emission scanning electron microscopy

GNP Graphene nanoplatelets

H Hydrogen

HRTEM High resolution transmission electron microscopy

MgO Magnesium oxide

MWCNTs Multi walled carbon nanotubes

Ni Nickel

NiAl₂O Nickel aluminate

O₂ Oxygen

PMC Polymer matrix composites

POD Pin-On-Disk

PP Polypropylene

RBMs Radial breathing modes

RSM Response surface methodology

SEM Scanning electron microscopy

SiC Silicon carbide

TEM Transmission electron microscopy

TPS Transient plane source

XRD X-ray Diffraction

LIST OF SYMBOLS

% Percentage

< Less than

> More than

° Degree

°C Degree Celsius

°C/min Degree Celsius per minute

F Force

g Gram

H Hour

L Litre

m Meter

min Minute

mm Millimetre

nm Nanometer

m/s Meter per second

μm Micrometer

rpm Revoltution per minute

V Wear volume loss

wt % Weight percent

w Normal load

W/mK Watts per meter kelvin

μ Coefficient of friction

SINTESIS DAN SIFAT-SIFAT KOMPOSIT BERASASKAN FENOLIK TERISI HIBRID TIUB NANO KARBON/BUKAN ORGANIK

ABSTRAK

Penggunaan pengisi tunggal dalam komposit polimer tidak selalu memenuhi syaratsyarat permintaan untuk aplikasi polimer komposit termaju. Oleh itu, adalah perlu untuk menghasilkan pengisi hibrid yang mengandungi lebih daripada satu pengisi. Kebelakangan ini, tiub nano karbon (CNTs) dihibridkan dengan pengisi yang lain untuk mencapai kesan gabungan pengisi. Gabungan pengisi-pengisi tersebut (hibrid pengisi) harus mempunyai interaksi fizikal dan kimia yang kuat antara satu sama lain untuk mencapai kesan penguatan yang optimum. Kajian ini mencadangkan kaedah pemendapan wap kimia (CVD) untuk menghasilkan hibrid CNTs dengan pengisi bukan organik dan CNTs hybrid yang disintesiskan, akan digunakan sebagai pengisi dalam komposit fenolik. Bahagian pertama kajian adalah penyiasatan mengenai hibrid CNTs/alumina dan parameter pemprosesannya seperti suhu dan tempoh pengkalsinan. Kajian perbandingan di antara CNTs hibrid menggunakan kaedah CVD dan kaedah fizikal (konvensional) ke atas sifat-sifat komposit fenolik turut dikaji. Komposit fenolik telah difabrikasikan dengan menggunakan kaedah cagak panas. Sifat tribological telah dikaji dengan menggunakan penguji pin-atas-cakra di bawah keadaan gelongsor yang berbeza. Hasil kajian menunjukkan bahawa tempoh pengkalsinan selama 10 jam pada suhu 900°C adalah parameter yang terbaik untuk menumbuhkan hibrid CNTs. Hasil kajian juga mendedahkan bahawa hibrid CNTs menggunakan cara CVD telah meningkatkan kekerasan, kekonduksian terma dan sifat-sifat tribologikal komposit fenolik hibrid. Dalam bahagian kedua kajian, model empirikal dengan pembolehubah bebas yang berbeza bagi kelakuan tribologikal untuk CNTs/alumina terisi komposit fenolik telah dibangunkan menggunakan pendekatan metodologi permukaan respon (RSM). Pengoptimuman fungsi pemboleh ubah bebas juga telah dijana. Ia menunjukkan bahawa 5HYB/FENOLIK menunjukkan prestasi kehausan yang lebih baik berbanding komposit 5PHY/FENOLIK. Dalam bahagian ketiga, kesesuaian kalsium karbonat, talkum dan dolomit untuk pertumbuhan CNTs dalam penghasilan sebatian hibrid CNTs/bukan organic menggunakan kaedah CVD telah dikaji. Hasil kajian menunjukkan bahawa CNTs tumbuh di atas partikel kalsium karbonat, talkum dan dolomit, yang mana menunjukkan bahawa mereka juga sesuai untuk menjadi bahan sokongan dalam penghasilan hibrid CNTs (pertumbuhan menggunakan pemangkin logam nikel dan metana sebagai stok suapan karbon pada suhu 800°C). Hasilnya juga mendedahkan bahawa hibrid CNTs/bukan organik meningkatkan kekerasan dan sifat terma komposit fenolik.

SYNTHESIS AND PROPERTIES OF PHENOLIC BASED HYBRID CARBON NANOTUBE/INORGANIC FILLED COMPOSITES

ABSTRACT

The use of a single filler in polymer composites does not always meet the on-demand requirements of an advanced polymer composite application. Therefore, producing a hybrid filler that contains more than one filler is necessary. Recently carbon nanotubes (CNTs) were hybridized with others fillers to achieve the combined effects of the filler. The combinations of the filler (hybrid filler) should have a strong physical and chemical interaction with each other in order to achieve the optimum reinforcing effect. This study proposed the chemical vapour deposition (CVD) method to produce a CNTs hybrid with inorganic fillers and this synthesised CNTs hybrid, was used as filler in phenolic composites. The first part of the research was the investigation of the CNTs/alumina hybrid and its processing parameter such as calcinations temperatures and duration. The comparative study of hybrid CNTs using the CVD method and the physical method (conventional) on the properties of the phenolic composite were also studied. The phenolic composites were fabricated via hot mounting process. The tribological properties were investigated using a pin-ondisk tester under different sliding conditions. The results showed that 10 hours duration of calcination and 900°C were the best parameters to growth the CNTs hybrid. The result also revealed that hybridising the CNTs via CVD improves the hardness, thermal conductivity and tribological properties of the phenolic hybrid composite. In the second part of the research, empirical models with different independent variables for the tribological behaviour of CNTs/alumina filled phenolic composites were developed using the response surface methodology (RSM) approach. The optimisation of the response as a function of the independent variable was generated. It shows that 5HYB/PHENOLIC exhibited better wear performance than 5PHY/PHENOLIC composites. In the third part, the suitability of calcium carbonate, talc and dolomite to growth the CNTs in the production of CNTs/inorganic hybrid compounds using the CVD method was investigated. The results showed that the CNTs growth on the calcium carbonate, talc and dolomite particles, which means they are also suitable as a support material in CNTs hybrids (growth using a nickel metal catalyst and methane as the carbon feedstock at 800°C). The result also revealed that the CNTs/inorganic hybrid improved the hardness and thermal properties of the phenolic composites.