

**MICROBIAL PRODUCTION OF
POLYHYDROXYBUTYRATE (PHB) BY *Burkholderia*
Cepacia BPT1213 FROM DIFFERENT CARBON
SOURCES AND ITS FERMENTATION KINETICS**

LIEW WEN CHIAN

UNIVERSITI SAINS MALAYSIA

JULY 2020



USM UNIVERSITI
SAINS
MALAYSIA



**PUSAT PENGAJIAN TEKNOLOGI INDUSTRI
UNIVERSITI SAINS MALAYSIA**

**BORANG PENYERTAAN DISERTAI MUTAKHIR
SATU (1) NASKAH**

Nama Penyelia: Dr. Lee Chee Keong

Bahagian: Teknologi Bioproses

Saya telah menyemak semua pembetulan/pindaan yang dilaksanakan oleh
~~Eneik/Puan~~/Cik Liew Wen Chian

mengemui disertainya sebagaimana yang dipersetujui oleh Panel Pemeriksa di Viva
Vocanya.

2. Saya ingin mengesahkan bahawa saya berpuashati dengan pembetulan/pindaan
yang dilaksanakan oleh calon.

Sekian, terima kasih.

Dr. Lee Chee Keong
School of Industrial Technology
Universiti Sains Malaysia
11800, USM, Penang, MALAYSIA.

(Tandatangan dan cop)

17 Julai 2020

Tarikh



**MICROBIAL PRODUCTION OF
POLYHYDROXYBUTYRATE (PHB) BY *Burkholderia
Cepacia* BPT1213 FROM DIFFERENT CARBON
SOURCES AND ITS FERMENTATION KINETICS**

by

LIEW WEN CHIAN

A dissertation submitted in the partial fulfillment of the requirements for the degree of
Bachelor of Technology (B.Tech) in the field of Bioprocess
Technology
School of Industrial Technology
Universiti Sains Malaysia

July 2020

DECLARATION BY AUTHOR

This dissertation is composed of my original work, and contains no material previously published or written by another person except where due reference has been made in the text. The content of my dissertation is the result of work I have carried out since the commencement of my research project and does not include a substantial part of work that has been submitted to qualify for the award of any other degree or diploma in any university or other tertiary institution.



LIEW WEN CHIAN

JULY 2020

ACKNOWLEDGEMENTS

Firstly, I would like to express my deepest gratitude and appreciation to my final year project supervisor, Dr. Lee Chee Keong for his patience guidance, wise advice, unconditional support and useful knowledge throughout my final year project. Without his persistent help, this dissertation would not be possible to be finished.

Secondly, I wish to show my sincere appreciation to all the Industrial Technology staff, especially lab assistants from A204, Mr. Azmaizan Yaakub and Mrs. Najmah Hamid for their generous help in providing apparatus and materials that I needed as well as giving me equipment assistance throughout my project. Furthermore, I would like to thank Mr. Basrul who helped me in the preparation of oil palm frond juices and Mr. Khairul Anuar who assisted me during GC analysis. I also wish to extend my special thanks to the School of Industrial Technology for letting me to use the equipment and facilities available throughout my project. Acknowledgement is also given to Master students, Ms. Wendy, Mr. Yong Sen and Ms. Rozi for their technical guidance. Nevertheless, I would like to credit to School of Chemical Sciences and ABrC for allowing me to use their laboratory devices.

Ultimately, the supports and encouragements from my fellow course mates and friends during my research were greatly appreciated. I like to thank the people who contributed indirectly in this research and those who names were not mentioned.

Finally, I am beyond grateful to my beloved parents for their unconditional love, caring and sacrifices for educating and preparing me for my future.

LIEW WEN CHIAN

(JULY 2020)

TABLE OF CONTENTS

Acknowledgements	iii
Table of Contents	iv
List of Tables	viii
List of Figures	ix
List of Symbols and Abbreviations	xi
Abstrak	xiii
Abstract	xv
CHAPTER 1 INTRODUCTION	
1.1 Research Background	1
1.2 Problem Statement	5
1.3 Research Scope and Objectives	6
CHAPTER 2 LITERATURE REVIEW	
2.1 Biopolymer	9
2.2 Poly-3-hydroxybutyrate, P(3HB)	11
2.3 History of P(3HB)	12
2.4 Properties of P(3HB)	14
2.5 Application of P(3HB)	17
2.6 Valeric Acid and Sodium Valerate as Precursor	19
2.7 PHB copolymer, (P(3HB-co-3HV))	20
2.8 Properties of P(3HB-co-3HV)	21
2.8.1 Chemical properties of P(3HB-co-3HV)	21
2.8.2 Physical and mechanical properties of P(3HB-co-3HV)	21
2.9 Bacteria as P(3HB) producer	22

2.10 <i>Burkholderia cepacia</i> as P(3HB) producer	25
2.11 Biosynthesis pathway of P(3HB) and P(3HB-co-3HV)	25
2.12 Fermentation Kinetic and Growth Profile	29
2.13 Renewable Carbon Source for P(3HB) Production	30
2.13.1 Banana Trunk Juices (BTJ) as Carbon Source	32
2.13.2 Molasses as Carbon Source	33
2.13.3 Oil Palm Frond Juices (OPFJ) as Carbon Source	34

CHAPTER 3 MATERIALS AND METHODS

3.1 Overall Experimental Design	35
3.2 Preparation of Carbon Sources	36
3.2.1 Extraction of Banana Trunk Juices (BTJ)	36
3.2.2 Preparation of Molasses	37
3.2.3 Extraction of Oil Palm Frond Juices (OPFJ)	38
3.3 Sugar Analysis of carbon sources (BTJ, Molasses, OPFJ) using HPLC method	38
3.4 Media Preparation	39
3.4.1 Nutrient Rich (NR) broth medium and Nutrient Agar	39
3.4.2 Mineral Salt Medium (MSM)	40
3.5 Bacterial Strain and Inoculum Preparation	41
3.6 Growth Profile Determination	42
3.7 Effect of Different Carbon Sources (BTJ, Molasses and OPFJ) on the Production of Poly (3-hydroxybutyrate), P(3HB) polymer by <i>B. cepacia</i> BPT1213	42
3.8 Fermentation Kinetics of <i>B. cepacia</i> BPT1213	43
3.9 Effect of P(3HB-co-3HV) copolymer by <i>B. cepacia</i> BPT1213 using Different Concentration of Precursors	44

3.10 Analytical Method	45
3.10.1 Cell Harvesting	45
3.10.2 Cell Freeze Drying	45
3.10.3 Cell Dry Weight (CDW) determination	46
3.10.4 Preparation of Methanolysis Solution	46
3.10.5 Methanolysis	47
3.10.6 Caprylic Methyl Ester (CME) Acid Preparation	47
3.10.7 Gas Chromatography (GC) Analysis	48
3.10.8 P(3HB) Percentage (%) and Total P(3HB) Concentration (g/L) calculation	49
3.11 SPSS analysis	49

CHAPTER 4 RESULTS AND DISCUSSION

4.1 Sugar Concentration and Composition of BTJ, Molasses and OPFJ	50
4.2 Effect of Different Carbon Sources (BTJ, Molasses and OPFJ) on the Production of Poly (3-hydroxybutyrate), P(3HB) polymer by <i>B. cepacia</i> BPT1213	55
4.3 Fermentation Kinetics of <i>B. cepacia</i> BPT1213 Grown using Different Carbon Sources	59
4.3.1 Growth Curve of <i>B. cepacia</i> BPT1213 using Different Carbon Sources	59
4.3.2 Specific Growth Rate and Doubling Time of <i>B.</i> <i>cepacia</i> BPT1213 using Different Carbon Sources	62
4.3.3 Productivity of Biomass and PHA of <i>B. cepacia</i> BPT1213 using Different Carbon Sources	65
4.4 Effect of poly(3-hydroxybutyrate-co-3-hydroxyvalerate), P(3HB-co-3HV) copolymer produced by <i>B. cepacia</i> BPT1213 using different concentrations of precursors	68

CHAPTER 5 CONCLUSIONS AND RECOMMENDATIONS FOR FUTURE

5.1 Conclusions	76
5.2 Recommendations for Future Study	78
References	79
Appendices	90

LIST OF TABLES

Table Caption	Page
2.1 Mechanical properties of polypropylene, P(3HB) and P(3HB-co-3HV)	16
2.2 Thermal and mechanical properties of P(3HB-co-3HV)	22
2.3 Carbon sources suitable for production of PHAs	32
3.1 The ingredients of nutrient rich (NR) broth medium	39
3.2 The ingredients of nutrient agar	40
3.3 Components of mineral salt medium (MSM)	41
3.4 Components of trace element	41
3.5 Gas chromatography setting for analysis of P(3HB)	48
4.1 Concentration of sugar of BTJ and OPFJ	54
4.2 Sugar composition (%) of BTJ, molasses and OPFJ	54
4.3 Comparison of PHA production by various microorganism and substrate	59
4.4 Comparison of specific growth rate and doubling time by various microorganism and substrate	64
4.5 Comparison of biomass and PHA productivity by various microorganism and substrate	67
4.6 Comparison of PHA content and total PHA concentration by various microorganism, carbon source and precursor	74

LIST OF FIGURES

Figure Caption	Page
2.1 Chemical structure of poly-3-hydroxybutyrate (P3HB)	14
2.2 Chemical structure of P(3HB-co-3HV), where x and y refer to the number of 3-HB and 3-HV comonomer subunits in the polymer chain, respectively	21
2.3 Biosynthesis pathway of P(3HB)	27
2.4 Biosynthesis pathway of P(3HB-co-3HV) copolymer	28
3.1 Diagram of overall experimental design	35
4.1 Concentration of sugar (mg/mL) in BTJ, molasses and OPFJ	52
4.2 Sugar composition of (a) BTJ, (b) molasses and (c) OPFJ	53-54
4.3 P(3HB) content (%) produced by <i>B. cepacia</i> BPT1213 using BTJ, molasses and OPFJ as carbon sources	58
4.4 PHA concentration (g/L) produced by <i>B. cepacia</i> BPT1213 using BTJ, molasses and OPFJ as carbon sources	58
4.5 Comparison of growth curve of <i>B. cepacia</i> BPT1213 utilizing BTJ, molasses and OPFJ as carbon sources for fermentation	61
4.6 Specific growth rate, μ (h^{-1}) and doubling time, t_d (h) of <i>B. cepacia</i> BPT1213 utilizing BTJ, molasses and OPFJ as carbon sources for fermentation	63
4.7 Productivity of biomass (g/hL) and PHA (g/hL) of <i>B. cepacia</i> BPT1213 utilizing BTJ, molasses and OPFJ as carbon sources for fermentation	66
4.8 PHA content (%) produced by <i>B. cepacia</i> BPT1213 using BTJ, molasses and OPFJ as carbon sources with the supplementation of different concentration of valeric acid	72
4.9 PHA concentration (g/L) produced by <i>B. cepacia</i> BPT1213 using BTJ, molasses and OPFJ as carbon sources with the supplementation of different concentration of valeric acid	72
4.10 PHA content (%) produced by <i>B. cepacia</i> BPT1213 using BTJ, molasses and OPFJ as carbon sources with the supplementation of different concentration of sodium valerate	73

4.11	PHA concentration (g/L) produced by <i>B. cepacia</i> BPT1213 using BTJ, molasses and OPFJ as carbon sources with the supplementation of different concentration of sodium valerate	73
------	---	----

LIST OF SYMBOLS

Symbol	Definition
°C	Degree Celsius
±	Plus Minus
+	Plus
×	Multiply
-	Minus
/	Divide
%	Percentage
>	Greater than
<	Less than
CoSO ₄	Cobalt sulphate
FeSO ₄	Iron sulphate
MnCl ₂	Manganese chloride
CaCl ₂	Calcium chloride
ZnSO ₄	Zinc sulphate
CuCl ₂	Copper (II) chloride
NaCl	Sodium chloride
(NH ₄) ₂ SO ₄	Ammonium sulphate
KBr	Potassium bromide
X _t	Biomass concentration at specific time
X ₀	Biomass concentration at t = 0

LIST OF ABBREVIATIONS

Abbreviation	Definition
<i>et al.</i>	And others
PHA	Polyhydroxyalkanoate
TCS	Type of carbon sources
VA	Valeric acid
SV	Sodium valerate
CDW	Cell dry weight
P(3HB-co-3HV)	Poly(3-hydroxybutyrate-co-3-hydroxyvalerate)
P(3HB)	Poly-3-hydroxybutyrate
mg	Milligram
mL	Millilitre
g	Gram
L	Litre
BTJ	Banana Trunk Juices
OPF	Oil Palm Frond
OPFJ	Oil Palm Frond Juices
rpm	Revolutions per minute
h	Hour
Min	Minutes
H ₂ O	Water
OD	Optical density
NR	Nutrient rich
MSM	Mineral salt medium
t _d	Doubling time
μ	Specific growth rate
P	Maximum product concentration
P ₀	Initial product concentration

**PENGHASILAN POLYHYDROXYBUTYRATE (PHB) OLEH *Burkholderia*
Cepacia BPT1213 DARIPADA SUMBER KARBOM BERBEZA DAN
KINETIK FERMENTASINYA**

ABSTRAK

Isu-isu pencemaran plastik telah menjadi ancaman besar bagi ekologi global disebabkan oleh ciri-cirinya yang tidak boleh degradasi. Oleh sebab itu, polimer bio-degradable seperti Polihidroksi alkanoats (PHA), boleh diaggap sebagai pengganti yang sesuai untuk polimer berasaskan petroleum konvensional kerana ia bersifat serupa dengan polimer sintetik dan degradasi secara lengkap. Walau bagaimanapun, homopolimer PHA, poly-3-hydroxybutyrate (P(3HB)) telah dikaji secara meluas. Dalam kajian ini, biosintesis polimer P(3HB) yang dihasilkan oleh *Burkholderia cepacia* BPT1213 dengan menggunakan sumber karbon yang berbeza seperti jus batang pisang, molases dan jus pelepah kelapa sawit telah dijalankan. Selain itu, kandungan gula (sukrosa, glukosa dan fruktosa) dalam sumber-sumber karbon ini telah dianalisis. Molasses mempunyai kandungan sukrosa, glukosa dan fruktosa tertinggi (8.41 ± 0.50 mg/mL, 35.34 ± 0.01 mg/mL and 33.88 ± 0.06 mg/mL masing-masing). Seterusnya, kajian kinetik untuk *B. cepacia* BPT1213 seperti kadar pertumbuhan spesifik, masa penggandaan, biomas dan produktiviti PHA ditentukan untuk pemahaman yang lebih baik. Di antara sumber karbon ini, molases adalah sumber karbon yang paling sesuai untuk menghasilkan PHA daripada *B. cepacia* BPT1213 yang dicatatkan pada 1.4442 ± 0.46 g/L dan produktiviti PHA dicatat pada 0.030 ± 0.0056 gL⁻¹ h⁻¹. Di samping itu, masa penggandaan dan produktiviti biojisim yang diperoleh oleh *B. cepacia* BPT1213 ketika menggunakan molases sebagai sumber karbon adalah 35.78 ± 1.65 h and 0.004 ± 0.0001 gL⁻¹ h⁻¹ masing-masing. Oleh itu, molases dan kepekatan prekursor yang berbeza (asid valerat dan natrium valerat)

digunakan untuk pengeluaran kopolimer P (3HB-co-3HV) oleh *B. cepacia* BPT1213. Walau bagaimanapun, Walau bagaimanapun, kandungan kopolimer P (3HB-co-3HV) tidak dapat dikesan, kecuali menggunakan 0.50 % natrium valerat sebagai pendahulu. Kesimpulannya, molases adalah sumber karbon yang paling sesuai untuk pengeluaran P(3HB) oleh *B. cepacia* BPT1213, sedangkan kopolimer tidak dapat dihasilkan oleh *B. cepacia* BPT1213 menggunakan asid valerat dan natrium valerat sebagai prekursor.

**MICROBIAL PRODUCTION OF POLYHYDROXYBUTYRATE (PHB) BY
Burkholderia Cepacia BPT1213 FROM DIFFERENT CARBON SOURCES
AND ITS FERMENTATION KINETICS**

ABSTRACT

The issue of plastic pollution has become a major threat to global ecology due to plastic's resilience against degradation and its proliferation in industry. As a result, the biodegradable polymer such as polyhydroxyalkanoate (PHA) is considered as a good substitute to the conventional petroleum-based polymers because of their similar material properties to synthetic polymers and complete biodegradability after disposal. However, PHA homopolymer, poly-3-hydroxybutyrate (P(3HB)) is the most common and widely studied PHA compounds. In this study, the biosynthesis of P(3HB) polymer produced by *Burkholderia cepacia* BPT1213 using different carbon source such as banana trunk juices, molasses and oil palm frond juices was studied. Besides, the sugar contents (sucrose, glucose and fructose) of these carbon sources were analysed. Molasses has the highest sucrose, glucose and fructose content (8.41 ± 0.50 mg/mL, 35.34 ± 0.01 mg/mL and 33.88 ± 0.06 mg/mL respectively). Next, kinetic study of *B. cepacia* BPT1213 such as specific growth rate, doubling time, biomass and PHA productivity were investigated for greater understanding of the fermentation efficiency. Among these carbon sources, molasses was the most suitable carbon source for PHA production by *B. cepacia* BPT1213 in which the PHA concentration recorded at 1.4442 ± 0.46 g/L and PHA productivity recorded at 0.030 ± 0.0056 gL⁻¹ h⁻¹. The doubling time and biomass productivity obtained by *B. cepacia* BPT1213 when using molasses as carbon source were 35.78 ± 1.65 h and 0.004 ± 0.0001 gL⁻¹ h⁻¹ respectively. Thus, molasses and different concentration of precursors (valeric acid and sodium valerate) were used for P(3HB-co-3HV) copolymer production by *B. cepacia* BPT1213. However, the P(3HB-co-3HV) copolymer content cannot be detected,

except when using 0.50 % sodium valerate as precursor. In conclusion, molasses was the most suitable carbon source for P(3HB) production by *B. cepacia* BPT1213 whereas the copolymer cannot be produced by *B. cepacia* BPT1213 using valeric acid and sodium valerate as precursors.